

# OVERVIEW OF FATIGUE DATA FOR HIGH FREQUENCY MECHANICAL IMPACT TREATED WELDED JOINTS

H.C. Yildirim and G.B. Marquis

**ABSTRACT** This paper provides an overview of published experimental data on the fatigue strength of welded joints improved by high frequency mechanical impact (HFMI) treatment methods. In total, 414 data points from four specimen types are available. Most tests were performed using constant amplitude  $R = 0.1$  axial tension fatigue, but some data for other  $R$  ratios, variable amplitude testing and bending fatigue are also reported. An S-N slope of  $m = 5$  gives a very good description of both individual data sets and of the composite data. Design curve recommendations for the four joint types and for the structural stress-based design curve are given. HFMI treated specimens generally follow the same trend as experimental data for hammer peened specimens, but the degree of improvement is better. Data for large structures, at stress ratios other than  $R = 0.1$  and for variable amplitude loading are still needed in order to update the IIW guideline for post-weld improvement. There is a general trend for increasing fatigue strength improvement as a function of steel yield strength but this influence needs further study in order to develop guidelines. Quality assurance measures for HFMI treatment methods must also be defined.

*IIW-Thesaurus keywords:* Fatigue improvement; High strength steels; Impact toughness; Weld toes.

## Nomenclature

A	Statistical intercept	N	Number of fatigue cycles
B	Statistical slope	$N_f$	Cycles to failure
$\hat{A}$	Estimate of the intercept	$N_i$	The number of cycles to failure of specimen i
$\hat{B}$	Estimate of the slope	$P_f$	Probability of failure
$C_i$	Fatigue capacity of specimen i	R	Stress ratio
$C_{50\%}$	Computed mean fatigue capacity of test series	$\Delta S_i$	Stress range of specimen i
$C_{97.7\%}$	Characteristic fatigue capacity of the test series	$\Delta S_{eq}$	Equivalent constant amplitude stress range
$f_y$	Yield strength	$S_{nA5}$	Nominal stress amplitude at 5 % failure probabilities
$f_u$	Ultimate tensile strength	$S_{nA95}$	Nominal stress amplitude at 95 % failure probabilities
FAT	Characteristic fatigue class in MPa at $2 \times 10^6$ cycles to failure	$T_\sigma$	Scatter range in stress
FAT <sub>97.7%</sub>	Characteristic fatigue class in MPa based on 97.7 % survival probability at $2 \times 10^6$ cycles to failure at 75 % level of confidence	$t_p$	Student distribution
k	Number of test specimens in a data set	$X_i$	$\log N_i$
$k_R$	Stress ratio correction factor	$Y_i$	$\log \Delta S_i$
$K_{hs}$	Structural hot-spot stress concentration factor	$\bar{X}$	Average of $\log N_i$
m	Slope of the S-N curve	$\bar{Y}$	Average of $\log \Delta S_i$
		$\hat{Y}$	Estimate of $\log \Delta S_i$
		$\sigma$	Standard deviation
		$\hat{\sigma}_N$	Estimate of the normal distribution variance

# 1 Introduction

In 2007 the International Institute of Welding (IIW) Commission XIII on Fatigue of Welded Components and Structures approved the best practice guideline concerning post-weld treatment methods for steel and aluminium structures [1]. This guideline covers four commonly applied post-weld treatment methods, burr-grinding, TIG re-melting (or TIG dressing), hammer peening and needle peening. Burr-grinding and TIG re-melting are generally classified as geometry improvement techniques for which the primary aim is to remove or reduce the size of the weld toe flaws and to reduce the local stress concentration due to the weld profile by achieving a smooth blend at the transition between the plate and the weld face. Hammer peening and needle peening are classified as residual stress modification techniques which eliminate the high tensile residual stress in the weld toe region and induce compressive residual stresses at the weld toe. These methods also result in a reduced stress concentration at the weld toe. The guideline also gives practical information on how to implement the four improvement technologies including good work practices, training, safety, and quality assurance.

In order to improve the reproducibility of the four methods, and to produce guidance for the degree of improvement that could be expected when using the methods in design, an inter-laboratory round-robin test programme was undertaken by IIW. Results of this round-robin programme were reported by Haagensen [2]. In this report, Haagensen reported S-N slopes ranging from  $m = 5.3$  to  $m = 12.2$  for the six laboratories who performed fatigue tests on hammer peened specimens [2]. The slope for all data collectively was  $m = 4.5$ , but the scatter was larger than that normally observed for inter-laboratory comparison studies of specimens in the as-welded condition. In spite of this,  $m = 3$  was selected as the S-N curve slope in the post-weld treatment guideline.

The IIW guideline for post-weld improvement applies to plate thickness of 6 to 50 mm for steel and 4 to 20 mm for aluminium. The improvement methods are only relevant to fatigue failures initiating from the weld toe. Thus, in some situations the analyst may also need to consider alternate failure modes. For welds improved by burr grinding or TIG re-melting or for hammer peening or needle peening of low strength steel ( $f_y < 355$  MPa), the fatigue strength benefit corresponds to an increase in allowable stress range by a factor of 1.3, corresponding to a factor of 2.2 on life (for  $m = 3$ ). However, the maximum class which can be claimed is the closest category below the FAT value obtained when the as-welded FAT value is multiplied by 1.3. For ease of computation, this corresponds to a two (2) fatigue class increase based on the IIW Fatigue Design Recommendations [3].

For aluminium and high-strength steel ( $f_y > 355$  MPa) welds improved by hammer peening or needle peening, the fatigue strength benefit consists of an upgrade by a

factor of 1.5 applied to the stress range, with a change in slope  $m = 3$  to  $m = 5$  at  $N = 1 \times 10^7$  cycles. However, the maximum class which can be claimed is the closest category below the FAT value obtained when the as-welded FAT value is multiplied by 1.5. For ease of computation, this corresponds to a three (3) fatigue class increase. For example, when a weld detail which, in the as-welded condition, would be classified as FAT 63 is hammer peened, the new FAT value is FAT 90. The highest detail class for which an improvement can be claimed is FAT 90, and the highest S-N curve that can be claimed following improvement is FAT 125. The slopes of the S-N curves follow the IIW Fatigue Design Recommendations [3].

An important practical limitation on the use of improvement techniques that rely on the presence of compressive residual stresses is that the fatigue lives are strongly dependent on the applied mean stress of the subsequent fatigue loading. In particular, the beneficial effect decreases as the maximum applied stress approaches tensile yield. Thus, in general, the techniques are not suitable for structures operating at applied stress ratios  $R > 0.5$  or maximum applied stresses above around 80 % yield. The guideline gives special limitations for high stress ratio situations. Even occasional application of high stresses in tension or compression, can also be detrimental in terms of relaxing the compressive residual stress but systematic guidelines are not yet available. Special limitations also exist for improved large-scale structures. It is recommended that for steel structures with plate thickness greater than 20 mm the benefit for hammer peening is assumed to be the same as for burr grinding and TIG dressing. Burr grinding and TIG re-melting can be applied only to conditions where the nominal stress range is less than twice the material yield strength,  $\Delta\sigma < 2f_y$ .

As previously mentioned, the existing IIW guideline allows the same degree of fatigue improvement for all steels with  $f_y > 355$  MPa. Numerous researchers have observed that the degree of improvement increases with material strength, see, e.g., Maddox [4] and Bignonnet [5]. There has been a desire to develop an IIW guideline covering high-strength steel (HSS) and, in 2003, a new round robin exercise was initiated within IIW Commission XIII. Simultaneously with the increased interest in HSS, there has been an interest in new weld improvement techniques like low transformation temperature filler material [6, 7] and HFMI treatments.

The technology for high frequency ultrasonic impact treatment was developed at the Northern Scientific and Technological Foundation in Severodvinsk, Russia in association with Paton Welding Institute in Kiev, Ukraine [8]. The past decade has seen steady increase in the number of HFMI equipment manufacturers and service providers. Numerous technologies are employed, e.g., ultrasonic piezoelectric elements, ultrasonic magnetostrictive elements or compressed air. In all cases, however, the working principal is identical: cylindrical indenters are accelerated against a workpiece with high frequency. The impacted material is plastically deformed causing both a

change in the local geometry and residual stress state in the region of impact. In comparison to hammer peening, the operation is more user-friendly and the spacing between alternate impacts on the workpiece is very small resulting in a finer surface finish. The indenters are high-strength steel cylinders and manufacturers have customized the effectiveness of their own tools by using indenters with different diameters, tip geometries or multiple indenter configurations. Devices are known by the names: ultrasonic impact treatment (UIT) [9], ultrasonic peening (UP) [10], ultrasonic peening treatment (UPT) [11, 12], high frequency impact treatment (HiFiT) [13], pneumatic impact treatment (PIT) [14], and ultrasonic needle peening (UNP) [15, 16].

The choice of  $m = 3$  for the S-N curve slope in the post-weld improvement guideline results in conservative design curves in the high cycle fatigue regime but less conservative or even non-conservative results for lower cycles to failure, i.e.,  $N = 1 \times 10^4$ . Individual experimental studies for HFMI treatments also typically observe that the slope of the best-fit line through the S-N data is typically greater than the  $m = 3.0$  used in the IIW guideline. The goal of the current study has been to collect and assess the available fatigue test data for a variety of HFMI treatments. Special attention is given to the S-N slope because the assumed S-N slope has a major impact on the measured degree of fatigue strength improvement and will eventually influence

the improvement factors proposed for HSS. Virtually all the testing has been done using constant amplitude testing at  $R = 0.1$ , but some constant amplitude tests and other R ratios and variable amplitude tests are available and have been reported. From a mechanical point of view, the HFMI techniques are considered to most closely resemble hammer peening. For this reason, a comparison is made between fatigue data following HFMI treatment and hammer peening.

## 2 Methods

### 2.1 Published data

The authors were able to locate 18 publications containing fatigue data for welded steel joints improved by one of the HFMI methods mentioned in the introduction. Some of these studies contained multiple materials, improvement techniques of specimen types. Thus, a total of 45 data sets for four specimen types have been reviewed. Data sets contained between 5 and 21 test results. Many of the references considered in this study provide fatigue data only as points on a graph. When numerical values were not provided, they were extracted from the S-N plots using open source software. This was not considered to introduce significant errors in the results or conclusion.

Table 1 – Extracted experimental fatigue data for HFMI treated longitudinal welds (constant amplitude axial loading)

Ref.	Steel type	$f_y$ [MPa]	$f_u$ [MPa]	R	Method	Plate thickness [mm]	Best-fit m	k	% imp. at $m = 5$ to IIW <sup>d</sup>	% imp. at $m = \text{free}$ to IIW <sup>d</sup>
[17]	S700	700 <sup>a</sup>	750 <sup>c</sup>	0.1	UP+UIT	8	5.5	16	69	74
[18]	S690QL	786 <sup>b</sup>	870 <sup>b</sup>	0.1	UIT	16	4.5	16	81	78
[18]	S690QL	786 <sup>b</sup>	870 <sup>b</sup>	0.1	HiFiT	16	4	15	72	65
[19]	16Mn	390 <sup>a</sup>	590 <sup>a</sup>	0.1	UP/UPT	8	14	6	89	106
[20]	S350	398 <sup>b</sup>	503 <sup>b</sup>	0.1	UP/UPT	12	5.3	5	93	98
[20]	S700	780 <sup>b</sup>	850 <sup>b</sup>	0.1	UP/UPT	12	3.9	7	79	69
[20]	S900	900 <sup>b</sup>	1 010 <sup>b</sup>	0.1	TIG+UP	12	4.48	10	118	110
[21]	SS800	700 <sup>b</sup>	830 <sup>b</sup>	0.1	UP/UPT	8	9.4	8	154	173
[21]	16Mn	390 <sup>b</sup>	591 <sup>b</sup>	0.1	UP/UPT	8	15.8	6	92	111
[21]	Q235B	267 <sup>b</sup>	435.5 <sup>b</sup>	0.1	UP/UPT	8	11.7	7	101	99
[22]	S355	355 <sup>a</sup>	600 <sup>a</sup>	0.1	UIT	8	3.71	10	170	153
[23]	S355J2	390 <sup>a</sup>	545 <sup>a</sup>	0.5	UIT	30	2.97	7	~0	10
[24]	S960	969 <sup>b</sup>	1 104 <sup>b</sup>	-1	UIT	6	4.81	11	308	307
[24]	S700	700 <sup>a</sup>	750 <sup>b</sup>	-1	UIT	8	4.24	5	169	163
[25]	SBHS500	572 <sup>b</sup>	661 <sup>b</sup>	< 0.5	UIT	12	5.37	10	18	22
[25]	SBHS500	572 <sup>b</sup>	661 <sup>b</sup>	0.5	UIT	12	3.83	12	7	~0
[25]	SBHS500	572 <sup>b</sup>	661 <sup>b</sup>	> 0.5	UIT	12	3.09	11	1	~0
[26]	S960	960 <sup>a</sup>	980 <sup>c</sup>	0.1	PIT	5	6	11	191	206

<sup>a</sup> Nominal value.

<sup>b</sup> Measured value.

<sup>c</sup> Not reported at the reference, but estimated using datasheets [27], [28] and [29].

<sup>d</sup> In comparison to  $P_f = 50\%$  values from Table 5.

The specimen types were longitudinal attachments, T-joints, transverse attachments, and butt joints. The T-joints were loaded in bending while the others were axially loaded. Virtually all tests were performed using constant amplitude at  $R = 0.1$ , but some tests at alternate R ratios ( $-1 \leq R \leq 0.5$ ) or with variable amplitude loading were also reported. Weld toe failures are taken into account for analyses. Run-outs were excluded. The yield stress of steel grades varies from 260 to 969 MPa, and the specimen thickness varies from 5 to 30 mm. Data are summarized in Tables 1-4.

Tables 1-4 show the specimen type, thickness, high frequency improvement method, and R ratio for each data set. The number of test specimens, k, and best-fit S-N slope based on linear regression is also reported. The FAT class of each specimen type is taken from the IIW Recommendation [3] and the stress range corresponding to 50 % survival probability for as-welded specimens at  $N = 2 \times 10^6$  are typical values used by the International Institute of Welding [39]. These are presented in Table 5.

Some of material properties in Tables 1-4, such as yield strength,  $f_y$ , and ultimate tensile strength,  $f_u$ , are not fully defined in the references. In such cases, values are taken from published datasheets [27], [28], [29] and the corresponding superscripts <sup>b</sup> and <sup>c</sup> are used in Tables 2, and 1 and 4 respectively. The last two columns in Tables 1-4 show the calculated fatigue strength improvement with respect to the 50 % failure probability stress range for the fatigue strength improvement [%] is computed assuming both a fixed S-N slope  $m = 5$  and based on the best-fit regression line for the respective data set.

### 2.2 Statistical methods

Fatigue test data includes k data points representing  $\log \Delta S_i$  and  $\log N_i$ , where  $S_i$  is the stress range, and  $N_i$  is the endurance in cycles. Special attention should be given when representing  $\log \Delta S_i$  on the vertical axis and  $\log N_i$  on the horizontal axis in an S-N plot. The statistically appropriate approach in linear regression analysis is to assume that the independent variable is plotted on the horizontal

Table 2 – Extracted experimental fatigue data for HFMI treated T-joint welds (constant amplitude bending loading)

Ref.	Steel type	$f_y$ [MPa]	$f_u$ [MPa]	R	Method	Plate thickness [mm]	Best-fit m	k	% imp. at m = 5 to IIW <sup>c</sup>	% imp. at m = free to IIW <sup>c</sup>
[30]	S420	420 <sup>a</sup>	490 <sup>b</sup>	0.1	UIT	20	11.70	8	166	198
[31]	S700	700 <sup>b</sup>	750 <sup>b</sup>	0.1	UIT	6	6.9	10	194	256
[32]	S700	700 <sup>a</sup>	800 <sup>a</sup>	0.1	UIT	6	4	21	258	238
[33]	S420	420 <sup>a</sup>	490 <sup>b</sup>	0.1	UIT	20	7.5	7	161	181
[26]	S960	960 <sup>a</sup>	980 <sup>b</sup>	0.1	PIT	5	3.65	7	154	119

<sup>a</sup> Nominal value.  
<sup>b</sup> Not reported at the reference, but estimated using datasheets [27], [28] and [29].  
<sup>c</sup> In comparison to  $P_f = 50\%$  values from Table 5.

Table 3 – Extracted experimental fatigue data for HFMI treated transverse attachment (constant amplitude axial loading)

Ref.	Steel type	$f_y$ [MPa]	$f_u$ [MPa]	R	Method	Plate thickness [mm]	Best-fit m	k	% imp. at m = 5 to IIW <sup>c</sup>	% imp. at m = free to IIW <sup>c</sup>
[34]	S355J2	398.3 <sup>b</sup>	537.2 <sup>b</sup>	0.1	UIT	12	6.6	7	106	141
[34]	S355J2	398.3 <sup>b</sup>	537.2 <sup>b</sup>	0.1	UIT	12	11.1	4	47	205
[34]	S460ML	503.5 <sup>b</sup>	553.4 <sup>b</sup>	0.1	UIT	12	5.27	5	105	113
[34]	S460ML	503.5 <sup>b</sup>	553.4 <sup>b</sup>	0.1	UIT	12	6.09	5	128	153
[34]	S690QL	812.8 <sup>b</sup>	870.8 <sup>b</sup>	0.5	UIT	12	7.22	6	33	70
[35]	S260	260 <sup>a</sup>	465 <sup>a</sup>	0.0	UIT	20	9.55	9	61	72
[36]	S355J2	477 <sup>b</sup>	556 <sup>b</sup>	0.1	PIT	12	11.6	8	132	170
[36]	S690QL	781 <sup>b</sup>	827 <sup>b</sup>	0.1	PIT	12	6.5	7	164	177
[37]	AH36	392 <sup>b</sup>	520 <sup>b</sup>	0.1	UIT	20	8.9	3	117	139
[37]	AH36	392 <sup>b</sup>	520 <sup>b</sup>	0.1	UIT	20	6.25	3	83	95
[37]	AH36	392 <sup>b</sup>	520 <sup>b</sup>	0.5	UIT	20	8.38	3	30	36
[37]	AH36	392 <sup>b</sup>	520 <sup>b</sup>	-1	UIT	20	18	3	249	276

<sup>a</sup> Nominal value.  
<sup>b</sup> Measured value.  
<sup>c</sup> In comparison to  $P_f = 50\%$  values from Table 5.

Table 4 – Extracted experimental fatigue data for HFMI treated butt joint welds (constant amplitude axial loading)

Ref.	Steel type	$f_y$ [MPa]	$f_u$ [MPa]	R	Method	Plate thickness [mm]	Best-fit m	k	% imp. at m = 5 to IIW <sup>d</sup>	% imp. at m = free to IIW <sup>d</sup>
[18]	S355J2	422 <sup>b</sup>	524 <sup>b</sup>	0.1	UIT	16	7	14	76	79
[18]	S355J2	422 <sup>b</sup>	524 <sup>b</sup>	0.1	HiFIT	16	4.2	18	75	68
[18]	S690QL	786 <sup>b</sup>	870 <sup>b</sup>	0.1	UIT	16	4.5	18	122	120
[18]	S690QL	786 <sup>b</sup>	870 <sup>b</sup>	0.1	HiFIT	16	3.36	12	120	99
[18]	S355J2	422 <sup>b</sup>	524 <sup>b</sup>	0.5	UIT	16	8.9	15	31	35
[18]	S355J2	422 <sup>b</sup>	524 <sup>b</sup>	0.5	HiFIT	16	9	11	15	27
[18]	S690QL	786 <sup>b</sup>	870 <sup>b</sup>	0.5	UIT	16	5	10	48	49
[18]	S690QL	786 <sup>b</sup>	870 <sup>b</sup>	0.5	HiFIT	16	5	12	44	44
[38]	E690	763 <sup>b</sup>	836 <sup>b</sup>	0.1	UP	9.5	3.74	8	89	79
[26]	S960	960 <sup>a</sup>	980 <sup>c</sup>	0.1	PIT	5	7.78	7	192	196

<sup>a</sup> Nominal value.  
<sup>b</sup> Measured value.  
<sup>c</sup> Not reported at the reference, but estimated using datasheets [27], [28] and [29].  
<sup>d</sup> In comparison to  $P_f = 50\%$  values from Table 5.

Table 5 – FAT values for different types of test specimens

Specimen type	FAT values [MPa] according to IIW [3]	Calculated $\Delta S$ [MPa] for $P_f = 50\%$ at $N_f = 2 \times 10^6$	$\sigma$ in Log(N) [39]
Longitudinal attachment	71	97	0.206
T-joint	80	110	0.206
Transverse attachment	80	110	0.206
Butt joint	90	123	0.206

86

axis and the dependent variable on the vertical axis, i.e., for historic reasons fatigue data is plotted contrary to current scientific practice.

Statistical methods are used in this section to assess the best-fit S-N slopes, the confidence interval of the S-N slope and the observed degree of improvement in fatigue strength at  $N = 2 \times 10^6$  for a specified S-N slope.

As is normally assumed, the S-N relationship is represented by a linear model  $\log N_i = A + B \log \Delta S_i$  and fitted to each set of results in Tables 1-4 by regression analysis. Confidence intervals associated with a defined confidence level for both A (intercept) and B (slope) were evaluated based on the Student distribution,  $t_p$ , as described as ASTM standard practice [40]. Values of  $t_p$  were taken directly from probability tables. A cumulative probability of 97.7 % is chosen in this exercise. Parameter A is given by Equation (1);

$$\hat{A} \pm t_p \hat{\sigma}_N \left[ \frac{1}{k} + \frac{\bar{X}^2}{\sum_{i=1}^k (X_i - \bar{X})^2} \right]^{1/2} \quad (1)$$

and for B is given by Equation (2);

$$\hat{B} \pm t_p \hat{\sigma}_N \left[ \sum_{i=1}^k (X_i - \bar{X})^2 \right]^{-1/2} \quad (2)$$

where

the symbol “caret” ( $\hat{\phantom{x}}$ ) denotes estimate,

the symbol “over bar” ( $\bar{\phantom{x}}$ ) denotes average and

k is the number of specimens.

The expression for estimating the variance of the normal distribution ( $\hat{\sigma}_N$ ) for log N can be calculated by Equation (3).

$$\hat{\sigma}_N^2 = \left[ \frac{\sum_{i=1}^k (Y_i - \hat{Y}_i)^2}{k - 2} \right]^{1/2} \quad (3)$$

With respect to the observed degree of improvement in fatigue strength at  $N = 2 \times 10^6$  for a specified S-N slope, fatigue data is evaluated according to Equations (4)–(8).

$$\Delta S_i^m \times N_i = C_i = \text{FAT}^m \times 2 \times 10^6 \quad (4)$$

$$\log C_{50\%} = \frac{\sum \log C_i}{k} \quad (5)$$

$$\sigma = \sqrt{\frac{\sum (\log C_i - \log C_{50\%})^2}{k - 1}} \quad (6)$$

$$\text{Log } C_{97.7\%} = \text{log } C_{50\%} - 2 \times \sigma \quad (7)$$

$$\text{FAT}_{97.7\%} = \sqrt[m]{\frac{C_{97.7\%}}{2 \times 10^6}} \quad (8)$$

The scatter ranges,  $T_\sigma$ , represent a measure of the scatter of the data with respect to the regression line. In Equation (9), the nominal stress amplitudes  $S_{nA5}$  and  $S_{nA95}$  refer to failure probabilities  $P_f = 5\%$  and  $P_f = 95\%$ , respectively.

$$T_\sigma = \frac{S_{nA5}}{S_{nA95}} \quad (9)$$

### 3 Results

#### 3.1 Assessment of S-N curve slopes

Test results from Tables 1-4 are statistically evaluated according to the methods in the previous section. Figures 1 to 4 present the results for each data set for the four most commonly used specimen types, longitudinal attachment, T-joint, transverse attachment and butt joint specimens, respectively. Most tests were performed using constant amplitude at  $R = 0.1$ , but some tests at alternate  $R$  ratios ( $-1$  or  $0.5$ ) are also included. In each figure, the confidence interval of the S-N slope for each study is indicated by a scatter band. The best estimate of the S-N slope is indicated by a point near the centre of the scatter band. The horizontal axes in these figures represent the number of test specimens,  $k$ , in a data set.

#### 3.2 Available experimental data

As can be seen from Figures 1-4, the S-N slope  $m = 5$  passes through or is below the scatter band for virtually all data sets for all four specimen types. Figures 5-8 present all data for a particular specimen type on a single plot. In each case, an S-N slope  $m = 5$  is assumed and the

regression lines representing the 50 % and 97.7 % survival probability lines are shown. In these plots only the fatigue data obtained using constant amplitude  $R = 0.1$  testing is considered. No adjustment has been made for the steel grade or plate thickness. Weld toe failures are taken into account for regression line analyses. Fatigue strength values for 50 % survival probability for each specimen type in the as-welded condition are taken from Table 5. Fatigue strength improvements at  $N = 2 \times 10^6$  are calculated and indicated in the plots.


Figure 9 shows available fatigue results for longitudinal non-load carrying attachments for  $R = 0.5$  and  $R = -1$  constant amplitude testing and variable amplitude loading. For the variable amplitude results, Equation (10) was used in order to obtain equivalent constant amplitude stress ranges,  $\Delta S_{eq}$  [19, 24]. Slopes for Huo *et al.* [19] and Marquis and Björk [24] studies were 14.6 and 5, respectively. Other details of the variable amplitude tests can be found in the original references. The figure also shows the regression lines from Figure 5, i.e., the 50 % and 97.7 % survival probability lines for longitudinal attachments based on constant amplitude  $R = 0.1$  and assuming  $m = 5$ .

$$\Delta S_{eq} = \sqrt[m]{\frac{\sum N_i \Delta S_i^m}{\sum N_i}} \quad (10)$$

### 4 Discussion

#### 4.1 S-N curve slopes and effect of loading

Figures 1-4 show that the horizontal line corresponding to an S-N slope  $m = 5$  passes through, or is slightly below, the scatter band computed using Equation (2) for virtually all data sets. This observation is consistent for all four specimen types. For some data sets the best-fit slope (based on  $\hat{B}$ ) is clearly greater than  $m = 5$ . In






Figure 2 – Estimates of slopes for T-joints




Figure 3 – Estimates of slopes for transverse attachments




Figure 4 – Estimates of slopes for butt joints




Figure 5 – Extracted HFMI treated fatigue data from references in Table 1 for non-load carrying longitudinal attachments at R = 0.1




Figure 6 – Extracted HFMI treated fatigue data from references in Table 2 for T-joints in bending at R = 0.1

some cases this may be due to a too narrow variation in the stress ranges used during testing. For example, in the extreme situation that all tests are performed using the same stress range, a slope  $m = \infty$  would necessarily be computed. The suitability of the slope  $m = 5$  for  $1 \times 10^4 < N < 1 \times 10^7$  is further confirmed from Figures 5-8 which present all constant amplitude R = 0.1 data for a particular specimen type on a single plot. Scatter ranges,  $T_\sigma$ , are also shown for each graph. Failures were not reported for  $N > 1 \times 10^7$  so an S-N curve slope in this region has yet to be confirmed. However, under constant amplitude loading it is advisable to follow the current IIW Fatigue Design Recommendations by using an S-N slope of  $m = 22$  for  $N > 1 \times 10^7$  [3].

In Figures 5-8 only fatigue test results obtained using constant amplitude R = 0.1 testing are presented and

used to compute the 50 % and 97.7 % survival probability regression lines. Figure 9 shows available fatigue results for longitudinal non-load carrying fillet weld attachments for R = 0.5 and R = -1 constant amplitude testing and variable amplitude loading. For reference, the 50 % and 97.7 % survival probability regression lines from Figure 5 are also shown in this figure. Most of the data points in Figure 9 are above the 97.7 % survival probability regression line (FAT 134). However, data points from Maddox *et al.* [23] fall below the line. One reason may be that a high stress ratio, R = 0.5, was used during testing. Additionally, some specimens in this study were pre-loaded before peening, while others were peened under tensile load. All other specimens presented in this overview were (apparently) HFMI treated without any pre-loading.

For the longitudinal non-load carrying fillet weld attachments used, the as-welded specimens have high tensile






Figure 7 – Extracted HFMI treated fatigue data from references in Table 3 for transverse attachments at R = 0.1




Figure 8 – Extracted HFMI treated fatigue data from references in Table 4 for butt joints at R = 0.1

welding residual stresses. This means that the fatigue life is dependent only on stress range with no influence of mean stress. Following HFMI treatment, the tensile residual stresses are removed and mean stress starts to have significant influence. The variable amplitude load spectrum used by Marquis and Björk [24] had  $R = -1$  for each cycle. The same study also reports  $R = -1$  constant amplitude fatigue data. The variable amplitude data falls approximately along the  $P_f = 50\%$  line, while constant amplitude results are significantly above this line. This is probably the result that only a fraction of the compressive portion of the fatigue cycle is damaging. Additionally, Marquis [41] has observed significantly different failure modes for these tests. Treated specimens tested using  $R = -1$  variable amplitude loading consistently failed in the weld toe region, while specimens tested at  $R = -1$  constant amplitude loading failed at a variety of other

locations. Data for variable loading and for  $R \neq 0.1$  is limited and more studies are needed before design guidelines can be extracted.

#### 4.2 Comparison with hammer peening

In technical literature HFMI methods are frequently qualitatively compared to hammer peening, e.g. see [23]. Figures 10-12 show a quantitative comparison of HFMI treatment and hammer peening for longitudinal non-load carrying attachments (Figure 10) [42, 43], for T-joints (Figure 11) [2, 44] and for transverse attachments (Figure 12) [45, 46]. In each of these figures the regression lines from HFMI treated welds in Figures 5, 6 or 7 are presented, i.e., the 50% and 97.7% survival probability lines for the similar weld specimen type based on constant amplitude  $R = 0.1$  and assuming  $m = 5$ .




Figure 9 – Extracted HFMI treated fatigue data from references in Table 1 for non-load carrying longitudinal attachments at constant amplitude  $R = -1$  and  $R = 0.5$




Figure 10 – Some of hammer peened data for non-load carrying longitudinal attachments [42, 43] in comparison with FAT 134 calculated in this study for HFMI treatment

It can be seen from Figures 10-12 that the S-N slope  $m = 5$  also tends to follow the trend of the hammer peened data. In each of these figures the dashed line represents the  $P_f = 50\%$  line for the HFMI treated specimens while the solid line represents  $P_f = 2.3\%$ . It can be observed that for all three specimen types, the hammer peened data tends to be lower than the HFMI data. For longitudinal non-load carrying welds (Figure 10), only one data point involving one-pass hammer peening fell below the  $P_f = 2.3\%$  line but all other data points fell between  $P_f = 2.3\%$  and  $P_f = 50\%$ . For transverse attachments (Figure 12) only two data point involving four-passes hammer peening fell below the  $P_f = 5\%$  line but many of the points from an early study by Booth [46] were above the  $P_f = 50\%$  line. For the T-joints tested in bending (Figure 11) data is

approximately evenly distributed around the  $P_f = 2.3\%$  for high frequency treated welds. Numerous discussions have suggested that the effective treatment depth of HFMI is greater than that of hammer peening. It has also been suggested that the resulting material microstructure and notch geometry in the treated region are different. However, the authors are not aware of any definitive studies which explain why HFMI treatment tends to give better fatigue strength as compared to hammer peening.

### 4.3 Structural stress for HFMI improved welds

The IIW best practice guideline concerning post-weld treatment methods for steel and aluminium structures




Figure 11 – Some of hammer peened data for T-joints [2, 44] in comparison with FAT 247 calculated in this study for HFMI treated specimens




Figure 12 – Some of hammer peened data for transverse attachment [45, 46] in comparison with FAT 164 calculated in this study

92

contains a section on recommendations related to the structural hot spot stress [1]. For non-load carrying fillet welds such as the longitudinal attachments, T-joints and transverse attachments reported here, the appropriate hot spot structural stress design curve is FAT 125 for mild steel ( $f_y < 355$  MPa) and FAT 140 for higher strength steel ( $f_y > 355$  MPa). For load-carrying butt welds the appropriate hot spot structural stress design curve is FAT 112 for mild steel ( $f_y < 355$  MPa) and FAT 125 for higher strength steel ( $f_y > 355$  MPa). Structural hot spot stress concentration factors,  $K_{hs}$ , were computed according to IIW [3] for a typical joint of each type. The nominal stress range for a specimen was multiplied by the suitable  $K_{hs}$  value for that specimen type:  $K_{hs} = 1.4$  for longitudinal attachments,

$K_{hs} = 1.2$  for transverse attachments and  $K_{hs} = 1.0$  for butt joints. Results are compiled in Figure 13. The computed FAT curves for  $P_f = 50\%$  and  $P_f = 2.3\%$  are FAT 290 and FAT 194, respectively. These are rounded down to FAT 250 and FAT 180 in order to be consistent with the IIW system. These are shown in Figure 13.

Figure 13 also shows the  $P_f = 2.3\%$  FAT lines from Figures 5, 7 and 8 which have then been multiplied by the suitable  $K_{hs}$  value for that specimen type. The resulting lines are FAT 188 for longitudinal attachments and FAT 197 for transverse attachments. These are in good agreement with a proposed hot spot structural stress design curve of FAT 180 ( $m = 5$ ) for non-load carrying




Figure 13 – Structural hot-spot stresses for axial loaded specimens in comparison with FAT values calculated in this study

HFMI treated welds. For load-carrying welds the proposed design curve is FAT 160 ( $m = 5$ ). Thus far data has not been separated based on  $f_y$  so this proposal may be slightly lowered for mild steel and increased for higher strength steel.

#### 4.4 Degree of improvement

The existing IIW guideline [1] allows up to 25 % increased design stress for mild steel ( $f_y < 355$  MPa) and up to 40 % increased design stress for steel  $f_y > 355$  MPa. Numerous researchers have observed that the degree of improvement increases with material strength even beyond this range, see, e.g., Maddox [4] and Bignonnet [5]. The constant amplitude fatigue test data at  $R = 0.1$  with  $m = 5$  for longitudinal attachments and transverse attachment

as a function of  $f_y$  is shown in Figure 14. The data generally shows an increasing trend with material strength but the large amount of variation indicates that more attention to the topic is needed. Figure 14 also shows the existing IIW rules with respect to steel strength. An additional line representing an 8 % increase in fatigue strength with yield strength above 355 MPa is also shown. This line is conservative with respect to the available data and represents a 40 % increase in allowable design stress for  $f_y = 355$  MPa and 91 % increase in design stress for  $f_y = 1\,000$  MPa.

The degree of improvement for the four weld types and the recommended FAT values for the HFMI treatment methods are summarized in Table 6. Based on experiments, the T-joints had significantly greater fatigue strength than did the transverse attachment. However, experiments for T-joints were performed using bending loading while the recommended FAT values assume axial loading as for transverse attachments. Thus the recommended FAT class is the same for both joint types. The recommendations for T-joints, transverse attachment and butt welds are higher than the IIW Recommendation for plate edges [3]. To attain such high values in practice, extra attention would need to be placed on the quality of the plate surface and edge condition both during fabrication and service.




Figure 14 – Fatigue strength improvement at  $N = 2 \times 10^6$  for HFMI treated longitudinal welded attachments and transverse attachments as a function of  $f_y$

Table 6 – Summary of FAT values [MPa] for different joint types

Stress analysis method	Nominal stress				Hot spot stress	
	Longitudinal attachment	T-Joint <sup>a</sup>	Transverse attachment	Butt weld	Non-load carrying	Load carrying
FAT value ( $P_f = 2.3\%$ ) for as-welded details according to IIW ( $m = 3$ ) [3]	71	80	80	90	100	90
FAT value ( $P_f = 2.3\%$ ) for HFMI improved welds found in this study ( $m = 5$ )	134	247	164	170	188-197	175
Fatigue strength increase at $N = 2 \times 10^6$ [%]	89	209	106	89	90-100	95
Recommended FAT value ( $P_f = 2.3\%$ ) for HFM improved welds ( $m = 5$ )	125	160	160	160	180	160

<sup>a</sup> For T-joints the experimental data was performed using bending loading but the recommended FAT values assume axial loading as for transverse attachments.

no benefit from peening  $R > 0.5$

$$k_R = 1.075 - 0.75 \times R \quad 0.1 \leq R \leq 0.5 \quad (11)$$

$$k_R = 1.0 \quad R < 0.1$$

For needle and hammer peened structures, the current IIW Fatigue Design Recommendations use slightly different stress ratio correction factors [3].

no benefit from peening  $R > 0.4$

$$k_R = 1 - R \quad 0 \leq R \leq 0.4 \quad (12)$$

$$k_R = 1.0 \quad R < 0$$

It should be noted, however, that Equation (12) is from an earlier version of the IIW best practice guideline for peened welds and that any difference will be corrected in future editions of the IIW Fatigue Design Recommendations.

In this study the HFMI improvement methods have been reported using the names: ultrasonic impact treatment, ultrasonic peening, ultrasonic peening treatment, high frequency impact treatment, pneumatic impact treatment and ultrasonic needle peening. No distinction has been made between these various technologies. All technologies have the common features in that hardened steel indenters are excited against the weld toe using some power source and the impact frequency is significantly greater ( $> 150$  Hz) than what is found in conventional hammer peening devices ( $< 80$  Hz).

## 5 Conclusions

This paper provides an overview of published experimental data on the fatigue strength of welded joints improved by HFMI treatment methods. Various high frequency mechanical impact methods are reported, but no attempt has been made to separate the methods or provide any ranking. In total, 414 data points from four specimen types

are available. Most tests were performed using constant amplitude  $R = 0.1$  axial tension fatigue, but some data for other R-ratios, variable amplitude testing and bending fatigue are also reported. Material yield strength varied from 260 MPa over 900 MPa. The extracted fatigue test data was statistically analysed in order to estimate the best slope for the S-N line and to investigate the degree of improvement for each specimen type. The following conclusions can be drawn:

1. An S-N slope of  $m = 5$  fits both the available HFMI treated fatigue data and the existing data for hammer peened welds. Thus, all of the following conclusions are based on an assumed S-N slope of  $m = 5$  and fatigue strength improvements are defined at  $N = 2 \times 10^6$ .
2. Welded specimens treated by HFMI methods tend to have slightly greater fatigue strength than do specimens treated with traditional hammer peening. Hammer peened data tends fall below the  $P_f = 50\%$  line for all specimen types.
3. A fatigue strength improvement of  $[40 + (f_y - 355) \times 0.08]\%$  was conservative with respect to the available data for fillet weld specimens tested at  $R = 0.1$ . This results in a 40% increase in allowable design stress for  $f_y = 355$  MPa and 91% increase in design stress for  $f_y = 1000$  MPa.
4. During the statistical analysis data was not separated based on material strength so the proposed following recommendations are preliminary and may require further revision based of yield strength.
  - For longitudinal attachments the respective nominal stress design fatigue classes was 125 MPa.
  - For T-joints, transverse attachments and butt joints the respective nominal stress design fatigue class was 160 MPa.
  - For non-load carrying joints, the respective hot spot stress design fatigue classes was 180 MPa.
  - For load-carrying joints, the respective hot spot stress design fatigue classes was 160 MPa.
5. R ratio rules for hammer peening seem suitable also for HFMI treated specimens but the available data is limited.

6. In the future, data obtained for stress ratios other than  $R = 0.1$  and for variable amplitude testing are needed. Also, more basic studies on residual stress stability during loading for treated welds should be encouraged. Attention must also be given to defining quality assurance procedures for HFMI treated welds. When reporting test results, researchers are encouraged to clearly define the observed failure location for each test.

## Acknowledgements

Support for this work has been partially provided by the LIGHT research programme of the Finnish Metals and Engineering Competence Cluster (FIMECC), the Finnish Funding Agency for Technology and Innovation (TEKES) and the EU Research Fund for Coal and Steel under grant agreement RFSR-CT-2010-00032 "Improving the fatigue life of high-strength steel welded structures by post-weld treatments and specific filler material".

## References

- [1] Haagensen P.J. and Maddox S.J.: IIW Recommendations on post-weld fatigue life improvement of steel and aluminium structures, IIW Doc. XIII-2200r7-10, 2010.
- [2] Haagensen, P.: IIW's round robin and design recommendations for improvement methods, in Proceedings of the IIW International Conference on Performance of Dynamically loaded welded structures., S.J. Maddox and M. Prager (eds), July 14-15, 1997, San Francisco, Welding Research Council, New York.
- [3] Hobbacher A.: IIW Recommendations for fatigue design of welded joints and components, Doc. IIW-1823, WRC Bulletin 520, The Welding Research Council, New York, 2009.
- [4] Maddox, S.J.: 2003 IIW Portevin lecture: Key developments in the fatigue design of welded constructions, Proceedings of the IIW International Conference, 10 July 2003, Welding in the World, 2003, vol 47, Special Issue, pp. 7-40.
- [5] Bignonnet A.: Improving the fatigue strength of welded steel structures, Steel in Marine Structures, Developments in Marine Technology, Proc. 3rd Intl ECSC Offshore Conference, C. Noordhoek, J. de Back (eds.), Elsevier Science Publishers, Delft, 15-18 June, 1987, pp. 99-118.
- [6] Ohta A., Watanabe O., Matsuoka K., Maeda Y., Suzuki N., Kubo T.: Fatigue strength improvement of box welds by low transformation temperature welding wire and PWHT., Doc. IIW-1480, Welding in the World, 2000, vol. 44, no. 3, pp. 52-56.
- [7] Barsoum Z. and Gustafsson M.: Fatigue of high strength steel joints welded with low temperature transformation consumables, Engineering Failure Analysis, 2009, vol. 16, no. 7, pp. 2186-2194.
- [8] Statnikov E., Trufyakov V.I., Mikheev P.P., Kudryavtsev Yu.F.: Specification for weld toe improvement by ultrasonic impact treatment, Doc. IIW-1346, Welding in the World, 2000, vol. 44, no. 1, pp. 5-7.
- [9] Applied Ultrasonics, In: <http://www.appliedultrasonics.com/>.
- [10] Integrity Testing Laboratory Inc, In: <http://itlinc.com/>.
- [11] Lets Global, In: <http://www.lets-global.com/>.
- [12] Zhao X., Wang D. and Huo L.: Analysis of the S-N curves of welded joints enhanced by ultrasonic peening treatment., Materials and Design, 2011, vol. 32, no. 1, pp. 88-96.
- [13] Pfeifer, In: <http://www.pfeifer.de/>.
- [14] Pitec, In: <http://www.pitec-gmbh.com/>.
- [15] Sonats, In: <http://www.sonats-et.com/>.
- [16] Bousseau M. and Millot T.: Fatigue life improvement of welded structures by ultrasonic needle peening compared to TIG dressing, IIW Doc. XIII-2125-06, 2006.
- [17] Haagensen P.J. and Alnes Ø.: Progress report on IIW WG2 round robin fatigue testing program on 700 MPa and 350 MPa YS Steels, IIW Doc. XIII-2081-05, 2005.
- [18] Weich, I.: Ermüdungsverhalten mechanisch nachbehandelter Schweißverbindungen in Abhängigkeit des Randschichtzustands, Fatigue behaviour of mechanical post weld treated welds depending on the edge layer condition, Technischen Universität Carolo-Wilhelmina, Doctorate Thesis, 2008 (in German).
- [19] Huo L., Wang D. and Zhang Y.: Investigation of the fatigue behaviour of the welded joints treated by TIG dressing and ultrasonic peening under variable-amplitude load. International Journal of Fatigue, 2005, vol. 27, no. 1, pp. 95-101.
- [20] Martinez L., Blom A.F., Trogen H. and Dahle T.: Fatigue behavior of steels with strength levels between 350 MPa and 900 MPa influence of post weld treatment under spectrum loading, In Blom A., ed.: Proceedings of the North European Engineering and Science Conference (NESCO): Welded High-Strength Steel Structure, Stockholm, 1997.
- [21] Wang T., Wang D., Huo L. and Zhang Y.: Discussion on fatigue design of welded joints enhanced by ultrasonic peening treatment (UPT), International Journal of Fatigue, 2009, vol. 31, no. 4, pp. 644-650.
- [22] Lihavainen V.M., Marquis G., Statnikov E.S.: Fatigue strength of a longitudinal attachment improved by

ultrasonic impact treatment, Doc. IIW-1631, *Welding in the World*, 2004, vol. 48, no. 5/6, pp. 67-73.

[23] Maddox S.J., Dore M.J. and Smith S.D.: A case study of the use of ultrasonic peening for upgrading a welded steel structure, Doc. IIW-2203, *Welding in the World*, 2011, vol. 55, no. 9/10, pp. 56-67.

[24] Marquis G. and Björk T.: Variable amplitude fatigue strength of improved HSS welds, IIW Doc. XIII-2224-08, 2008.

[25] Mori T., Shimanuki H. and Tanaka M.: Effect of UIT on fatigue strength of web-gusset welded joints considering service condition of steel structures, Doc. IIW-2318, to be published in *Welding in the World*, 2012, vol. 56, no. 9/10.

[26] Leitner M., Stoschka M., Schörghuber M. and Eichlseder W.: Fatigue behaviour of high-strength steels using an optimized welding process and high frequency peening technology, Proceedings of the IIW International Conference, Chennai, 21-22 July, 2011, IC38.

[27] SSAB: Domex 420 MC D Hot rolled, high strength, cold forming steel, DATASHEET: 11-02-03 GB8415 DOMEX.

[28] SSAB: Domex 700 MC Hot rolled, extra high strength, cold forming steel, DATA SHEET: 11-02-03 GB8421 DOMEX.

[29] SSAB: Domex 960 Structural strip steel sheet, DATA SHEET: 11-02-16 GB8435 DOMEX.

[30] Trufiakov V.I., Statnikov E.S., Mikheev P.P. and Kuzmenko A.Z.: The efficiency of ultrasonic impact treatment for improving the fatigue strength, IIW Doc. XIII-1745-98, 1998.

[31] Pedersen M., Mouritsen O.Ø., Hansen M.R., Andersen J.G. and Wenderby J.: Comparison of post-weld treatment of high-strength steel welded joints in medium cycle fatigue, Doc. IIW-2077, *Welding in the World*, 2010, vol. 54, no. 7/8, pp. R208-R217.

[32] Galtier A. and Statnikov E.: The influence of ultrasonic impact treatment on fatigue behaviour of welded joints in high-strength steel, IIW Doc. XIII-1976-03, 2003.

[33] Statnikov E.S., Muktepavel V.O. and Blomqvist A.: Comparison of ultrasonic impact treatment (UIT) and other fatigue life improvement methods, doc. IIW-1506, *Welding in the World*, 2002, vol. 46, no. 3/4, pp. 20-32.

[34] Kuhlmann U., Dürr A., Bergmann J. and Thumser R.: Effizienter Stahlbau aus höherfesten Stählen unter Ermüdungsbeanspruchung, Fatigue strength improvement for welded high strength steel connections due to the application of post-weld treatment methods, Forschungsvorhaben P620 FOSTA, Verlag und Vertriebsgesellschaft GmbH, Düsseldorf, 2006 (in German).

[35] Kudryavtsev Y., Kleiman J., Lugovskoy A., Lobanov L., Knysh V., Voitenko O. and Propenko G.: Rehabilitation and repair of welded elements and structures by ultrasonic peening, Doc. IIW-1806, *Welding in the World*, 2007, vol. 51, no. 7/8, pp. 47-53.

[36] Kuhlmann U. and Gunther H.: Experimentelle Untersuchungen zur ermüdungssteigernden Wirkung des PIT-Verfahrens, Experimental investigations of the fatigue-enhancing effect of the PIT process, Versuchsbericht, Universität Stuttgart, Institut für Konstruktion und Entwurf, September 2009 (in German).

[37] Okawa T., Shimanuki H., Funatsu Y., Nose T. and Sumi Y.: Effect of preload and stress ratio on fatigue strength of welded joints improved by ultrasonic impact treatment, IIW Doc. XIII-2377-11, 2011.

[38] Janosch J.J., Koneczny H., Debiez S., Statnikov E.C., Troufiakov V.J. and Mikhee P.P.: Improvement of fatigue strength in welded joints (in HSS and in aluminium alloys) by ultrasonic hammer peening, Doc. IIW-1300, *Welding in the World*, 1996, vol. 37, no. 2, pp. 72-82.

[39] Fricke, W.: IIW Recommendations for the fatigue assessment by notch stress analysis for welded structures, IIW Doc. XIII-2240r3-10, 2010.

[40] ASTM E739-10: Standard Practice for Statistical Analysis of Linear or Linearized Stress-Life and Strain-Life Fatigue Data, 2010.

[41] Marquis G.: Failure modes and fatigue strength of improved HSS welds, *Engineering Fracture Mechanics*, 2010, vol. 77, no.11, pp. 2051-2062.

[42] Maddox S.J.: Progress report on IIW Working Group 2 round robin fatigue testing programme, IIW Doc. XIII-WG2-104-04, 2004.

[43] Gurney T.: Effect of peening and grinding on the fatigue strength of fillet welded joints, *British Welding Journal*, December 1968, pp. 601-609.

[44] Branco, C., Infante, V. and Baptista, R.: Fatigue behaviour of welded joints with cracks, repaired by hammer peening, *Fatigue & Fracture of Engineering Materials & Structures*, 2004, vol. 27, no. 9, pp. 785-798.

[45] Manteghi S. and Maddox S.J.: Methods for fatigue life improvement of welded joints in medium and high strength steels, IIW Doc. XIII-2006-04, 2004.

[46] Booth G.: Techniques for improving the fatigue strength of plate welded joints, *Steel in Marine Structures*, SIMS-87, Paper TS 41, 1987, pp. 747-757.

### About the authors

Mr Halid Can YILDIRIM ([halidyildirim@aalto.fi](mailto:halidyildirim@aalto.fi)) and Prof. Gary B. MARQUIS ([garymarquis@aalto.fi](mailto:garymarquis@aalto.fi)) are both with Aalto University, Department of Applied Mechanics, Aalto (Finland).