



Antibacterial and wound healing activities of silver nanoparticles embedded in cellulose compared to other polysaccharides and protein polymers

Mehran Alavi · Rajender S. Varma

Received: 14 April 2021 / Accepted: 3 July 2021 / Published online: 12 July 2021
© The Author(s), under exclusive licence to Springer Nature B.V. 2021

Abstract The aggregation of silver nanoparticles (AgNPs) in colloidal solution and the oxidative cytotoxicity towards human cells are two major hindrances for their thriving medicinal applications. Their incorporation in natural polymers such as cellulose, chitosan, alginate, collagen, gelatin, silk fibroin, carrageenan, curdlan, hyaluronic acid, keratin and starch may be an alluring alternative strategy to sidestep these complications and attain advantageous wound dressings. Biocompatibility, bioavailability, biodegradability, and inherent therapeutic properties known for such polymers, would accelerate the healing of infected chronic wounds. However, the low thermal stability, mechanical strength, rapid biodegradation, and weak washing resistance properties are some of the limitations for these polymers. Herein, recent advances, present challenges, and future perspectives for AgNPs-incorporated nanocomposites (NCs) are discussed to realize the ideal

antibacterial activities by exploiting the abundant natural biopolymers.

Keywords AgNPs · Natural polymers · Biocompatibility · Antibacterial activities · Infected chronic wounds · Wound dressing

Introduction

Hemostasis, inflammation, proliferation, and tissue remodeling are four main continuous phases of wound healing, which can be slowed by bacterial and fungal infections particularly in the case of diabetic foot ulcers (DFUs) (Ezhilarasu et al. 2020). Multidrug resistant (MDR) bacteria in infected wounds can complicate this situation by their adaptation mechanisms to a wide range of conventional antibiotics. Moreover, bacterial biofilms with complex and sessile community of bacteria and fungi embedded in extracellular matrix (ECM) composed mainly of exopolysaccharides (EPS) are more resistant to penetration of antibiotics (Pouget et al. 2020). Silver nanoparticles (AgNPs) have appropriate bacteriostatic and bactericidal traits but are cytotoxicity towards eukaryotic cells and hence their limited therapeutic applications. Micro- and nanoformulations based on natural polymers with appropriate biocompatibility, bioavailability, biodegradability, and therapeutic

M. Alavi (✉)
Nanobiotechnology Laboratory, Biology Department,
Faculty of Science, Razi University, Kermanshah, Iran
e-mail: mehranbio83@gmail.com

R. S. Varma (✉)
Regional Centre of Advanced Technologies and
Materials, Czech Advanced Technology and Research
Institute, Palacky University, Šlechtitelů 27,
783 71 Olomouc, Czech Republic
e-mail: Varma.Rajender@epa.gov

attributes can reduce the side effects of AgNPs under physiological conditions (Alavi and Varma 2021; Hussein et al. 2018). As illustrated in Fig. 1, the antibacterial mechanisms of AgNPs have been studied via the interaction of Ag^+ with cell wall, membrane, and enzymes of the respiratory chain, proteins and nucleic acids of bacteria. Reactive oxygen species (ROS) such as superoxide (O_2^-) and hydroxyl radical (OH^\bullet) can ensue from the reaction of Ag^+ ions with molecular oxygen around outside and inside medium of bacteria (Alavi et al. 2019; Taran et al. 2016; Alavi and Karimi 2019, 2020; Singh et al. 2021; Alavi and Kennedy 2021).

Living organisms encompassing animals, plants, bacteria, fungi, and alga can synthesize natural polymers or biopolymers with higher biocompatibility, bioavailability, and biodegradability properties. These polymers may be classified based on their monomers, wherein polysaccharide, polypeptide, and

polynucleotides are three major forms comprising glucose, amino acids, and nucleotides (Alavi 2020; Alavi and Varma 2020). Among the natural polymers, cellulose, chitosan, alginate, collagen, gelatin, silk fibroin, hyaluronic acid, keratin, curdlan, carrageenan, and starch have garnered more attention owing to their unique physicochemical and biological properties (Table 1) (Kaczmarek et al. 2020).

Polysaccharide polymers

Cellulose

Three major properties namely biocompatibility, biodegradability, and appropriate hydrophobicity are indicated for cellulose polymer. In terms of the extraction processes for this polymer, milling, stream explosion, CO_2 explosion, wet oxidation, ozonolysis,




Fig. 1 Main antibacterial mechanisms for AgNPs in colloidal medium (Singh et al. 2021)

Table 1 Major advantages and disadvantages of each polymer discussed in this review

Polymers	Advantages	Disadvantages	References
Cellulose	Low cost, biodegradable in ecosystem, absorbance moisture easily, desirable mechanical property, biocompatible without skin irritation	Variable quality based on cellulose sources (various plants and bacteria), low wetting in composition form with hydrophobic polymers, slow rate for production, uncontrollable hydration rate	(Alavi and Webster 2021; Alavi 2019; El-Naggar et al. 2020)
Chitosan	Antibacterial property, eco-friendly, Biodegradable, Biocompatible, Bio-adhesive property, mucoadhesive character,	Low porosity, low mechanical strength, less solubility in neutral and alkaline pH, difficulty in electrospinning for pure chitosan	(Garg et al. 2019; Alavi and Rai 2021)
Alginate	Low cytotoxicity and cost, comfortable for wound dressing application, simple to manipulation and mixture production	Low efficiency in control of mechanical property, instability owing to ion-leaching	(Kurakula et al. 2020)
Gelatin	Biodegradability biocompatibility, easy swallowing, flexible in formulation	Expensive to produce, should be stored in freezer until application	(Huang et al. 2020)
Carrageenan	gel-inducing agent, food-grade biopolymer, suitable for encapsulation of therapeutic compounds	Low thermal stability which can be improved by other polymers such as chitosan	(Elnashar and Yassin 2009)
Hyaluronic acid	Promote wound healing by regulation of inflammation phase, provide skin moisture, significant clinical integration and epithelization in autograft groups	In some cases, redness and itching have been reported for wound dressings based on this polymer	(Sierra-Sánchez et al. 2020)
Pectin	Biocompatible, biodegradable, moisturizing the wound area	Sensitivity to water and degradation in physiological environment	(Shahzad et al. 2019)
Starch	Cost-effective, high abundance, nontoxic, biocompatible, and biodegradable	Weak mechanical, difficulty of gel formation, and high hydrophilic properties	(Adeli et al. 2019)
Curdlan	Increase wound healing because of their appropriate biological and mechanical properties	Poor antimicrobial activity and low control of moisture levels	(Steffens et al. 2020; Shaheen et al. 2016)
Cyclodextrin	Suitable for poorly soluble drugs, enhanced stability of drugs, the sustained and controlled release of encapsulated drugs, reduction of side effects of drugs such as irritation	High dose of drugs may be resulted from high molecular weight of this polymer, limitation in route of administration in the case of specific subtypes of this polymer such as renal toxicity of γ -CD or unsuitability of β -CD for nasal administration	(Gadade and Pekamwar 2020)
Collagen	Good biocompatibility and mechanical properties	Susceptible to sterilization process, rapid degradation via gelatinase, collagenase, and other proteinases	(Tottoli et al. 2020)
Keratin	Excellent bioactivity, activation of fibroblast cells in the wound site via stimulating the proliferation of these cells, promotion of epithelialization, increased biodegradability, tensile strength, and hydrophilicity of scaffold by adding this polymer	Poor mechanical stability, spinnability with brittle structure	(Tan et al. 2017; Naderi et al. 2020; Cruz-Maya et al. 2019; Guo et al. 2018)
Silk fibroin and Sericin	Biocompatibility, biodegradability, suitable strength mechanical properties, production in bulk for the textile, facile processability, and versatile functionalization	The difficulty to control molecular weight and the structure	(Nguyen et al. 2019; Sapru et al. 2018)

concentrated acid, diluted acid, and ionic liquids have been employed as pretreatment techniques. Depending on the cellulose sources encompassing various plant species and bacteria, different cellulose content are expected, wherein in the case of plants, waste papers from chemical pulp, reed, hemlocks, pine, sorghum, barely straw, and oat straw have the high cellulose percentages of 60–70%, 49.4%, 47.5%, 44–46%, 44.4%, 43.3%, and 41%, respectively. This issue can be critical for the high level of the cellulose purification because of the co-presence of hemicellulose and lignin with cellulose. (Bhatt and Shilpa 2014). Formed at the nano scale, cellulose nanocrystals (CNCs) and cellulose nanofibrils (CNFs) can be prepared commonly by acid hydrolysis and high pressure homogenization (Alavi 2019). These nanomaterials (NMs) are employed to improve the mechanical strength of hydrogel, cryogels, and scaffold (Abdelgawad et al. 2020). Functionalization of cellulose can be completed by targeting its hydroxyl groups to improve mechanical strength, biochemical reactivity, and absorbency in physiochemical conditions. AgNPs are often synthesized via the reduction of Ag^+ ions and stabilizing of ensuing NPs by hydroxyl groups of this polymer without any additional stabilizers (Alavi and Nokhodchi 2020). Sustained release of Ag^+ ions is critical to hinder the growth of MDR bacteria and formation of biofilm at wound site. Ag nanowires (AgNWs) with higher aspect ratio (length to diameter ratio) can improve the release of Ag^+ ions and mechanical properties of wound dressings. Stretchable wound dressing has been made combining the bacterial cellulose (BC) with AgNWs in three volume ratios of 10: 4.5, 10: 3, and 10: 1, wherein after 24 h, sustained release of Ag^+ ions was observed at the period 9 days for all volume ratios; highest tensile stress and Young's module were 1.56 MPa and 2.88

GPa, respectively for the volume ratio of 10: 4.5. Additionally, the complete wound closure after 12 days as well as significant antibacterial effect ($\approx 100\%$ after 6 h) against *E. coli* and *S. aureus* bacteria were indicated for this volume ratio (Wan et al. 2020). Wound dressings based on polymeric hydrogels encompassing AgNPs are interesting alternative to enhance the antibacterial activity with wound healing properties in vitro and in vivo. AgNPs have been loaded on hydrogel composed of cellulose carbamate using Tween 80, cetyl trimethylammonium bromide (CTAB) and rarasaponin as values of 7.53, 9.94 and 10.15 mg/g, sequentially. Compared to other groups, higher antibacterial effect was indicated for AgNPs (99.4 μg) @hydrogel-CTAB as inhibition zone diameters (IZDs) of 18.98 and 19.84 mm toward *E. coli* and *S. aureus*, which may be caused by synergistic effect of AgNPs with cellulose carbamate and CTAB surfactant. It is worth noting that CTAB has positive charge with high affinity for the negative charge of cell membranes (Bundjaja et al. 2021). Stability and durability of AgNPs is critical factor for employing these NPs in a large-scale production. There are various derivatives for cellulose such as hydroxypropyl methylcellulose and ethylcellulose, which can contribute in synthesis and stabilization of AgNPs at 25 and 4.0 $^{\circ}\text{C}$ for long period (~ 3 months). Antibacterial activity of four types of AgNPs involving bare AgNPs, ethylcellulose (EC)-AgNPs, hydroxypropyl methylcellulose (HPMC)-AgNPs, methylcellulose (MC)-AgNPs and polyethylene glycol (PEG₆₀₀₀)-AgNPs toward *E. coli* and *S. aureus* were evaluated in a comparative way. Internalization of HPMC-AgNPs > EC-AgNPs > MC-AgNPs formulations into bacteria was higher compared to PEG-AgNPs and pure AgNPs for both bacteria significantly *E. coli* (Fig. 2). Higher penetration ability of HPMC, EC, and




Fig. 2 Different internalization of AgNPs into *E. coli*: A) Control, B) PEG-AgNPs, C) MC-AgNPs, D) EC-AgNPs, and HPMC-AgNPs; scale bar is 500 nm for all images (Abdellatif et al. 2021)

MC into the bacterial cell membrane with phospholipid structure, enhanced NPs production by these cellulose derivatives, and sustained release of silver ions may be reasons for this difference (Abdellatif et al. 2021). Specifically, eco-friendliness, biocompatibility, economically viable feedstock, simple physicochemical modification, and desirable mechanical strength compared to other polymers may be considered as major advantages of this polymer for deployment as the stabilizer and the reducer in the formation of AgNPs (Blanco Parte et al. 2020). Accessibility of hydroxyl groups on the surface of cellulose facilitate the reduction process of Ag^+ ions and settling of the nucleation and growth sites for formation AgNPs and durability of antimicrobial activity of NPs with the sustain release of Ag^+ ions (Ma et al. 2021). Additionally, the distance between cellulose chains (~ 1 nm), microfibrils (~ 3 nm), microfibril bundles (~ 10 nm), bundle networks (~ 1 μm), and fibers (~ 10 μm) can easily trap Ag ions to stabilize the NPs and hinder the uncontrollable growth of the AgNPs as well as the reduction of cytotoxicity in bacteriostatic and bactericidal doses, which are unique properties for this polymer (Paajanen et al. 2019; Liu et al. 2021). Moreover, AgNPs embedded in cellulose polymer can lead to increase wound healing particularly in the case of infected wounds such as DFU type by hindering and disruption of microbial biofilm formation before the occurrence of chronic ulcers (Ezhilarasu et al. 2020). Sustained release of Ag^+ ions in cellulose scaffold can augment antibacterial activity owing to physicochemical properties of cellulose as mentioned earlier. In addition to enhanced antibacterial activity, the channels for appropriate air permeability and exudate absorption can be provided by the 3D structure of cellulose (Ye et al. 2016). In addition to the effects of size and shape, aggregated or dispersed AgNPs are two main morphological forms of NPs in colloidal solution that can significantly contribute to the differences in antibacterial activities. High electrostatic repulsion between AgNPs (prepared by 0.1 M of AgNO_3) with molecules of the ionic solution such as NaCl (1 mM), NaNO_3 (1 mM), $\text{Ca}(\text{NO}_3)_2$ (1 mM), and Na_2CO_3 (10 mM) can present the uniform dispersed NPs with zeta potential value of -37.95 mV and more antibacterial effect on *S. aureus* compared to NPs prepared by 0.01 and 0.5 M of AgNO_3 having -26.37 and -28.23 mV of zeta potential, respectively (Vanitha et al. 2017).

Additionally, based on NP synthesis route, different morphology and efficacy are expected, wherein spray technique was applied for *in-situ* synthesis of AgNPs (11–30 nm) onto and inside microfibril cellulose (MFC) and nanofibril cellulose (NFC). For this study, MFC film produced larger size AgNPs with lower antibacterial effect relative to NFC which can be explained by the less charge density of MFC compared to NFC, presumably caused by additional carboxyl and hydroxyl groups on NFC compared to MFC (Yan et al. 2016).

Chitosan

The linear polymer polysaccharide containing D-glucosamine and N-acetyl-D-glucosamine by β -(1 \rightarrow 4)-linkage is obtained from the chitin shells of shrimp and other crustaceans such as crabs and lobsters by alkaline treatment (Alavi and Rai 2019). Suitably designed scaffold with large pores size (≥ 250 μm) promote the adherence, proliferation and migration of skin cells which leads to rapid regeneration of dermal tissue. Further, chitosan ($\text{C}_{56}\text{H}_{103}\text{N}_9\text{O}_{39}$) with amine groups can interact with negative charge of cell envelope of bacteria and synergize the antibacterial activity of AgNPs. Wound dressing comprising chitosan-collagen-AgNPs (spherical by size in the range of 10–25 nm at concentration of 10 $\mu\text{g}/\text{mL}$) illustrated accelerated wound healing via promotion of the fibroblasts migration, more expression of α -smooth muscle actin (α -SMA), and macrophage performance (Fig. 3). Dead cells at wound site can be eliminated by increasing the number of IL-10 levels and M2 macrophages in inflammatory phase (J. Wang and Xu 2020). In another study, a faster wound healing by abundant granulation tissue, higher collagen formation, lower levels of macrophage and vessel density were indicated for the electrospun chitosan-based NFs containing AgNPs at concentrations of 12 and 60 mg in comparison with control samples after 14 days of treatment. Moreover, this investigation demonstrated that the inorganic ions and proteins can slow down and block the release of Ag^+ from AgNPs (Shao et al. 2019).




Fig. 3 The possible mechanisms for accelerated cutaneous wound healing by scaffold of chitosan-collagen-AgNPs; tumor necrosis factor- α (TNF- α), transforming growth factor- β (TGF- β), interleukin 6 (IL-6), interleukin 10 (IL-10), interferon

gamma (IFN- γ), α -smooth muscle actin (α -SMA), classical macrophage activation (M1) and alternative macrophage activation (M2) (Adapted and modified from (You et al. 2017) and BioRender.com)

Alginate

Brown alga such as *Turbinaria turbinata*, *Sargassum filipendula*, *Macrocystis pyrifera*, *Saccharina longicruris*, *Sargassum carpophyllum*, and *Sargassum siliquosum* as well as bacteria namely *P. aeruginosa* have the ability to produce hydrophilic polymer of alginate containing three types of block structure: G block (poly α -L-galuronic acid), M block (β -D-mannuronic acid), and MG block (both polyuronic acids) with β -(1–4) glycosidic linkage (1–4) (García-Ríos et al. 2012; Valentine et al. 2020). AgNPs have been incorporated in the matrix of sodium alginate and collagen via interactions between the amine group of

collagens and the carboxylate group of alginates with AgNPs. In this way, NaBH_4 and polyvinyl pyrrolidone (PVP) were employed, respectively as reducing and stabilizing agents to obtain spherical AgNPs with the mean particle size of 7 nm. AgNPs in concentration of 50 μM exhibited negligible cytotoxicity against NIH3T3 cell line with bacterial inhibition toward *E. coli* and *S. aureus* as inhibition zone diameters (IZDs) of 2.7 and 1.9 mm, respectively (Zhang et al. 2018). As an efficient strategy, polydopamine (PDA) spheres (a mean diameter of 0.430 μm) were decorated by AgNPs (size in the range of 50–70 nm) followed by immobilization on oxidized sodium alginate (OSA) wound dressing. Significant porosity

value of 77.30% (relative to hyaluronic acid/cationized dextran (73%) and quercetin/duck's feet collagen/hydroxyapatite (76.36%) and blood compatibility at concentration of 200 ppm made this NC ideal and safe wound dressing (Liang et al. 2020). Size, shapes, and distribution pattern of AgNPs on polymers are dependent on polymer type; Fig. 4 illustrates the different AgNPs formation on three main polysaccharides of cellulose, chitosan, and alginate origin.

Gelatin

In addition to enzymatic extraction (Ahmad et al. 2017), partial acid and alkaline hydrolysis of type I collagen from the skin, bones, cartilage, and meat can produce gelatin types A and B, respectively (Yang et al. 2019). Gelatin as an extracellular matrix (ECM) protein may be used to prepare drug and gene delivery systems, wound dressings, tissue engineering, and 3D cell culture (Han and Lv 2019; Afewerki et al. 2019). PVP-stabilized AgNPs have been aminated via 3-aminopropyltriethoxysilane (APTES) treatment at 70 °C for 12 h and incorporated in the carboxylated CNF to achieve injectable nanoformulation for wound therapy in nursing infants. This formulation was employed to accelerate inflammation and proliferation phases of wound healing by increasing the number of white blood cells (WBCs) specifically neutrophils at wound site after 14 days of treatment compared to control group of CNF/gelatin (Gou et al. 2020). It is noteworthy that in the inflammation phase, increased capillary permeability and migration of cells

particularly neutrophils to the wound tissue would help sterilize the wounds and release the proteases to remove the denatured ECM followed by transformation of monocytes into macrophages in the wound site, regulated by cytokines such as monocyte chemotactic protein-1 (MCP-1) and transforming growth factor- β (TGF- β) (J. Wang and Xu 2020). Wound healing activities for combination of metal NPs (MNPs)/metal oxide NPs (MONPs) with important growth factors (GFs) involving fibroblast growth factor (FGF), epidermal growth factor (EGF), bone morphogenic proteins (BMPs), TGF- β , vascular endothelial growth factor (VEGF), and platelet-derived growth factor (PDGF) in wounds' healing phases of hemostasis, inflammation, proliferation, and remodeling/maturation, have been reviewed previously (Alavi and Rai 2020). Incorporation of AgNPs (0.004 M) in hydrogel formulated as sodium alginate/gelatin in the ratio of 80:20 displayed prowess for the topical application with MIC values toward *Pseudomonas aeruginosa* (0.5 ppm) and *Staphylococcus aureus* (53 ppm), higher consistency and a significant epithelialization after 14 days treatment compared to control and hydrogels without AgNPs (Fig. 5) (Diniz et al. 2020).

Carrageenan (CAR)

Three types of CAR including kappa, iota, and lambda are commercial polymers, which are commonly deployed in food and pharmacy industries. The stabilization of MNPs/MONPs, gelling and thickening applications, specifically in food industry, have been




Fig. 4 TEM images of cellulose-AgNPs (8.2–40 nm) (a) (Roig-Sanchez et al. 2019), TEM images of chitosan nanofibrous scaffolds loaded with AgNPs as dark spots on the polymer

(7 nm) (b) (Sandri et al. 2019), alginate-AgNPs (10–35 nm) composite fibers (c) (by copyright permission from (Zhao et al. 2015))




Fig. 5 Histological sections (a) and images of wound closure (b) showing a striking wound healing in the period of 14 days of experiment. (Intense edema (ed), the lymphocyte-rich infiltrate (lym) and immature granulation tissue (igt), a cellular primary

fibrous scar (cfs); groups of hydrogel with AgNPs 4 mM AgNO₃ (GHP), hydrogel sodium alginate/gelatin (80:20) (GH), and control (GCTR)) (Adapted and modified from (Diniz et al. 2020))

reported for CAR as a sulfated polymer of galactose units linked alternatively by β -1,4 and α -1,3 (Pandey et al. 2020). Cryotropic hydrogel or cryogels are supermacroporous gels produced by the cryogelation of the polymeric components at the subzero temperature, which have abilities of desirable reversible transformation in response to external parameters and promotion of cellular growth and migration, suitable for tissue engineering (Nayak and Das 2018; El-Naggar et al. 2020). CAR and carboxymethyl CNC were deployed to formulate cryogel loaded AgNPs with 100% reduction ability towards *E. coli* and *S. aureus*. This polymeric composition instigated desirable controlled and sustained release by 40 μ g/mL of AgNPs within 250 min. rapid wound healing; suitable mechanical strength of this wound dressing originated from CAR and carboxymethyl CNC polymers, respectively (Abdelgawad et al. 2020). In addition to anti-planktonic and anti-biofilm activities towards *P. aeruginosa* and *S. aureus*, the stability of CAR-Ag NPs was indicated for 6 months in a colloidal medium which is due to the suitable interaction of CARs by their hydroxyl (–OH) groups with AgNPs (Goel et al. 2019).

Hyaluronic acid (HA)

HA, hyaluronate or hyaluronan, is anionic polymer of nonsulfated glycosaminoglycan (disaccharides of *N*-acetyl-D-glucosamine and D-glucuronic acid) with high molecular weight, and is present in prokaryotic and eukaryotic cells particularly in ECM section with the critical role in proliferation and migration of human cells in epithelial, neural, and connective tissues; inflammation response, angiogenesis and granulation of wounds are influenced positively by HA (Alemzadeh et al. 2020). According to molecular weight (MW) property, 1–25 \times 10⁴, 25–10 \times 10⁴, > 1 \times 10⁶, > 6 \times 10⁶ Da were indicated for low MW, medium MW, high MW and very high MW of HA, respectively. All four stages of wound healing are influenced distinctly by low and high molecular weight of HA through interaction with the CD44 receptors related to granulocytes and monocytes as well as various interleukins such as IL-6, IL-1 β , and IL-8 (Graça et al. 2020). Wrapping bacteria, reactive oxygen species (ROS) production, lipid peroxidation, membrane disruption, interaction with glutathione (GSH), adenine, and proteins leakage were indicated as the main antibacterial mechanisms

for graphene oxide (GO) (Nanda et al. 2016; Mohammed et al. 2020). HA-AgNPs NC was loaded on the GO sheet in solution of *N*-(3-Dimethylamino-propyl)-*N'*-ethylcarbodiimide hydrochloride and *N*-hydroxysuccinimide. Bactericidal activity against *S. aureus* could be synergized by heat conversion ability of HA-AgNPs-GO, resulting from the higher specific surface area of GO, under near infrared (NIR) irradiation (808 nm for 2 min) from 25.5 to 58.4 °C. Wound healing was effected by controlled release of Ag⁺ ions from HA-AgNPs under hyaluronidase enzyme (Ran et al. 2017). Inflammatory step of wound healing can be affected negatively by ROS species, which can be controlled by suitable formulations of Ag and HA. Polygalacturonic acid (PGA), an herbal polymer, was employed as a reducing and stabilizer agent to prepare AgNPs followed by incorporation in nanofibers (NFs) comprising HA and poly vinyl alcohol (PVA) by electrospinning technique. Antibacterial activities have not been observed for (PGA/HA)-PVA, while incorporation of AgNPs imparted significant antibacterial effects on *B. subtilis*, *S. aureus*, and *E. coli*. In addition, the percentages of wound contraction for (PGA/HA)-PVA and (AgNPs-PGA/HA)-PVA after 14 days were 97.42 and 99.51%, respectively relative to 92.43% for Garamycin® cream as a control group (El-Aassar et al. 2020).

Pectin

Pectin, acidic heteropolysaccharides (linear chain of alpha (1–4) linked D-galacturonic acid; C₆H₁₀O₇) with high molecular weight (194.14 g/mol), are found in the cell walls of plant species. They are used as antioxidant, emulsifiers, food coloring agent, anti-infective agent, and stabilizers of NPs in the food and pharmaceutical industries (Mercado-Mercado et al. 2020; Jiang et al. 2020). Combination of pectin with other synthetic and natural polymers has been deployed as novel wound bandages to reduce the disadvantages of each individual polymer by itself. NFs comprising AgNPs/polyvinylalcohol (PVA)/polyvinylpyrrolidone (PVP)/pectin/mafenide acetate (MF) were electrospun in the weight ratio of 0.7 and 91.8 wt% for AgNPs and PVA as well as 2.5 wt% for PVP, pectin and MF, respectively. NPs were synthesized in PVA solution and mixed in solution of pectin, MF, and PVP followed by electrospinning on a

grounded collecting drum. Higher antibacterial effect, although not adequate enough, was indicated against Gram-negative bacteria relative to Gram-positive bacteria owing to difference in thickness of bacterial cell wall. Moreover, the releases rate of AgNPs was influenced mainly by their interaction with the functional groups such as –SO₂ and –NH₂ of MF (Alipour et al. 2019). The size of AgNPs was affected by two parameters including weight percentage of pectin (extracted from citrus peel) (0.5, 1, and 2%) and temperature (20 and 60 °C), wherein smaller diameter of NPs (8 nm) was obtained for 1% of pectin in 60 °C. MIC values for pectin-AgNPs showed 31.25 and 500 μM towards *E. coli* and *S. epidermidis* after 24 incubation compared to glutathione-AgNPs with MIC amounts of 140 and 1680 μM, respectively. In this regard, the ability of pectin to adhere to the bacterial membrane enhances the antibacterial activity of AgNPs (Pallavicini et al. 2017).

Starch

Starch (C₆H₁₀O₅)_n, the linear polymer of glucose as amylose and amylopectin in the branched form, is a renewable and biodegradable polysaccharide and has been applied for various applications such as drug delivery, micro and nano formulations of therapeutic agents, production of pharmaceutical tablets (Athira et al. 2018; Chen et al. 2020). This polymer has reducing and stabilizing functions in MNPs/MONPs synthesis in one-pot operation. Synthesized Ag/Au bimetallic NPs have been shown to affect the morphology change of *E. coli* as lacking flagella in treatment samples relative to control. IC₅₀ values for these bimetallic NPs compared to AuNPs were 4.92 ± 0.81 and 6.95 ± 1.70 μg/mL against multidrug resistant (MDR) *E. coli* and methicillin-resistant *S. aureus* (MRSA) (Lomelí-Marroquín et al. 2019). Isolated starch from babassu mesocarp, a by-product of babassu oil, was utilized to synthesize AgNPs with different diameter size of 124.2, 119.1, and 181.7 nm by microwave, autoclave, and water bath methods, respectively. In a comparative way, MBC value of > 27 μg/mL was determined for all NPs as well as AgNO₃ salt against *S. aureus*. The prominent cell membrane damage, pore formation and the release of bacteria contents of *E. coli* was observed after treatment by AgNP prepared by water bath

method (at sub value of MIC = 6.75) (Bastos Araruna et al. 2020). Combination of AgNPs, starch, PVA, and GO as a scaffold showed synergic antibacterial effects with the Modulus and tensile strength of 145% and 26.81%, respectively (Usman et al. 2016). In this regard, GO can increase the antibacterial activities of AgNPs by lipid peroxidation resulting from carbon radicals (*C) and cellular membrane damage caused by sharp edge of GO (Alavi et al. 2020).

Curdlan

Curdlan polymer, a gelling agent, is a hydrophobic linear β -(1,3)-glucan with a high-molecular-weight generated as an exopolysaccharide in various species of *Agrobacterium* genus of the Rhizobiaceae family, which can have dual action as reducer and stabilizer for the formation of AgNPs. As an example, Ag-Au core-shell NPs in spherical shape with 5–15 nm were prepared by alkali treatment of curdlan via microwave irradiation technique (Shaheen et al. 2016). Curdlan at 200 mg weight was applied as the film formation agent in curdlan-AgNP composite, wherein AgNPs (20–50 nm) were prepared by glycyrrhiza polysaccharide. Dose-dependent antibacterial activity was observed for AgNPs at concentration of 4 mg relative to 2 and 1 mg against *E. coli* (Cai et al. 2019).

Cyclodextrin (CD)

Cyclodextrin (CD) belongs to a cyclic oligosaccharides family with a macrocyclic ring of glucose subunits bonded by α -1,4 glycosidic links in three main types namely 6: α -CD, 7: β -CD, and 8: γ -CD, which can be used to encapsulate hydrophobic drugs in interior section due to improve its bioavailability, solubility, and stability; α -CD and γ -CDs types are more water soluble relative to β -CD (Tian et al. 2020). Carboxymethyl- β -cyclodextrin (CM- β CD) as a derivative of CD has solubility of 50 mg/mL, which can be used to load and stabilize AgNPs in various micro and nano formulations. Two concentrations of CM- β CD involving 50 and 25 mg were reacted with chitosan (50 mg), and glutaraldehyde (0.013 mM) to produce hydrogels 1 and 2 (H1 and H2). Incorporated constant amounts of AgNPs in this formulation illustrated different antibacterial properties dependent

on CM- β CD concentration, wherein 19, 15, and 41.8 mm were observed for H1 and H2, and gentamycin (30 μ g) toward *E. coli* (Mohamadi Zahedi and Mansourpanah 2018). Gallic acid (GA) (3,4,5-trihydroxybenzoic acid) is a phenolic acid found in plants such as tea leaves, gallnuts, and oak bark and has antibacterial activities against *Listeria monocytogenes*, *Pseudomonas aeruginosa*, *E. coli*, and *S. aureus* by irreversible changes in membrane and cell wall morphology (Li et al. 2019). A synergic effect of GA and its antibacterial activity in hydrogel formulation was obtained by incorporation and loading of these materials in β -CD and GO, separately. Hydrogel film comprising PVA/GA@ β CD/Ag-GO demonstrated improved tensile strength (> 126.2 MPa), sustained and slower GA release over 2 h and higher antibacterial activity towards *E. coli* and *S. aureus* compared to PVA/GA@ β CD and PVA/ β CD (Pooresmaeil and Namazi 2019). Hydroxypropyl- β CD (HP- β CD) with solubility of 45% (w/v), as another derivative of β -CD, has been used as a delivery system to increase the solubility of therapeutic agents in aqueous media of biological conditions (Wei et al. 2017); 1 wt% AgNPs in NFs of AgNPs-HP- β CD showed 11.6 and 10.7 mm for *S. aureus* and *E. coli*, respectively. Higher antibacterial capacity and The larger fiber diameter were observed for 2 wt% AgNPs in these NFs (Celebioglu et al. 2019). Thiomers, thiolated polymers, are polymers employed in micro and nanoformulations to augment the absorption of therapeutic agents in vaginal, ocular, mouth, and nose routes. Thiomers with low molecular mass can impart higher permeability and mucoadhesive properties to polymeric formulations (Palazzo et al. 2017). For instance, β -CD-SH1200 and β -CD-SH600 illustrated 46.37- and 39.73- fold higher mucoadhesion relative to β -CDs, respectively (Moghadam et al. 2018).

Protein polymers

Collagen

Collagen has been found as the frequent protein in terrestrial and marine animals with desirable tensile strength, biocompatibility, bioavailability, and biodegradability properties for various therapeutic applications particularly tissue engineering (Lim et al. 2019; Divakar et al. 2019). Scaffold of collagen can

attract and guide the migration of fibroblast cells along a connective tissue matrix (Dill and Mörgelin 2020). By interaction with blood platelets, this polymer can lead to the wound closure and prompt the acceleration of hemostatic phase of wound healing (Ding et al. 2020). However, weak washing resistance, low thermal stability, mechanical strength, and rapid biodegradation properties are some limitations for this protein (Pietrucha 2005; El-Fiqi et al. 2013). Obtaining stable colloidal solution of AgNPs with uniform size distribution may be realized by the appropriate selection of suitable reducing/stabilizing agents. Dialdehyde xanthan gum (DXG) with favorable biocompatibility was employed to produce spherical AgNPs in the range of 12–35 nm followed by incorporation in collagen matrix by cross linkage of DXG (via Schiff's base reaction) to attain the wound dressing. In addition to antibacterial activities toward *E. coli*, *S. aureus*, and *P. aeruginosa*, this sponge illustrated the complete integrity after physical pressing in contrast to collagen sponge. Lack of collagen in wound tissue was indicated for the collagen sponge and the sterile gauze compared to collagen-AgNPs NCs after a period of 18 days treatment (Ge et al. 2018). Resistance of bacteria specifically in biofilm formation to a wide range of antibiotics has led to present the novel promising strategies such as photodynamic therapy based on metal and metal oxide NPs. In this technique, light as source of energy and photosensitizer (metal/meal oxide NPs) can inactivate bacteria via three main stages comprising light energy absorption, ROS generation followed by disruption of bacterial envelope and macromolecules (Bekmukhametova et al. 2020). The photodynamic antibacterial efficacy could be influenced by size, morphology, surface modification (changing of surface plasmon resonance), and colloidal solution properties of AgNPs, which influences the release of Ag⁺ ions in bacterial medium and also cytocompatibility of the AgNP/polymeric nanoformulation (Jose and Kuriakose 2019; Acharya et al. 2018). In the case of collagen formulation, UV-light treated GO/AgNP composite was grafted on PDA modified Ti followed by the immersion in collagen solution. Synergic cytocompatibility and bacteria killing ensued from the respective availability of collagen and AgNPs in this formulation. For antibacterial effect, the energy of visible light at 660 nm wavelength for 20 min irradiation promoted the ROS formation on the scaffold of

GO and inactivation of both Gram-positive and Gram-negative bacteria with efficacy of 96.3%–99.4%. This formulation also circumvents the disadvantages of pure collagen, specifically, the poor strength mechanics (Xie et al. 2017).

Keratin

The main component of the wool, feather, horns, hair, and hooves is keratin, which has been investigated widely owing to its intrinsic physicochemical, mechanical durability, biocompatibility, and biological properties. In contrast to other biopolymers such as chitosan, collagen, cellulose, and starch, cumbersome chemical conditions are required to dissolve this polymer in water and organic solvents for appropriate extraction. The keratin extraction may be performed via the reduction, oxidation, microbial technique, microwave irradiation, and steam explosion pathways (Feroz et al. 2020). Based on mentioned advantages, a promising nanofibrous mat can be prepared from this type of polymer for apt wound bandages and tissue engineering (Esparza et al. 2017; Guo et al. 2019). For instance, a NC of keratin, polyurethane, and AgNPs can generate desirable antimicrobial impact. In this case, human hair was used as source of keratin followed by functionalization with iodoacetic acid to prepare S-(carboxymethyl) keratin. High concentration of AgNPs (5% of silver nitrate) revealed more antibacterial effects against *E. coli* and *S. aureus* relative to polyurethane and polyurethane -S-(carboxymethyl) keratin (Y. Wang et al. 2016).

Silk fibroin (SF) and sericin

Various species of silk worm such as *Bombyx mori* can be used to extract SF (70–80%) with cytocompatibility, high adhesiveness and suitable mechanical properties emanating from fibrillar structure with the β -sheet crystal of (Gly-Ser-Gly-Ala-Gly-Ala)_n, which can promote the adhesion of platelets and proliferation of stem cells (Patil et al. 2020; Anuduang et al. 2020). Anti-adhesion, anti-planktonic, and inhibition of biofilm was indicated for AgNPs/gentamycin-loaded SF-based film of titanium. The synergic antibacterial mechanism of AgNPs and gentamycin encompasses adhering and accumulation on bacterial cell

wall and membrane, disruption of cell wall and membrane, damaging of proteins/nucleic acids, and blocking of the transcription process by binding with 16S rRNA (Zhou et al. 2017). 20–30% of silk consist of sericin protein comprising 18 amino acids (glycine and aspartic acid as abundant amino acids) with glue-like structure, moisture absorbent, hydrophilic and mechanical stretching properties (Luo and Wang 2016). Tyrosine amino acid in this protein can contribute to AgNPs formation by redox reaction. Wound dressing comprising AgNPs/sericin/PVA illustrated the disruption of cell wall and membrane of *P. aeruginosa*, *S. aureus*, and *E. coli* upon treatment for 12 h of incubation (Fig. 6) (Tao et al. 2019). Growth stages of bacteria displayed a different behavior toward antibacterial agents, wherein the lag phase for *S. aureus* (16 h) and *E. coli* (12 h) was delayed for AgNPs-sericin/PVA films prepared by UV-assisted method (He et al. 2017).

Conclusion

Toxicity of AgNPs towards eukaryotic cells is a main side effect for the applications of these MNPs in medicinal field. Many investigators have presented assorted materials in combination with AgNPs to

increase the biocompatibility of MNPs under physiological conditions. Among these, polymers specifically biopolymers have garnered more attraction owing to their desirable biocompatibility, bioavailability, weak antigenicity, and biodegradability properties. Bacterial and fungal infections are one of the most critical complications that delay the wound healing specifically in chronic infectious wounds such as DFU. Inhibition of bacterial colonization, promising swelling and porosity properties, absorption ability of blood secretions, and moist environment can be delivered by the polymer-based wound dressing. Compared to other wound dressings based on hyaluronic acid/cationized dextran and quercetin/duck's feet collagen/hydroxyapatite, NCs of OSA-PDA-AgNPs demonstrated more porosity of 77.30%. In this review, antibacterial and wound healing activities of important applicable biopolymers including cellulose, chitosan, collagen, curdlan, alginate, hyaluronic acid, silk fibroin, sericin, CAR, pectin, keratin, starch, and CD in combination with AgNPs are deliberated to acquire a clear viewpoint of these materials and their NMs forms in suitable micro and nanoformulations. Accordingly, each biopolymer can contribute to different stage of wound healing for example chitosan can increase antibacterial activities of AgNPs in infected chronic wounds and the




Fig. 6 Morphological alteration of bacterial cell envelope under treatment of sericin/PVA (SP) and NCs of SP with different concentrations of AgNPs (0.1, 0.2, and 0.5 mM/L of

AgNO_3). Complete cell wall deformation and disruption are mainly observable in the higher concentration of AgNPs; Scale bar at 1 μm ; with copyright permission from (Tao et al. 2019)

application of collagen in wound bandages can attract fibroblast cells and promote deposition of new collagen fibers to the wound area. Cationic charge of chitosan is critical for the interaction of this polymer with teichoic acids and lipoteichoic acids (containing phosphate groups) linked to respectively the peptidoglycan and the underlying plasma membrane in Gram-positive bacteria. This function can synergize the antibacterial mechanisms of AgNPs (oxidative stress, increased cell permeability, pore formation in cell envelope, blocking of electron transport chain, cell wall and membrane disruption, nucleic acid and enzymes damage) at low and safe concentrations compared to pure AgNPs. In the case of applicable wound dressing, the mechanical and chemo-physical properties of scaffold to achieve suitable water-retaining, tensile strength, and promotion of cell growth properties can be efficiently attained by cellulose and its derivatives. Cellulose derivatives including HPMC and EC displayed high physical stability and durability of AgNPs for 3 months period owing to contribution of C–O and OH groups in NPs synthesis and stabilization. Furthermore, a higher ability for internalization of cellulose functionalized AgNPs into bacteria cells was found for HPMC, EC, and MC derivatives. As an example of protein polymer, collagen has a vital role in acceleration of hemostasis phase, fibroblasts migration along a connective tissue matrix, and nucleation process in wound area. Therefore, the formulation of several polymers is more efficient relative to the combination of one polymer with AgNPs, wherein, in some cases, synthetic polymers can be tremendously helpful to increase the mechanical strength of wound dressings.

Declarations

Conflict of interest The authors declare no competing financial interest.

Ethics approval This study has not reported the results of studies involving humans and/or animals.

References

- Abdelgawad AM, El-Naggar ME, Elsherbiny DA, Ali S, Abdel-Aziz MS, Abdel-Monem YK (2020) Antibacterial cargeenan/cellulose nanocrystal system loaded with silver nanoparticles, prepared via solid-state technique. *J Environ Chem Eng* 8:104276. <https://doi.org/10.1016/j.jece.2020.104276>
- Abdellatif AAH, Alturki HNH, Tawfeek HM (2021) Different cellulosic polymers for synthesizing silver nanoparticles with antioxidant and antibacterial activities. *Sci Rep* 11:84. <https://doi.org/10.1038/s41598-020-79834-6>
- Acharya D, Singha KM, Pandey P, Mohanta B, Rajkumari J, Singha LP (2018) Shape dependent physical mutilation and lethal effects of silver nanoparticles on bacteria. *Sci Rep* 8:1–11
- Adeli H, Khorasani MT, Parvazinia M (2019) Wound dressing based on electrospun PVA/chitosan/starch nanofibrous mats: fabrication, antibacterial and cytocompatibility evaluation and in vitro healing assay. *Int J Biol Macromol* 122:238–254
- Afewerki S, Sheikhi A, Kannan S, Ahadian S, Khademhosseini A (2019) Gelatin-polysaccharide composite scaffolds for 3D cell culture and tissue engineering: towards natural therapeutics. *Bioeng Trans Med* 4:96–115
- Ahmad T, Ismail A, Ahmad SA, Khalil KA, Kumar Y, Adeyemi KD et al (2017) Recent advances on the role of process variables affecting gelatin yield and characteristics with special reference to enzymatic extraction: a review. *Food Hydrocolloids* 63:85–96. <https://doi.org/10.1016/j.foodhyd.2016.08.007>
- Alavi M (2019) Modifications of microcrystalline cellulose (MCC), nanofibrillated cellulose (NFC), and nanocrystalline cellulose (NCC) for antimicrobial and wound healing applications. *e-Polymers* 19:103–119
- Alavi M (2020) Applications of Chitosan and Nanochitosan in Formulation of Novel Antibacterial and Wound Healing Agents. In: Rai M (ed) *Nanotechnology in Skin, Soft Tissue, and Bone Infections*. Springer International Publishing, Cham, pp 169–181
- Alavi M, Jabari E, Jabbari E (2020) Functionalized carbon-based nanomaterials and quantum dots with antibacterial activity: a review. *Expert Rev Anti Infect Ther*. <https://doi.org/10.1080/14787210.2020.1810569>
- Alavi M, Karimi N (2019) Biosynthesis of Ag and Cu NPs by secondary metabolites of usnic acid and thymol with biological macromolecules aggregation and antibacterial activities against multi drug resistant (MDR) bacteria. *Int J Biol Macromol* 128:893–901. <https://doi.org/10.1016/j.ijbiomac.2019.01.177>
- Alavi M, Karimi N (2020) Hemoglobin self-assembly and antibacterial activities of bio-modified Ag-MgO nanocomposites by different concentrations of *Artemisia haussknechtii* and *Protopermaliopsis muralis* extracts. *Int J Biol Macromol* 152:1174–1185. <https://doi.org/10.1016/j.ijbiomac.2019.10.207>
- Alavi M, Karimi N, Valadbeigi T (2019) Antibacterial, anti-biofilm, anti-quorum sensing, antimotility, and antioxidant activities of green fabricated Ag, Cu, TiO₂, ZnO, and Fe₃O₄ NPs via protopermaliopsis muralis lichen aqueous extract against multi-drug-resistant bacteria. *ACS Biomater Sci Eng* 5:4228–4243. <https://doi.org/10.1021/acsbiomaterials.9b00274>
- Alavi M, Kennedy JF (2021) Recent advances of fabricated and modified Ag, Cu, CuO and ZnO nanoparticles by herbal secondary metabolites, cellulose and pectin polymers for

- antimicrobial applications. *Cellulose* 28:3297–3310. <https://doi.org/10.1007/s10570-021-03746-5>
- Alavi M, Nokhodchi A (2020) Antimicrobial and wound treatment aspects of micro- and nanoformulations of carboxymethyl, dialdehyde, and TEMPO-oxidized derivatives of cellulose: recent advances. *Macromol Biosci* 20:1900362
- Alavi M, Rai M (2019) Recent progress in nanoformulations of silver nanoparticles with cellulose, chitosan, and alginate biopolymers for antibacterial applications. *Appl Microbiol Biotechnol* 103:8669–8676
- Alavi M, Rai M (2020) Topical delivery of growth factors and metal/metal oxide nanoparticles to infected wounds by polymeric nanoparticles: an overview. *Expert Rev Anti Infect Ther* 18:1021–1032. <https://doi.org/10.1080/14787210.2020.1782740>
- Alavi M, Rai M (2021) Chapter 11 - Antibacterial and wound healing activities of micro/nanocarriers based on carboxymethyl and quaternized chitosan derivatives. In: Rai M, dos Santos CA (eds) *Biopolymer-based nano films*. Elsevier, pp 191–201
- Alavi M, Varma RS (2020) Overview of novel strategies for the delivery of anthracyclines to cancer cells by liposomal and polymeric nanoformulations. *Int J Biol Macromol* 164:2197–2203. <https://doi.org/10.1016/j.ijbiomac.2020.07.274>
- Alavi M, Varma RS (2021) Phytosynthesis and modification of metal and metal oxide nanoparticles/nanocomposites for antibacterial and anticancer activities: recent advances. *Sustain Chem Pharm* 21:100412. <https://doi.org/10.1016/j.scp.2021.100412>
- Alavi M, Webster TJ (2021) Recent progress and challenges for polymeric microsphere compared to nanosphere drug release systems: is there a real difference? *Biorg Med Chem* 33:116028. <https://doi.org/10.1016/j.bmc.2021.116028>
- Alemzadeh E, Oryan A, Mohammadi AA (2020) Hyaluronic acid hydrogel loaded by adipose stem cells enhances wound healing by modulating IL-1 β , TGF- β 1, and bFGF in burn wound model in rat. *J Biomed Mater Res B Appl Biomater* 108:555–567
- Alipour R, Khorshidi A, Shojaei AF, Mashayekhi F, Moghadam MJM (2019) Skin wound healing acceleration by Ag nanoparticles embedded in PVA/PVP/Pectin/Mafenide acetate composite nanofibers. *Polym Test* 79:106022. <https://doi.org/10.1016/j.polymertesting.2019.106022>
- Anuduang A, Loo YY, Jomduang S, Lim SJ, Wan Mustapha WA (2020) Effect of thermal processing on physico-chemical and antioxidant properties in mulberry silkworm (*Bombyx mori* L.) powder. *Foods* 9:871
- Athira GK, Jyothi AN, Vishnu VR (2018) Water soluble octenyl succinylated cassava starch-curcumin nanoformulation with enhanced bioavailability and anticancer potential. *Starch-Stärke* 70:1700178
- Bastos Araruna F, Oliveira Sousa Araruna F, Lima Alves Pereira LP, Aranha Brito MC, Veras Quelemes P, de Araújo-Nobre AR et al (2020) Green syntheses of silver nanoparticles using babassu mesocarp starch (*Attalea speciosa* Mart. ex Spreng.) and their antimicrobial applications. *Environ Nanotechnol Monit. Manage* 13:100281. <https://doi.org/10.1016/j.enmm.2019.100281>
- Bekmukhametova A, Ruprai H, Hook JM, Mawad D, Houang J, Lauto A (2020) Photodynamic therapy with nanoparticles to combat microbial infection and resistance. *Nanoscale* 12:21034–21059
- Bhatt SM (2014) Lignocellulosic feedstock conversion, inhibitor detoxification and cellulosic hydrolysis—a review. *Biofuels* 5:633–649
- Blanco Parte FG, Santoso SP, Chou C-C, Verma V, Wang H-T, Ismadji S et al (2020) Current progress on the production, modification, and applications of bacterial cellulose. *Crit Rev Biotechnol* 40:397–414
- Bundjaja V, Santoso SP, Angkawijaya AE, Yuliana M, Soetaredjo FE, Ismadji S et al (2021) Fabrication of cellulose carbamate hydrogel-dressing with rarasaponin surfactant for enhancing adsorption of silver nanoparticles and antibacterial activity. *Mater Sci Eng, C* 118:111542. <https://doi.org/10.1016/j.msec.2020.111542>
- Cai Z, Dai Q, Guo Y, Wei Y, Wu M, Zhang H (2019) Glycyrrhiza polysaccharide-mediated synthesis of silver nanoparticles and their use for the preparation of nanocomposite curdlan antibacterial film. *Int J Biol Macromol* 141:422–430. <https://doi.org/10.1016/j.ijbiomac.2019.09.018>
- Celebioglu A, Topuz F, Yildiz ZI, Uyar T (2019) One-step green synthesis of antibacterial silver nanoparticles embedded in electrospun cyclodextrin nanofibers. *Carbohydr Polym* 207:471–479. <https://doi.org/10.1016/j.carbpol.2018.12.008>
- Chen S, Wu J, Tang Q, Xu C, Huang Y, Huang D, et al (2020) Nano-micelles based on hydroxyethyl starch-curcumin conjugates for improved stability, antioxidant and anticancer activity of curcumin. *Carbohydr Polym* 228:115398
- Cruz-Maya I, Guarino V, Almaguer-Flores A, Alvarez-Perez MA, Varesano A, Vineis C (2019) Highly polydisperse keratin rich nanofibers: scaffold design and in vitro characterization. *J Biomed Mater Res, Part A* 107:1803–1813
- Dill V, Mörgelin M (2020) Biological dermal templates with native collagen scaffolds provide guiding ridges for invading cells and may promote structured dermal wound healing. *Int Wound J* 17:618–630. <https://doi.org/10.1111/iwj.13314>
- Ding C, Tian M, Feng R, Dang Y, Zhang M (2020) Novel self-healing hydrogel with injectable, pH-responsive, strain-sensitive, promoting wound-healing, and hemostatic properties based on collagen and chitosan. *ACS Biomater Sci Eng* 6:3855–3867
- Diniz FR, Maia RCAP, Rannier L, Andrade LN, Chaud V, M, da Silva CF, et al (2020) Silver nanoparticles-composing alginate/gelatine hydrogel improves wound healing in vivo. *Nanomaterials* 10:390
- Divakar P, Yin K, Wegst UGK (2019) Anisotropic freeze-cast collagen scaffolds for tissue regeneration: How processing conditions affect structure and properties in the dry and fully hydrated states. *J Mech Behav Biomed Mater* 90:350–364
- El-Aassar MR, Ibrahim OM, Fouda MMG, El-Beheri NG, Agwa MM (2020) Wound healing of nanofiber comprising Polygalacturonic/Hyaluronic acid embedded silver nanoparticles: In-vitro and in-vivo studies. *Carbohydr Polym* 238:116175. <https://doi.org/10.1016/j.carbpol.2020.116175>

- El-Fiqi A, Lee JH, Lee E-J, Kim H-W (2013) Collagen hydrogels incorporated with surface-aminated mesoporous nanobioactive glass: improvement of physicochemical stability and mechanical properties is effective for hard tissue engineering. *Acta Biomater* 9:9508–9521
- El-Naggar ME, Hasanin M, Youssef AM, Aldalbahi A, El-Newehy MH, Abdelhameed RM (2020) Hydroxyethyl cellulose/bacterial cellulose cryogel doped silver@titanium oxide nanoparticles: Antimicrobial activity and controlled release of Tebuconazole fungicide. *Int J Biol Macromol* 165:1010–1021. <https://doi.org/10.1016/j.ijbiomac.2020.09.226>
- Elnashar MMM, Yassin MA (2009) Covalent immobilization of β -galactosidase on carrageenan coated with chitosan. *J Appl Polym Sci* 114:17–24. <https://doi.org/10.1002/app.30535>
- Esparza Y, Ullah A, Boluk Y, Wu J (2017) Preparation and characterization of thermally crosslinked poly (vinyl alcohol)/feather keratin nanofiber scaffolds. *Mater Des* 133:1–9
- Ezhilarasu H, Vishalli D, Dheen ST, Bay B-H, Srinivasan DK (2020) Nanoparticle-Based Therapeutic Approach for Diabetic Wound Healing. *Nanomaterials* 10:1234
- Feroz S, Muhammad N, Ranayake J, Dias G (2020) Keratin - Based materials for biomedical applications. *Bioactive Mater* 5:496–509. <https://doi.org/10.1016/j.bioactmat.2020.04.007>
- Gadade DD, Pekamwar SS (2020) Cyclodextrin based nanoparticles for drug delivery and theranostics. *Adv Pharmac Bulletin* 10:166
- García-Ríos V, Ríos-Leal E, Robledo D, Freile-Pelegrin Y (2012) Polysaccharides composition from tropical brown seaweeds. *Phycol Res* 60:305–315
- Garg U, Chauhan S, Nagaich U, Jain N (2019) Current advances in chitosan nanoparticles based drug delivery and targeting. *Adv Pharmac Bulletin* 9:195
- Ge L, Xu Y, Li X, Yuan L, Tan H, Li D et al (2018) Fabrication of antibacterial collagen-based composite wound dressing. *ACS Sustainable Chemistry & Engineering* 6:9153–9166. <https://doi.org/10.1021/acssuschemeng.8b01482>
- Goel A, Meher MK, Gupta P, Gulati K, Pruthi V, Poluri KM (2019) Microwave assisted κ -carrageenan capped silver nanocomposites for eradication of bacterial biofilms. *Carbohydr Polym* 206:854–862. <https://doi.org/10.1016/j.carbpol.2018.11.033>
- Gou L, Xiang M, Ni X (2020) Development of wound therapy in nursing care of infants by using injectable gelatin-cellulose composite hydrogel incorporated with silver nanoparticles. *Mater Lett* 277:128340. <https://doi.org/10.1016/j.matlet.2020.128340>
- Graça MFP, Miguel SP, Cabral CSD, Correia IJ (2020) Hyaluronic acid—Based wound dressings: a review. *Carbohydr Polym* 241:116364. <https://doi.org/10.1016/j.carbpol.2020.116364>
- Guo T, Yang X, Deng J, Zhu L, Wang B, Hao S (2018) Keratin nanoparticles-coating electrospun PVA nanofibers for potential neural tissue applications. *J Mater Sci Mater Med* 30:9. <https://doi.org/10.1007/s10856-018-6207-5>
- Guo T, Yang X, Deng J, Zhu L, Wang B, Hao S (2019) Keratin nanoparticles-coating electrospun PVA nanofibers for potential neural tissue applications. *J Mater Sci Mater Med* 30:9
- Han Y, Lv S (2019) Synthesis of chemically crosslinked pululan/gelatin-based extracellular matrix-mimetic gels. *Int J Biol Macromol* 122:1262–1270
- He H, Cai R, Wang Y, Tao G, Guo P, Zuo H et al (2017) Preparation and characterization of silk sericin/PVA blend film with silver nanoparticles for potential antimicrobial application. *Int J Biol Macromol* 104:457–464. <https://doi.org/10.1016/j.ijbiomac.2017.06.009>
- Huang Y, Zhao X, Zhang Z, Liang Y, Yin Z, Chen B et al (2020) Degradable gelatin-based IPN cryogel hemostat for rapidly stopping deep noncompressible hemorrhage and simultaneously improving wound healing. *Chem Mater* 32:6595–6610
- Hussein J, El-Naggar ME, Latif YA, Medhat D, El Bana M, Refaat E et al (2018) Solvent-free and one-pot synthesis of silver and zinc oxide nanoparticles: activity toward cell membrane component and insulin signaling pathway in experimental diabetes. *Colloids Surf B Biointerfaces* 170:76–84. <https://doi.org/10.1016/j.colsurfb.2018.05.058>
- Jiang Y, Wang D, Li F, Li D, Huang Q (2020) Cinnamon essential oil Pickering emulsion stabilized by zein-pectin composite nanoparticles: characterization, antimicrobial effect and advantages in storage application. *Int J Biol Macromol* 148:1280–1289
- Jose LM, Kuriakose S (2019) Photochemical studies and photoinduced antibacterial properties of silver nanoparticle-encapsulated biomacromolecule bovine serum albumin functionalised with photoresponsive chromophoric system 2-[(E)-(3-hydroxynaphthalen-2-yl) diazenyl] benzoic acid. *Macromol Res* 27:73–82
- Kaczmarek B, Nadolna K, Owczarek A (2020) Chapter 6 - The physical and chemical properties of hydrogels based on natural polymers. In: Chen Y (ed) *Hydrogels based on natural polymers*. Elsevier, pp 151–172
- Kurakula M, Rao GSNK, Kiran V, Hasnain MS, Nayak AK (2020) Alginate-based hydrogel systems for drug releasing in wound healing. In: *Alginates in drug delivery*. Elsevier, pp 323–358
- Li K, Guan G, Zhu J, Wu H, Sun Q (2019) Antibacterial activity and mechanism of a laccase-catalyzed chitosan-gallic acid derivative against *Escherichia coli* and *Staphylococcus aureus*. *Food Control* 96:234–243. <https://doi.org/10.1016/j.foodcont.2018.09.021>
- Liang L, Hou T, Ouyang Q, Xie L, Zhong S, Li P et al (2020) Antimicrobial sodium alginate dressing immobilized with polydopamine-silver composite nanospheres. *Compos B Eng* 188:107877. <https://doi.org/10.1016/j.compositesb.2020.107877>
- Lim Y-S, Ok Y-J, Hwang S-Y, Kwak J-Y, Yoon S (2019) Marine collagen as a promising biomaterial for biomedical applications. *Mar Drugs* 17:467
- Liu G, Yu R, Jiang J, Ding Z, Ma J, Liang R (2021) Robust immobilization of anionic silver nanoparticles on cellulose filter paper toward a low-cost point-of-use water disinfection system with improved anti-biofouling properties. *RSC Adv* 11:4873–4882
- Lomeli-Marroquín D, Medina Cruz D, Nieto-Argüello A, Vernet Crúa A, Chen J, Torres-Castro A et al (2019) Starch-mediated synthesis of mono- and bimetallic silver/gold

- nanoparticles as antimicrobial and anticancer agents. *Int J Nanomed* 14:2171–2190. <https://doi.org/10.2147/IJN.S192757>
- Luo Y, Wang T (2016) Chapter 9 - Pharmaceutical and osmetic applications of protein by-products. In Singh Dhillon G (ed) *Protein byproducts*. Academic Press, pp 147–160
- Ma Z, Liu J, Shen G, Zheng X, Pei Y, Tang K (2021) In-situ synthesis and immobilization of silver nanoparticles on microfibrillated cellulose for long-term antibacterial applications. *Cellulose* 28:1–17
- Mercado-Mercado G, Laura A, Alvarez-Parrilla E (2020) Effect of pectin on the interactions among phenolic compounds determined by antioxidant capacity. *J Mol Struct* 1199:126967
- Moghadam A, Ijaz M, Asim MH, Mahmood A, Jelkmann M, Matuszczak B et al (2018) Non-ionic thiolated cyclodextrins - the next generation. *Int J Nanomed* 13:4003–4013. <https://doi.org/10.2147/IJN.S153226>
- Mohamadi Zahedi S, Mansourpanah Y (2018) Construction of chitosan-carboxymethyl β -cyclodextrin silver nanocomposite hydrogel to improve antibacterial activity. *Plast, Rubber Compos* 47:273–281. <https://doi.org/10.1080/14658011.2018.1475166>
- Mohammed H, Kumar A, Bekyarova E, Al-Hadeethi Y, Zhang X, Chen M, et al (2020) Antimicrobial mechanisms and effectiveness of graphene and graphene-functionalized biomaterials. A scope review. *Front Bioeng Biotechnol* 8:465
- Naderi P, Zarei M, Karbasi S, Salehi H (2020) Evaluation of the effects of keratin on physical, mechanical and biological properties of poly (3-hydroxybutyrate) electrospun scaffold: potential application in bone tissue engineering. *Eur Polym J* 124:109502. <https://doi.org/10.1016/j.eurpolymj.2020.109502>
- Nanda SS, Yi DK, Kim K (2016) Study of antibacterial mechanism of graphene oxide using Raman spectroscopy. *Sci Rep* 6:28443. <https://doi.org/10.1038/srep28443>
- Nayak AK, Das B (2018). 1 - Introduction to polymeric gels. In K. Pal, & I. Banerjee (Eds.), *Polymeric Gels* (pp. 3–27): Woodhead Publishing.
- Nguyen TP, Nguyen QV, Nguyen V-H, Le T-H, Huynh VQN, Vo D-VN et al (2019) Silk fibroin-based biomaterials for biomedical applications: a review. *Polymers* 11:1933. <https://doi.org/10.3390/polym11121933>
- Paajanen A, Ceccherini S, Maloney T, Ketoja JA (2019) Chirality and bound water in the hierarchical cellulose structure. *Cellulose* 26:5877–5892. <https://doi.org/10.1007/s10570-019-02525-7>
- Palazzo C, Trapani G, Ponchel G, Trapani A, Vauthier C (2017) Mucoadhesive properties of low molecular weight chitosan-or glycol chitosan-and corresponding thiomercated poly (isobutyrylcyanoacrylate) core-shell nanoparticles. *Eur J Pharm Biopharm* 117:315–323
- Pallavicini P, Arciola CR, Bertoglio F, Curtosi S, Dacarro G, D'Agostino A et al (2017) Silver nanoparticles synthesized and coated with pectin: an ideal compromise for antibacterial and anti-biofilm action combined with wound-healing properties. *J Colloid Interface Sci* 498:271–281. <https://doi.org/10.1016/j.jcis.2017.03.062>
- Pandey S, Do JY, Kim J, Kang M (2020) Fast and highly efficient catalytic degradation of dyes using κ -carrageenan stabilized silver nanoparticles nanocatalyst. *Carbohydr Polym* 230:115597. <https://doi.org/10.1016/j.carbpol.2019.115597>
- Patil S, Dhyani V, Kaur T, Singh N (2020) Spatiotemporal control over cell proliferation and differentiation for tissue engineering and regenerative medicine applications using silk fibroin scaffolds. *ACS Appl Bio Mater* 6:3476–3493
- Pietrucha K (2005) Changes in denaturation and rheological properties of collagen-hyaluronic acid scaffolds as a result of temperature dependencies. *Int J Biol Macromol* 36:299–304
- Pooresmaeil M, Namazi H (2019) Preparation and characterization of polyvinyl alcohol/ β -cyclodextrin/GO-Ag nanocomposite with improved antibacterial and strength properties. *Polym Adv Technol* 30:447–456
- Pouget C, Dunyach-Remy C, Pantel A, Schuldiner S, Sotto A, Lavigne J-P (2020) Biofilms in diabetic foot ulcers: significance and clinical relevance. *Microorganisms* 8:1580
- Ran X, Du Y, Wang Z, Wang H, Pu F, Ren J et al (2017) Hyaluronic acid-templated Ag nanoparticles/graphene oxide composites for synergistic therapy of bacteria infection. *ACS Appl Mater Interfaces* 9:19717–19724
- Roig-Sanchez S, Jungstedt E, Anton-Sales I, Malaspina DC, Faraudo J, Berglund LA et al (2019) Nanocellulose films with multiple functional nanoparticles in confined spatial distribution. [10.1039/C8NH00310F]. *Nanoscale Horizons* 4:634–641. <https://doi.org/10.1039/C8NH00310F>
- Sandri G, Miele D, Faccendini A, Bonferoni MC, Rossi S, Grisoli P et al (2019) Chitosan/glycosaminoglycan scaffolds: the role of silver nanoparticles to control microbial infections in wound healing. *Polymers* 11:1207
- Sapru S, Das S, Mandal M, Ghosh AK, Kundu SC (2018) Prospects of nonmulberry silk protein sericin-based nanofibrous matrices for wound healing-in vitro and in vivo investigations. *Acta Biomater* 78:137–150
- Shaheen TI, El-Naggar ME, Hussein JS, El-Bana M, Emara E, El-Khayat Z et al (2016) Antidiabetic assessment; in vivo study of gold and core-shell silver-gold nanoparticles on streptozotocin-induced diabetic rats. *Biomed Pharmacother* 83:865–875. <https://doi.org/10.1016/j.biopha.2016.07.052>
- Shahzad A, Khan A, Afzal Z, Umer MF, Khan J, Khan GM (2019) Formulation development and characterization of cefazolin nanoparticles-loaded cross-linked films of sodium alginate and pectin as wound dressings. *Int J Biol Macromol* 124:255–269
- Shao J, Wang B, Li J, Jansen JA, Walboomers XF, Yang F (2019) Antibacterial effect and wound healing ability of silver nanoparticles incorporation into chitosan-based nanofibrous membranes. *Mater Sci Eng, C* 98:1053–1063. <https://doi.org/10.1016/j.msec.2019.01.073>
- Sierra-Sánchez Á, Fernández-González A, Lizana-Moreno A, Espinosa-Ibáñez O, Martínez-Lopez A, Guerrero-Calvo J, et al (2020) Hyaluronic acid biomaterial for human tissue-engineered skin substitutes: preclinical comparative in vivo study of wound healing. *J Eur Acad Dermatol Venereol* 34:2414–2427
- Singh P, Pandit S, Jers C, Joshi AS, Garnæs J, Mijakovic I (2021) Silver nanoparticles produced from *Cedecea* sp. exhibit antibiofilm activity and remarkable stability. *Sci*

- Rep 11:12619. <https://doi.org/10.1038/s41598-021-92006-4>
- Steffens L, de Barros Dias MCH, Arantes PR, Gnoatto J, Raabe M, Moura DJ (2020). Modified polysaccharides in wound healing. In *Tailor-Made Polysaccharides in Biomedical Applications* (pp. 225–258): Elsevier.
- Tan BY, Nguyen LTH, Kim HS, Kim JH, Ng KW (2017) Cultivation of human dermal fibroblasts and epidermal keratinocytes on keratin-coated silica bead substrates. *J Biomed Mater Res, Part A* 105:2789–2798
- Tao G, Cai R, Wang Y, Liu L, Zuo H, Zhao P et al (2019) Bioinspired design of AgNPs embedded silk sericin-based sponges for efficiently combating bacteria and promoting wound healing. *Mater Des* 180:107940. <https://doi.org/10.1016/j.matdes.2019.107940>
- Taran M, Rad M, Alavi M (2016) Characterization of Ag nanoparticles biosynthesized by *Bacillus* sp. HAI4 in different conditions and their antibacterial effects. *J Appl Pharm Sci* 6:094–099
- Tian B, Hua S, Liu J (2020) Cyclodextrin-based delivery systems for chemotherapeutic anticancer drugs: a review. *Carbohydr Polym* 232:115805. <https://doi.org/10.1016/j.carbpol.2019.115805>
- Tottoli EM, Dorati R, Genta I, Chiesa E, Pisani S, Conti B (2020) Skin wound healing process and new emerging technologies for skin wound care and regeneration. *Pharmaceutics* 12:735
- Usman A, Hussain Z, Riaz A, Khan AN (2016) Enhanced mechanical, thermal and antimicrobial properties of poly(vinyl alcohol)/graphene oxide/starch/silver nanocomposites films. *Carbohydr Polym* 153:592–599. <https://doi.org/10.1016/j.carbpol.2016.08.026>
- Valentine ME, Kirby BD, Withers TR, Johnson SL, Long TE, Hao Y et al (2020) Generation of a highly attenuated strain of *Pseudomonas aeruginosa* for commercial production of alginate. *Microb Biotechnol* 13:162–175
- Vanitha G, Rajavel K, Boopathy G, Veeravazhuthi V, Nee-lamegam P (2017) Physicochemical charge stabilization of silver nanoparticles and its antibacterial applications. *Chem Phys Lett* 669:71–79. <https://doi.org/10.1016/j.cplett.2016.11.037>
- Wan Y, Yang S, Wang J, Gan D, Gama M, Yang Z et al (2020) Scalable synthesis of robust and stretchable composite wound dressings by dispersing silver nanowires in continuous bacterial cellulose. *Compos B Eng* 199:108259. <https://doi.org/10.1016/j.compositesb.2020.108259>
- Wang J, Xu J (2020) Effects of topical insulin on wound healing: a review of animal and human evidences. *Diabetes, Metabolic Syndrome and Obesity: Targets Therapy* 13:719–727. <https://doi.org/10.2147/DMSO.S237294>
- Wang Y, Li P, Xiang P, Lu J, Yuan J, Shen J (2016) Electrospun polyurethane/keratin/AgNP biocomposite mats for bio-compatible and antibacterial wound dressings. *J Mater Chem B* 4:635–648
- Wei Y, Zhang J, Zhou Y, Bei W, Li Y, Yuan Q et al (2017) Characterization of glabridin/hydroxypropyl- β -cyclodextrin inclusion complex with robust solubility and enhanced bioactivity. *Carbohydr Polym* 159:152–160
- Xie X, Mao C, Liu X, Zhang Y, Cui Z, Yang X et al (2017) Synergistic bacteria killing through photodynamic and physical actions of graphene oxide/Ag/collagen coating. *ACS Appl Mater Interfaces* 9:26417–26428
- Yan J, Abdelgawad AM, El-Naggar ME, Rojas OJ (2016) Antibacterial activity of silver nanoparticles synthesized In-situ by solution spraying onto cellulose. *Carbohydr Polym* 147:500–508. <https://doi.org/10.1016/j.carbpol.2016.03.029>
- Yang X-R, Zhao Y-Q, Qiu Y-T, Chi C-F, Wang B (2019) Preparation and characterization of gelatin and antioxidant peptides from gelatin hydrolysate of skipjack tuna (*Katsuwonus pelamis*) bone stimulated by in vitro gastrointestinal digestion. *Mar Drugs* 17:78
- Ye D, Zhong Z, Xu H, Chang C, Yang Z, Wang Y et al (2016) Construction of cellulose/nanosilver sponge materials and their antibacterial activities for infected wounds healing. *Cellulose* 23:749–763. <https://doi.org/10.1007/s10570-015-0851-4>
- You C, Li Q, Wang X, Wu P, Ho JK, Jin R et al (2017) Silver nanoparticle loaded collagen/chitosan scaffolds promote wound healing via regulating fibroblast migration and macrophage activation. *Sci Rep* 7:10489. <https://doi.org/10.1038/s41598-017-10481-0>
- Zhang H, Peng M, Cheng T, Zhao P, Qiu L, Zhou J et al (2018) Silver nanoparticles-doped collagen–alginate antimicrobial biocomposite as potential wound dressing. *J Mater Sci* 53:14944–14952
- Zhao X, Li Q, Ma X, Quan F, Wang J, Xia Y (2015) The preparation of alginate–AgNPs composite fiber with green approach and its antibacterial activity. *J Ind Eng Chem* 24:188–195. <https://doi.org/10.1016/j.jiec.2014.09.028>
- Zhou W, Jia Z, Xiong P, Yan J, Li Y, Li M et al (2017) Bioinspired and biomimetic AgNPs/gentamicin-embedded silk fibroin coatings for robust antibacterial and osteogenic applications. *ACS Appl Mater Interfaces* 9:25830–25846

Publisher's Note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.