




Transition metal tungstates AWO_4 ($A^{2+} = Fe, Co, Ni, \text{ and } Cu$) thin films and their photoelectrochemical behavior as photoanode for photocatalytic applications

Maria Joseíta dos Santos Costa¹ · Aline Estefany Brandão Lima¹ · Ester Pamponet Ribeiro² · Gilson dos Santos Costa¹ · Elson Longo³ · Geraldo Eduardo da Luz Jr^{1,2} · Laecio Santos Cavalcante²  · Reginaldo da Silva Santos^{1,2}

Received: 15 August 2022 / Accepted: 18 December 2022 / Published online: 18 January 2023
© The Author(s), under exclusive licence to Springer Nature B.V. 2023

Abstract

This paper discusses about a facile transition metal tungstate thin films preparation method and their remarkable photoelectrochemical properties. The films of AWO_4 ($A^{2+} = Fe, Co, Ni, Cu$) were deposited onto conductive fluorine-doped tin oxide (FTO) glass substrate. The results of X-ray diffraction analysis indicated the presence of crystalline films. Field emission scanning electron microscopy images revealed nanostructured materials. X-ray photoelectron studies were employed to analyze elemental and chemical composition. Optical behavior indicated indirect transitions for all AWO_4 films. Photoelectrochemical studies displayed that AWO_4 films were successfully used as photoanodes in a photoelectrochemical cell under polychromatic irradiation. From electrochemical measurement, it was possible to estimate the flat band potential and so prevising suitable application of photoelectrodes. This work reports for the first time a comparative and comprehensive photoelectrochemical study with AWO_4 films prepared in a simple way. The results indicate that the films can be used as photoanodes in water splitting reactions and other photoelectrocatalytic applications.


✉ Laecio Santos Cavalcante
laeciosc@gmail.com

¹ Programa de Pós-Graduação em Química-PPGQ, Universidade Federal do Piauí-UFPI, Teresina, PI 64049-550, Brazil

² PPGQ-GreeTec-CETEM, Universidade Estadual do Piauí-UESPI, Rua: João Cabral, N, 2231, P.O. Box 381, Teresina, PI 64002-150, Brazil

³ CDMF, Universidade Federal de São Carlos-UFSCar, P.O. Box 676, São Carlos, SP 13565-905, Brazil

Graphical Abstract



Keywords Wolframite thin films · Photoelectrochemical · Visible irradiation · Bands diagram

1 Introduction

In the last years, the growth of the world population and expansion of industrial centers have raised serious concerns caused by pollution and demands for clean water (H_2O) and energy [1]. Versatile, low-cost, and environment-friendly treatment technologies have been investigated to mitigate these issues. Besides that, recent developments in research and application of heterogeneous photocatalysis for light (ultraviolet, visible, or solar irradiation) conversion have been used as the most advanced and greenest method [2]. Among various semiconductor applications, photoelectrochemical (PEC) cell for H_2O splitting based on semiconductor oxides materials is a promising and environmentally friendly alternative approach to convert solar energy into a fuel source [3]. In addition, persistent organic pollutants or carbon dioxide (CO_2) can be converted into less inert compounds by photo(electro)catalytic processes [4].

In the photoelectrocatalysis process, the semiconductor material must be supported on the conductive substrate as a film, usually called photoelectrode. The photocatalytic process starts when the material absorbs light with energy equal to or superior to the semiconductor bandgap energy (E_{bg}) value [5]. This process results in photogenerated electrons ($e^-_{(\text{CB})}$) in the conduction band (CB) and holes ($h^+_{(\text{VB})}$) in the valence band (VB). These photogenerated charges can reach the semiconductor surface and then react with chemical species present in an electrolyte solution. It is typically considered that an electron can be transferred to an acceptor molecule if its redox potential lies below the CB of the photocatalyst, while a hole can be transferred to a donor molecule if its redox potential lies above the VB of the photocatalyst [6, 7].

Several types of metal oxide semiconductors such as titanium dioxide (TiO_2) [8, 9], tungsten trioxide (WO_3) [10], hematite ($\alpha\text{-Fe}_2\text{O}_3$) [11], and zinc oxide (ZnO) [12], have been investigated in many photocatalytic applications. However, although these materials exhibit substantial photocatalytic activity, TiO_2 and ZnO have limited application due to their high E_{bg} values. On the other hand,

WO_3 , $\alpha\text{-Fe}_2\text{O}_3$ and Ag_3PO_4 oxides are colored, but have some drawbacks, which include reduced chemical stability at alkaline condition, acid medium and weak photostability, respectively [10–14]. In general, colored semiconductor oxides undergo photocorrosion, while white oxides like TiO_2 and ZnO are photoactive only under ultraviolet radiation. In addition, the main disadvantages presented by oxides in catalytic applications include a short carrier path length and, high charge carrier recombination [15–17]. Thus, ideally, it would be important to obtain oxides materials that present excellent chemical stability and photoactivity under visible irradiation. This way, it is important to research semiconductors with small E_{bg} , facile surface reaction kinetic, abundant and stable chemically semiconductors for efficient PEC H_2O splitting. Recently, our research group has investigated the properties of copper tungstate (CuWO_4) films as photoelectrode for photocatalysis applications [18, 19]. CuWO_4 is a transition metal tungstate, displays great chemical stability, and can harvest sunlight owing to its low bandgap energy.

Transition metal tungstates like AWO_4 (with $A^{2+} = \text{Fe}$, Co , Ni , and Cu) are ternary oxide semiconductors that have attracted considerable attention due to their interesting photoelectrochemical, electrocatalytic, luminescent, and photocatalytic properties [20, 21]. Wolframite-type tungstates are favored by metal cations with radii less than 0.077 nm, while metal ions greater than 0.099 nm favor scheelite-type tungstates [22]. In tungstates with the wolframite-type monoclinic structure the transition metal (A) and W atoms are both bonded with six oxygen atoms to form $[\text{AO}_6]/[\text{WO}_6]$ clusters. In scheelite structures, the transition metal is combined with eight oxygen and the W atoms are bonded with four oxygen, which forms the $[\text{AO}_8]/[\text{WO}_4]$ clusters [23–25].

The iron tungstate (FeWO_4) is a semiconductor with a bandgap of approximately varying of 1.8 to 2.0 eV, absorbing a wide range of light responses and playing an important role in the magnetic and photocatalytic potential application [26–28]. Cobalt tungstate (CoWO_4) has a well-defined magnetic structure and bandgap of about 2.8 eV, exhibiting excellent electrical and magnetic properties [29]. Nickel tungstate (NiWO_4) demonstrates an indirect bandgap of 2.0 eV [30] and the remarkable quantum size effect [31], which make it a potential photoanode candidate in the H_2O splitting; and, others applications including photocatalysis [32], antimicrobial [33] and electrocatalysis [34]. Copper tungstate (CuWO_4) has an indirect bandgap energy (E_{bg}) in the range of 2.2 to 2.45 eV [35–37], owing to their sufficient chemical stability, efficient sunlight utilization, and nontoxicity has been applied highly photoelectrocatalytic activity and photoelectrochemical H_2O splitting [38–40]. In addition, others applications have aroused technological and scientific interest such as scintillation detectors [41],

humidity and gas sensors [42, 43], supercapacitors [44], photoanodes [35], supercapacitor [45, 46], photoelectrolysis electrodes for lithium-ion batteries [47–49], electrochromic devices [44, 50] and photoelectrodes for hydrogen treatment [51].

Recently, some synthesis methods were employed for obtention of metal tungstate-based photoanode films as hydrothermal method [40], template-assisted synthesis method [52], co-precipitation [20], spray pyrolysis [53] and electrochemical deposition [54]. The polymeric precursor's method (PPM) has been very effective about conventional methods principally for wastewater treatment [55]. The main advantages of PPM have been seen allowing the control of the composition, the grain size, and the homogeneity of powders [56]. There is a variety of studies using AWO_4 as dispersed photocatalyst particles in the reaction medium for organic pollutants degradation. However, there are still few reports of preparing films from these materials. In addition, most film preparation methods are time-consuming and require an expensive structure. Thus, simple methodology, low cost, and high-performance AWO_4 films still need to be investigated. To the best of our knowledge, the PPM has not been used to obtain transition metal tungstate AWO_4 ($A^{2+} = \text{Fe}$, Co , Ni , and Cu) thin films. PPM has been studied in preparation of AWO_4 oxides semiconductores at powder form. In addition, this is the first time that a detailed photoelectrochemical study of these materials has been presented.

Therefore, in this paper, AWO_4 ($A^{2+} = \text{Fe}$, Co , Ni , and Cu) thin films were synthesized by the PPM and deposited on the transparent conductive substrate (FTO-glass) using a simple drop-casting method. After thermal treatment, the film's photoelectrochemical behaviors were investigated. These studies are important and can provide information about the potential use of films in photocatalytic applications, such as H_2O splitting. Besides, all films were structurally characterized using X-ray diffraction (XRD) patterns; the composition was analyzed by X-ray photoelectron spectroscopy (XPS); the morphological features were examined by field emission scanning electron microscope (FE-SEM), and the optical bandgap energies were estimated using UV–Vis spectroscopy.

2 Experimental section

2.1 Materials and procedure

The citric acid ($\text{C}_6\text{H}_8\text{O}_7$; 99% purity), tungstic acid (H_2WO_4 ; 99% purity), ammonium iron (II) sulfate hexahydrate $[(\text{NH}_4)_2\text{Fe}(\text{SO}_4)_2]$, 99.9% purity], cobalt (II) nitrate hexahydrate $[\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}]$, 99.99% purity], nickel (II) nitrate hexahydrate $[\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}]$, 99.99% purity] and copper nitrate trihydrate $[\text{Cu}(\text{NO}_3)_2 \cdot 3\text{H}_2\text{O}]$; 99% purity] were

purchased from Sigma-Aldrich®. Ammonium hydroxide (NH_4OH , 35% purity) and ethylene glycol ($\text{C}_2\text{H}_6\text{O}_2$, 99.5% purity) were purchased from Dynamic®.

AWO_4 ($A^{2+} = \text{Fe}, \text{Co}, \text{Ni}, \text{Cu}$) films were obtained from the resin by the PPM [57]. This is a modified sol–gel method that is based on the complexation of metal alkoxides, and the esterification/polymerization reaction [58]. Recently, this synthesis method has been successfully used to obtain crystalline ceramic powders when calcined at temperatures between 500 and 700 °C [55, 59, 60]. For first time here was used to obtain metal tungstate thin films.

2.2 Synthesis of AWO_4 thin film by polymeric precursor method

A tungsten metal citrate (Cit-W, pH = 7) was initially prepared using deionized water (DI- H_2O) as a solvent, 0.135 mol citric acid ($\text{C}_6\text{H}_8\text{O}_7$) as a complexing agent and 0.045 mol tungstic acid (H_2WO_4) as a network modifier forming a transparent solution with concentration of $0.4256 \mu\text{mol L}^{-1}$. After homogenization, bivalent cation precursors ($A = \text{Fe}^{2+}, \text{Co}^{2+}, \text{Ni}^{2+}, \text{and Cu}^{2+}$) were added to citrate, respectively. The 150 g citrate with each bivalent cations was heat-treated and stirred at 90 °C for 2 h and obtained a homogeneous brown, wine, green, and blue color solution for iron, cobalt, nickel, and copper, respectively. Ammonium hydroxide (NH_4OH) was used to adjust the pH ~ 7. This solution was polymerized with the addition of 2.467 g ethylene glycol ($\text{C}_2\text{H}_6\text{O}_2$, polyalcohol); after reaction at a temperature of approximately 90 °C is formed a polyester and H_2O . The citric acid/metal molar ratio was set at 3:1 and 60:40 for citric acid/ethylene glycol to promote citrate polymerization. The polymerized solution was heated until H_2O evaporated and a polymeric resin formed about 24 h and cooled to 16 °C. Before the film's preparation, the FTO glasses ($1.0 \times 2.5 \text{ cm}$) were cleaned by a sonication bath, successively, with H_2O and a neutral liquid soap, DI- H_2O , and finally with isopropyl alcohol for 15 min in each step. For films preparation, an adhesive tape was used to define the geometrical area of the films (1.0 cm^2); then, 80 μL resin was dripped onto the FTO-glass (Sigma-Aldrich® R-7 $\Omega \text{ cm}^{-2}$) by dropping casting method, heated at 100 °C for 1 h (10 °C /min) and heat-treated at 500 °C for 2 h (2 °C /min) in a muffle furnace. To form a second and third layer, the resin was dropped again, heated and one unique thermal treatment was realized.

2.3 Structural, morphological, optical, and composition characterization of AWO_4 films

AWO_4 ($A = \text{Fe}^{2+}, \text{Co}^{2+}, \text{Ni}^{2+}, \text{and Cu}^{2+}$) thin films were characterized by the X-ray diffraction (XRD)

pattern (Rigaku-DMax 2500PC, Japan with Cu $K\alpha$ radiation ($\lambda = 0.15406 \text{ nm}$) in the 2θ range from 10 to 80° with a scan speed of $0.02^\circ/\text{min}$. The diffraction patterns were compared to the data from the Inorganic Crystal Structure Database (ICSD). Optical analyzes were obtained by UV–Vis transmittance spectra using the UV–Vis spectrophotometer (Shimadzu, 2600). The E_{bg} values of the samples was obtained by the transmittance spectrum in the UV–Vis region, using FTO-glass as a reference, applying the Wood-Tauc plot method [61]. The surface and average grain size were characterized by field emission–scanning electron microscopy (FE-SEM, Supra 35-VP Carl Zeiss (Germany)). The images were obtained with a working voltage of 15 kV. The composition of the heterojunction film surface was analyzed by X-ray photoelectron spectroscopy (XPS; Scientia Omicron ESCA, Germany) using a monochromatic X-ray Al $K\alpha$ (1486.7 eV).

2.4 Photoelectrochemical analysis of AWO_4 photoelectrodes

The photoelectrochemical properties were investigated using an electrochemical cell fabricated with an optic glass window (100% transmittance for $\lambda > 360 \text{ nm}$). Working electrodes were the AWO_4 ($A^{2+} = \text{Fe}, \text{Co}, \text{Ni}, \text{and Cu}$) films, a Pt wire as the counter electrode, and Ag/AgCl (in 3.0 mol L^{-1} KCl saturated aqueous solution) was the reference electrode (in Luggin capillary). A three-electrode system configuration was used to measure; and so, was investigated in an aqueous solution of 0.1 mol L^{-1} Na_2SO_4 (pH 5.6) as the inert support electrolyte.

The measurements were performed using an Autolab Potentiostat/Galvanostat (PGSTAT302N Metrohm) and recorded by the NOVA 1.7 software, in the absence of light (dark) and under backside polychromatic irradiation. A metallic vapor discharge lamp (HQI-TS NDL) with a nominal potency of 150 W was used to irradiate the system. All our measurements were carried out with an irradiance of 100 mW cm^{-2} , with the AWO_4 films placed 10 cm from the irradiation source, similar to previous studies carried out by our group [9, 62]. The irradiance was measured with a Newport Power Meter, model 843-R. For more details on the behavior of the radiation source, see the supplementary material section (Fig. S1). Photoelectrochemical analyses consisted initially in the determination of layers which were using linear sweep voltammetry (LSV). Thus, the determination of the flat band potential (E_{fb}) was carried out with the data recorded in the anodic potential range of 0.1–1.3 V at a scan rate of 1.0 mV s^{-1} , using a chopped illumination at 0.1 Hz following the Gärtner–Butler model [63, 64].

The photocurrent-potential was measured using cyclic voltammetry (CV) with a scan rate of 20 mV/s in the dark and under polychromatic irradiation. Also, the chronoamperometric curves were registered under dark or light conditions with the electrodes polarized at +0.7 V (vs Ag/AgCl). For comparison, the potential registered using the Ag/AgCl reference electrode was adjusted to a reversible hydrogen electrode (RHE), according to the Eq. (1) [37, 54, 65]:

$$E(\text{vs. RHE}) = E(\text{vs. Ag/AgCl}) + 0.0591V \times \text{pH} + 0.199V. \quad (1)$$

Further, the potentials after adjustment with respect to the RHE (in volts) were converted to energy levels (eV) relative to vacuum level using Eq. (2) [66]:

$$E_{(\text{eV})} = [-4.5\text{eV} - eE_{(\text{RHE})}] \quad (2)$$

From the photoresponse, it was possible to calculate the recombination lifetime from the time constant (τ) obtained from Eq. (3), which describes the kinetics of the transient currents as follows below:

$$R = \exp(-t/\tau) \quad (3)$$

where the ratio R is $R = \frac{J_t - J_{st}}{J_{in} - J_{st}}$, J_t is the photocurrent at time t , J_{st} is the steady-state photocurrent, and J_{in} is the photocurrent at the initial time [67, 68].


3 Results and discussion

3.1 Structural, morphological and optical characterization of AWO₄ films

The crystal structures of the resulting samples were identified by the X-ray diffraction (XRD) patterns. The XRD patterns are recorded in the range of 10–80° as shown in Fig. 1a–d. Diffraction signals suppressed and marked with the symbol “•” correspond to the FTO transparent conductive glass substrate.

For FeWO₄, CoWO₄, and NiWO₄ films displayed in Fig. 1a–c, the XRD patterns show diffraction peaks which are characteristic and attributed to (010), (100), (110), (011), (111), ($\bar{1}\bar{1}$ 1), (020), (002), (021), and (200) planes, at 2θ equal to 15.6°, 19°, 24°, 25°, 30.6°, 31°, 36°, 37°, and 38°, respectively. These XRD patterns are characteristic of wolframite-type monoclinic phase structure with space group ($P2/c$) as determined by ICSD card No. 15952, 15851, and 15852 for FeWO₄, CoWO₄, and NiWO₄ crystal, respectively [69, 70]. On the other hand, the XRD pattern for the CuWO₄ sample (Fig. 1d) shows typical diffraction peaks for triclinic structure (ICSD No. 16009) with space group ($P\bar{1}$) [71]. The XRD diffraction were registered at 2θ of 15.29°, 18.19°, 19.02°, 22.94°, 23.56°, 24.13°, 25.96°, 26.97°, 28.70°, 30.14°, 30.85°,

Fig. 1 XRD patterns of (a) FeWO₄, (b) CoWO₄, (c) NiWO₄, and (d) CuWO₄ thin films synthesized by the PPM and heated at 500 °C for 2 h. The “•” indicates the FTO-glass substrate. The vertical bars represent planes and intensity of the ICSD card No. 15952, 15851, 15852, and 16009 for the pure monoclinic FeWO₄, CoWO₄, NiWO₄ phase, and pure triclinic CuWO₄ phase, respectively






Fig. 2 FE-SEM images of the surface of the (a) FeWO_4 , (b) CoWO_4 , (c) NiWO_4 , (d) and CuWO_4 films synthesized by PPM and heated at 500°C for 2 h

31.65° , 32.11° , 34.34° , 35.66° , 36.44° and 36.86° , which correspond to the planes (010), (001), (100), (110), $(0\bar{1}1)$, (011), $(\bar{1}10)$, (101), $(\bar{1}\bar{1}1)$, (111), (020), $(\bar{1}11)$, $(1\bar{1}1)$, (120), $(\bar{0}21)$, (021), and (002), respectively. The diffraction peaks without other impurities or deleterious phases, which suggests that films can be prepared successfully by means of PPM.

FE-SEM images for the morphology, particles size, and surface of AWO_4 ($A^{2+} = \text{Fe, Co, Ni, and Cu}$) films are shown in Fig. 2a–d, respectively. In Fig. 2a–d, the FE-SEM images revealed the morphology and particles size of the FeWO_4 , CoWO_4 , NiWO_4 and CuWO_4 films. The deposition of the FeWO_4 , CoWO_4 , NiWO_4 , and CuWO_4 films on a conductive substrate (FTO-glass), followed by annealing at 500°C , led to an immobilized particle density of ca. $1.6 \pm 0.2 \text{ mg cm}^{-2}$, $1.2 \pm 0.2 \text{ mg cm}^{-2}$, $0.9 \pm 0.2 \text{ mg cm}^{-2}$ and $1.4 \pm 0.1 \text{ mg cm}^{-2}$, respectively. The FeWO_4 film presented in Fig. 2a indicates that has a well-sintered nanoplates-like structure with an average particles size of $51.3 \text{ nm} \pm 1.343$ (See histogram in Fig. S2(a)). Yu et al. reported that FeWO_4 synthesized

by hydrothermal method present morphology influenced by pH condition, which can change from hexagonal flakes to nano-rods [72]. Figure 2b shows the morphological surface for CoWO_4 film with irregular spherical nanoparticles and an average particles size of ca. $27.7 \text{ nm} \pm 0.9799$ (See histogram in Fig. S2(b)). Whereas, the NiWO_4 film exhibits an irregular surface morphology formed by polyhedron interconnected particles (Fig. 2c) and an average particles size of ca. $74.75 \text{ nm} \pm 0.8185$ (See histogram in Fig. S2(c)). Figure 2d shows that CuWO_4 film is formed by irregular nanoparticles with an average size of $24.77 \text{ nm} \pm 2.537$ (See histogram in Fig. S2(d)). Thus, the presence of several grains in the CuWO_4 film agglomerated is very similar to that speculated to triclinic structure crystals [37]. In this case, a porous structure with a non-uniform pore distribution is formed. This porous nanostructure can contribute to superior charge mobility and a large specific surface area [73]. In all cases, the average crystal size was calculated by equatorial diameter and estimated using the GNU Image Manipulation Program (GIMP 2.10.10 version for Windows 7–64 bits) [74].




Fig. 3 a UV-Vis transmittance curves of films and bandgap energy estimated by Wood-Tauc plot method for (b) FeWO₄, (c) CoWO₄, (d) NiWO₄ and (e) CuWO₄ film deposited on FTO substrate.

The optical properties of these films were examined with UV-Vis spectra registered in transmittance mode and estimated the bandgap energy (E_{bg}) by Wood-Tauc plot method as shown in Fig. 3. Figure 3a shows that the AWO₄ ($A^{2+} = \text{Fe, Co, Ni, and Cu}$) films had a maximum transmittance of ~72% in the visible region and interference fringes

can be registered in FeWO₄ and CoWO₄ thin films. Considering an indirect gap transition, the optical E_{bg} for AWO₄ ($A^{2+} = \text{Fe, Co, Ni, and Cu}$) films were calculated with the following Eq. (4) [61]:

$$(\alpha h\nu)^{0.5} = C(h\nu - E_{bg}). \quad (4)$$

In this Eq. (4), the $h\nu$ is the incident photon energy, C is a constant of proportionality of semiconductors, E_{bg} is the optical bandgap energy and α is the optical absorption coefficient of the film. According to the equation, $(\alpha h\nu)^{0.5}$ has a linear relation with the $h\nu$ [75]. The optical E_{bg} values of AWO_4 ($A = \text{Fe, Co, Ni, Cu}$) films were determined by extrapolation of the linear relation to $(\alpha h\nu)^{0.5} = 0$. As illustrated in Fig. 3 b–e, the E_{bg} of FeWO_4 , CoWO_4 , NiWO_4 and CuWO_4 films are estimated to be about 1.87, 2.40, 2.45, and 2.19 eV, respectively. These E_{bg} values are slightly close that on registered in other studies [30, 54, 76–80]. Slight deviations in the E_{bg} values can be attributed to the effects of film morphology and particle sizes. These results indicate that the materials are able to harvest sunlight. Also, UV–Vis measurements using an integrating sphere were made. In general, there are no significant differences for the curves registered in both modes (See Fig. S3 on the Supporting Information).

An X-ray photoelectron spectroscopy (XPS) analyses were utilized to investigate the elemental and chemical composition of samples, as shown in Figs. S4, and 4. A full survey spectrum shown in Fig. S4 indicate the presence of Fe 2p [81], Co 2p [82], Ni 2p [83], and Cu 2p states [51] signals due to presence these elements in FeWO_4 , CoWO_4 , NiWO_4 , and CuWO_4 films samples. All XPS spectra are attributed to the constituent element core levels or Auger lines. Also, in all survey analyses, it was possible to observe the presence of corresponding peaks O 1s and W 4f. The C 1s peak can be attributed to carbon adsorbed on the surface of the AWO_4 films, probably due to polymeric precursors method not completely eliminated during the thermal treatment. Table S1 displays the values of XPS primary peak for all A divalent ions transitions metal ($A^{2+} = \text{Fe, Co, Ni, and Cu}$), W 4f, and O 1s core-level binding energies.

Metal ions ($A^{2+} = \text{Fe, Co, Ni, and Cu}$) 2p state in XPS spectra of each AWO_4 film are presented in Fig. 4a–d. The deconvoluted Fe 2p XPS (Fig. 4a) consists of two peaks which corresponds the binding energy of Fe $2p_{3/2}$ (710.70 and 712.48 eV), which higher binding energy of 712.48 eV can be attributed to +3 oxidation state [84], and Fe $2p_{1/2}$ (724.88 eV) due to Fe^{2+} in the lattice sites of FeWO_4 film [85]. In addition, there are two shake-up satellite peaks at Fe $2p_{3/2}$ (715.71 and 719.81 eV) and one satellite peak at Fe $2p_{1/2}$ (732.07 eV), which are typical Fe^{2+} oxidation states [86]. By using a Gaussian fitting method, the high-resolution Co 2p spectra is deconvoluted into two spin–orbit doublets and two shake-up satellites peaks (802.08 and 785.28 eV) [87]. The XPS Co 2p core-level spectra of CoWO_4 film is presented in Fig. 4b. The deconvolution of Co 2p peak is divided in Co $2p_{3/2}$ (779.94 and 781.31 eV) and Co $2p_{1/2}$

(796.57 eV) understanding Co^{2+} oxidation state. In same way that Fe for peaks of Co 2p (higher binding energy of 781.31 eV) attributed to +3 oxidation state [88].

Similarly, an XPS Ni 2p spectrum of NiWO_4 film is seen in Fig. 4c. The binding energy of the Ni $2p_{3/2}$ (855.08 and 856.59 eV) and Ni $2p_{1/2}$ (872.66 and 874.28 eV) are resulted of spin–orbit doublets deconvolution which characteristic of Ni^{2+} and two shake-up satellite peaks (856.59 and 874.28 eV) and good agreement with the literature data [34]. Two deconvolution of Ni 2p (higher binding energy of 874.28 eV and 856.59 eV) can be attributed to +3 oxidation state [89]. The satellites peaks are typical shake-up satellites which were due to the multielectron transitions and the decrease of the kinetic energy of emitted photoelectrons [90, 91]. Also, Fig. 4d shows XPS core-level spectrum of Cu 2p, which displays two sets of Gaussian doublets (Cu $2p_{3/2}$ and Cu $2p_{1/2}$) located at 931.33/933.61 eV, and 951.42/953.54 eV and shake-up satellite peaks located at 940.52, 942.80 and 961.40 eV assigned to a typical feature for Cu^{2+} oxidation state [92]. On the other hand, Tang and co-workers have shown in previous works that signals which occur at lower binding energy values (951.42 and 931.33 eV) can be attributed to Cu^{1+} oxidation state [51]. The appearance of doublet peaks in bivalent cations can indicate presence of monovalent or trivalent cations (A^+ or A^{3+}) [91, 93]. Figure 4e displays the W 4f core-level spectra of AWO_4 ($A^{2+} = \text{Fe, Co, Ni, and Cu}$) films. The deconvolution of W 4f spectra into one pair of spin–orbit doublet peaks dominated by W $4f_{5/2}$ and W $4f_{7/2}$ states corresponding to the W^{6+} valence state in tungstate-based crystal structure [7, 94]. The binding energy values of W 4f show doublet of W $4f_{7/2}$ and W $4f_{5/2}$, besides W $5p_{3/2}$ at 33.64/34.28, 35.95/37.22 and 39.83 eV for FeWO_4 , 34.26/34.96, 36.45/36.65 and 40.36 eV for CoWO_4 , 34.14/34.72, 36.57/36.71 and 40.37 eV for NiWO_4 and 34.42/35.07, 36.73/37.91 and 40.19 eV for CuWO_4 [95]. The appearance of doublet peaks of W 4f and W5p in XPS spectra indicates the presence of W^{5+} in the film [96]. As the presence of W^{5+} (or A^+) in AWO_4 films can induce oxygen vacancies that are regarded as shallow donors [52], a higher concentration of W^{5+} will result in a larger electron density in metal tungstate-based films [51]. Figure 4f shows the XPS O 1s core-level spectra of AWO_4 films annealed at 500 °C for 2 h. The O1s spectra was decomposed into three peaks located at 529.89, 530.88 and 531.60 eV, and were assigned to the O–W–O bonds, lattice oxygen of Fe–O–Fe, metallic oxide of Fe–O bonds in FeWO_4 , respectively [2, 26]. Similarly, the XPS O 1s spectra of CoWO_4 was analyzed and then, was observed three peaks located at 529.32, 530.23 and 531.40 eV. For NiWO_4 , the O 1s core-level spectra deconvoluted into three peaks are located at 529.46, 530.27, and 531.57 eV. Similar to others films, the O 1s core-level spectra of CuWO_4 was also deconvoluted in three peaks located at 529.76, 530.56 and 531.65 eV corresponding to same




Fig. 4 High-resolution XPS spectra for (a) Fe 2p, (b) Co 2p, (c) Ni 2p, (d) Cu 2p, (e) W 4f, and (f) O 1s core-level spectra of FeWO₄, CoWO₄, NiWO₄, and CuWO₄ film, respectively




Fig. 5 LSV curves plots of (a) FeWO₄, (b) CoWO₄, (c) NiWO₄, and (d) CuWO₄ photoanodes in inert 0.1 mol L⁻¹ Na₂SO₄ solution (pH~5.6) irradiated with chopped polychromatic light (0.1 Hz), respectively

description as previously presented. The XPS spectra confirm the formation of possible defect states on the surface and suggest the presence of oxygen vacancies created during production and incorporated in the crystal analyzed [15]. Here, the XPS data suggest that oxygen vacancies cause lower oxidation states in metals, in order to maintain the electroneutrality of the material. Thus, these defects may be responsible for the *n*-type conductivity of semiconductors, as well as the non-stoichiometry at surface FeWO₄, CoWO₄,

NiWO₄, and CuWO₄ films [97]. Hence, the XPS spectra confirm the formation of good-quality tungstate-based films.

3.2 Photoelectrochemical behavior of AWO₄ films

Figures 5a–d show the photoelectrochemical behavior of AWO₄ (A²⁺=Fe, Co, Ni, and Cu) films with different deposited layers on FTO-glass was examined by linear sweep voltammetry (LSV) curves registered at 1mVs⁻¹ under chopped 0.10 Hz polychromatic irradiation. All AWO₄ films

displayed a more negative photo-potential after irradiation condition, which means, in the dark the open-circuit-potential (OCP) value is more positive than OCP registered under irradiation condition ($E_{\text{light-on}} < E_{\text{light-off}}$ vs. Ag/AgCl). This negative photo-potential is characteristic of *n*-type semiconductor oxides [98]. Thus, LSV curves were registered toward anodic direction and positive photocurrents were observed as applied bias until oxygen evolution reaction (OER) signals under dark condition. To investigate the influence of AWO₄ film layers on photocurrent response, samples were prepared with one, two, and three layers.

For FeWO₄ and CoWO₄ materials, films with two layers showed the best photoresponse values, which can be with associated adequate quantity and thickness of semiconductors, as shown in Fig. 5a,b. Moreover, the FeWO₄ and CoWO₄ films with three layers showed lower values of photocurrents, suggesting that these films present greater resistance in the flow of electrons. From Fig. 5c,d, it is possible to observe that this reduction in photocurrents values was not registered for NiWO₄, and CuWO₄ films. In NiWO₄ film with three layers, higher photocurrents were observed, while in CuWO₄ films this photoresponse value was maintained. For comparison effect, all other photoelectrochemical measures registered hereinafter were developed with two layers for FeWO₄, CoWO₄, NiWO₄, and CuWO₄ films.

From Fig. 5a, it is possible to observe that an enhancement in photocurrent density of FeWO₄ photoelectrode started from 0.95 V vs. Ag/AgCl (1.48 V vs. RHE). For CoWO₄, NiWO₄, and CuWO₄ the photocurrent values evolve in potentials closer to OCP, suggesting that in these films the electrons can reach the conductive substrate more easily. In all photoelectrodes, some positive spikes of current were observed immediately after the light was turned on, followed by an exponential drop in current values, which can be related to transient effects in the semiconductor material [65]. These spikes can be caused by the rapid injection of electrons into the CB (peak anode current), while the exponential drop is related to the electron/hole charges recombination process, even under polarization conditions. When the light is turned off, rapid recombination in VB happened and cathodic spikes can be registered, as displayed in Fig. 5b [99]. Current spike behavior also depends on the degree of crystallinity. Current spike diminishes by increasing the annealing temperature, but the conductivity of FTO substrate deteriorates at temperature above 500 °C. The NiWO₄ shows a beautiful LSV curve (Fig. 5c) due to a good crystallinity as shown in FE-SEM (Fig. 2c) and large particle size (Fig. S2c). Also, this transient cathodic peak can be associated to back electron transfer from the external circuit to the photoanode, which resulted in a surface recombination process [100]. According to Le Chatelier's principle, a system at equilibrium that is subjected to an alteration in concentration will readjust itself to counteract

the alteration and establish a new equilibrium caused by an excess of electrons. This would explain the transient current spikes in the AWO₄ photoanodes.

The photocurrent density measurements by LSV curves were utilized to estimate the flat band potential (E_{fb}) of these semiconductors, following the Butler–Gärtner model [63, 64], as displayed in Fig. 6(a–d). Gärtner–Butler analysis is an alternative method of determining the E_{fb} is based on the measurement of the square of the photocurrent density as a function of electrode potential. The E_{fb} is predicted to be at the intercept of the square of the photocurrent density with the potential axis [101]. This model assumes that the photocurrent (I_{ph}) is observed only when the electrode potential is more positive than the semiconductor flat band potential (i.e., when $E > E_{\text{fb}}$ and $I_{\text{ph}} > 0$). Thus, the Butler–Gärtner model can be represented by Eq. (5) below:

$$I_{\text{ph}} = \alpha W_0 q \varphi_0 \sqrt{E - E_{\text{fb}}} \quad (5)$$

where α is the absorption coefficient, W_0 is the depletion layer width, φ_0 is the radiation intensity, q is the electron charge, and E_{fb} is the flat band energy. This methodology already was employed to determine E_{fb} values for other photoelectrodes by our research group [11, 37, 102]. Therefore, E_{fb} values obtained by extrapolation of photocurrent initial potential were estimated at 0.23, 0.25, 0.28, and 0.38 V (vs. Ag/AgCl) for FeWO₄, CoWO₄, NiWO₄, and CuWO₄ electrodes, respectively. The E_{fb} value is strongly dependent on the medium conditions such as pH and electrolyte composition, as well as film thickness, crystal structure, and morphology of the semiconductor [103]. It is very important to determine the E_{fb} value of semiconductor materials before its application in any photoelectrochemical proposition [97, 104–106], since this electrode potential can be related to the Fermi energy level and the CB band edge position in *n*-type semiconductors [107]. The flat band potential and CB must be related to electron donor and acceptor states using Eq. (6):

$$E_{\text{CB}} = E_{\text{fb}} - \frac{kT}{e} \ln \frac{N_{\text{C}}}{N_{\text{D}}} \quad (6)$$

where k is the Boltzmann constant, T is the absolute temperature, e is the electron charge, N_{C} is the effective density of states in the CB, and N_{D} is the effective charge density [108]. Considering that the values of N_{D} and N_{C} are similar, the second term in Eq. (6) should be relatively small and then conduction band potential (E_{CB}) can be approximated to E_{fb} [109]. Thus, the relative positions of VB and CB edge potentials of the semiconductors were estimated from E_{bg} and E_{fb} values and using the Eqs. (5, 6), as shown in Fig. 6e. All electrodes show sufficient CB potential values to oxidize H₂O/O₂ (see dashed line in Fig. 6e. The photocatalytic




Fig. 6 Variation in the square of the photocurrent density with applied potential, for (a) FeWO_4 , (b) CoWO_4 , (c) NiWO_4 , and (d) CuWO_4 electrode in 0.1 mol L^{-1} Na_2SO_4 aqueous solution, under

polychromatic irradiation obeying Butler-Gärtner model and (e) the experimentally determined band diagrams

activity of each material is dependent on the relative positions of the conduction and valence bands. Previous studies reveal that it is important to determine the oxidation potential of species present in solution, relating this potential to the positions of CB and VB to predict the photocatalytic capacity of the semiconductor material [11, 102]. Similarly, E_{fb} values were estimated by Mott-Schottky plot through Electrochemical Impedance Spectroscopy. Fig S5(a) shows the Mott-Schottky curves and relative positions of the CB and VB obtained for all samples. As observed at Fig S5(b), there are no significant differences for the relative positions of the bands for curves obtained by Mott-Schottky or by Butler–Gärtner model.

Figures S6(a–d) display the cyclic voltammetry (CV) curves of AWO_4 ($A^{2+} = Fe, Co, Ni, \text{ and } Cu$) films registered at 20 mV s^{-1} in the dark and under polychromatic irradiation. In the dark, the electrodes presented an almost zero capacitive current. As mentioned before, the potential value associated with OER serves to limit the potential window toward anodic reactions. The OCP shifted toward more negative values under irradiation conditions, resulting in a photopotential of $-20, -60, -80, \text{ and } -50 \text{ mV}$ for $FeWO_4, CoWO_4, NiWO_4, \text{ and } CuWO_4$ photoelectrodes, respectively. These differences recorded in the OPC before and after illumination may be attributed to electron accumulation in the conduction band (CB), due to the electron–hole charge separation [110]. According to theory, after adequate illumination of a n -type semiconductor oxide, the electrons accumulated in the CB are collected by circuit until the Pt counter-electrode, while the photogenerated holes are moved to the electrode/electrolyte interface, thus generating the anodic photocurrent [111]. The photocurrent density of electrodes was respectively $15 \mu\text{A cm}^{-2}, 30 \mu\text{A cm}^{-2}, 20 \mu\text{A cm}^{-2}, \text{ and } 48 \mu\text{A cm}^{-2}$ at $1.0 \text{ V vs. Ag/AgCl (1.53 V vs. RHE)}$ for $FeWO_4, CoWO_4, NiWO_4, \text{ and } CuWO_4$ electrodes, as displayed in Figs. S6(a–d). The photoelectrochemical performance of photocatalyst electrodes fabricated in different synthesis methods reported in recent years were compared with this work, as shown in Table S2. Table S2 relating synthesis methods, photocurrent values, type of irradiation and electrolyte was presented [18, 19, 112–125]. Photocurrent values in photoelectrochemical measurements are dependent on several factors, including the material's bandgap energy value, material defects, and the ability of electron charges to reach the conductive substrate. Even with a higher E_{bg} value, $CuWO_4$ film presented higher photocurrent value, indicating that the photogenerated charges reach the conductive substrate more easily than the other AWO_4 investigated.

To investigate the photocurrent stability and e_{CB}^-/h_{VB}^+ recombination lifetime of electrodes in an aqueous medium, a photoelectrochemical study was carried out by measuring the photocurrent density over time at a constant potential of ca. $0.7 \text{ V vs. Ag/AgCl (1.23 V vs. RHE)}$. This study is

based on transient photocurrent behavior, in which the current response of a system is monitored while a light source is modulated periodically (usually light-on and light-off). Based on this measure, it is possible to study charge carrier dynamics and their traps in a semiconductor material as photoelectrode. The curves registered for AWO_4 films are displayed in Fig. 7. In the dark, all films displayed the current was almost null, while under irradiation, the photocurrent increased abruptly because of charge separation and electrons accumulating in the conduction band, a typical characteristic of n -type semiconductor oxides, as seen in Fig. 7a. In addition, the films demonstrated excellent photo-stability for 2100s, except the $FeWO_4$ film, whose, its photocurrent density has decreased continuously over time. The photocurrent density values followed the same results exposed previously by LSV and cyclic voltammetry measurements, see Fig. 5 and S6.

To obtain the electron–hole recombination lifetimes for the photoelectrodes, photocurrent-time curves, following the schematic representation in Fig. 7b, were analyzed according to Eq. (3). This equation shows that the kinetics of the transient photocurrent can be obtained from slope of the $\ln R$ vs. time (t) plot, as shown in Fig. 7c for $FeWO_4, CoWO_4, NiWO_4, \text{ and } CuWO_4$ photoelectrodes, biased at 0.70 V . The reciprocal $1/\tau$ is related to the electron–hole lifetime. In previous studies, we demonstrated that the mass transport mechanism (i.e. migration or diffusion) in the system does not alter the recombination exponential profile of transient photocurrent utilized to determine the lifetime [102]. As observed in Fig. 7a and schematically represented in Fig. 7b, an initial anodic photocurrent spike J_{in} indicates the injection of electrons in the CB owing to the electron/hole charge separation process. At the same time, electrons are transported to the conductor substrate to be collected by the external circuit; the holes are moved towards the semiconductor surface where they are reduced by the species in the electrolyte. Simultaneously, the photocurrent decreases exponentially with time until it reaches a steady-state photocurrent density (J_{st}) because of charge recombination.

The slope of the plot provides photocurrent transient (τ), which is related to the charge recombination lifetime in each electrode. The recombination lifetime results are displayed in Table S3. The τ values were calculated at about $83 \pm 7, 32 \pm 3, 25 \pm 4, \text{ and } 40 \pm 1 \text{ s}$ for the $FeWO_4, CoWO_4, NiWO_4, \text{ and } CuWO_4$ films, respectively. These τ values for the $CoWO_4$ and $NiWO_4$ films are smaller than the $FeWO_4$ and $CuWO_4$ films. However, these charge recombination time values are not in agreement with the photocurrent values shown in Fig. 5. Thus, Nyquist plots were used to assess the effective parallel resistance of charge transfer in the samples. Fig S7 shows the Nyquist plots. Even not displaying a well-defined arc as a semicircle, the maximum values observed for the Z' axis were used to verify the greater or lesser




Fig. 7 **a** Photocurrent density-time ($J-t$) curves of the annealed films measured under polychromatic illumination with chopped 300 s light on/off at 0.7 V vs. Ag/AgCl, **b** schematic representation of photocur-

rent transient curve and **c** normalized plot of current–time dependence for AWO_4 ($A^{2+} = \text{Fe, Co, Ni, and Cu}$)

tendency in charge transfers. The reduction of the effective parallel resistance indicates a better charge transfer for CuWO_4 , CoWO_4 , NiWO_4 , and FeWO_4 samples, respectively. This sequence agrees with the photocurrent values. Thus, probably, the electrons promoted to the conduction band do not return to VB. However, we have suppressed defects in the crystal lattice and we believed the holes are captured by

traps present in the grain boundaries of the material. Therefore, the photoelectrochemical properties were observed in different wolframite films with anodic photocurrent and capable of harvesting visible light allowing several photoelectrochemical applications.

4 Conclusion

In summary, FeWO₄, CoWO₄, NiWO₄, and CuWO₄ thin films onto FTO-glass were synthesized with success by the PPM method via drop-casting after heat treatment at 500 °C for 2 h. XRD patterns analyses confirmed the presence of wolframite-type monoclinic structure for FeWO₄, CoWO₄, and NiWO₄ films, while the CuWO₄ film exhibits a triclinic structure. The AWO₄ (A²⁺ = Fe, Co, Ni, and Cu) films showed an ability to absorb in the visible light region, which suggests being excellent harvesters of sunlight for energy conversion applications, such as H₂O oxidation. Morphological features showed by means of FE-SEM images revealed the presence of nanostructured oxides with irregular shapes and the diverse average size of particles. The PEC testing under illumination revealed anodic photocurrent and negative photopotential characteristics of *n*-type semiconductors oxides. In inert electrolyte, the CuWO₄ electrode showed the highest photocurrent density value of 48 μA cm⁻² at 1.0 V vs. Ag/AgCl (1.53 V vs. RHE). In addition, all electrodes demonstrated excellent chemical stability for photoelectrochemical oxygen evolution reaction with constant bias potential at 0.7 V vs. Ag/AgCl (1.23 V vs. RHE). From *E*_{bg} and *E*_{fb} values were possible to assemble a diagram of (CB and VB) positions, which leads to deducting the greatest applicability of electrodes in PEC, exploring these AWO₄ (A²⁺ = Fe, Co, Ni, and Cu) films as electrodes with a high potential to H₂O-splitting photocatalysts.

Supplementary Information The online version contains supplementary material available at <https://doi.org/10.1007/s10800-023-01851-w>.

Acknowledgements The Brazilian authors acknowledge the financial support from the Brazilian research financing institutions: CNPq (312318/2017-0 and 408036/2018-4), CCN2-PPGCM-UFPI-LIMAV, GERATEC-UESPI-CETEM, FAPESP-CDMF (13/07296-2) and CAPES.

Author contributions MJSC: conceptualization, methodology, formal analysis, investigation, data curation, writing—original draft, writing—review & editing, visualization. AEBL: methodology, investigation. EPR: resources, methodology, investigation. GSC: methodology, investigation, formal analysis. EL: conceptualization, writing—review & editing, GELJ: conceptualization, methodology, writing—review & editing. LSC: conceptualization, methodology, project administration, writing—review & editing and RSS: conceptualization, methodology, writing—review & editing, project administration, and supervision. All authors participated in writing the manuscript and discussing all the results.

Funding The authors do have not any funding to pay for open access.

Declarations

Conflict of interest The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

References

- Kumar P, Saroj DP (2014) Water-energy-pollution nexus for growing cities. *Urban Climate* 10:846–853. <https://doi.org/10.1016/j.uclim.2014.07.004>
- Bajorowicz B, Kobylański MP, Malankowska A, Mazierski P, Nadolna J, Pieczyńska A, Zaleska-Medynska A (2018) Application of metal oxide-based photocatalysis. In: Zalenska-Medynska A (ed) *Metal Oxide-Based Photocatalysis; Fundamentals and Prospects for Application; Metal Oxides*, vol series, 1st edn. Elsevier, Amsterdam, pp 211–340
- van de Krol R, Liang Y, Schoonman J (2008) Solar hydrogen production with nanostructured metal oxides. *J Mater Chem* 18:2311–2320. <https://doi.org/10.1039/B718969A>
- Kalanur S, Hwang J-Y, Seo H (2017) Facile fabrication of bittergourd-shaped copper (II) tungstate thin films for improved photocatalytic water splitting. *J Catal* 350:197–202. <https://doi.org/10.1016/j.jcat.2017.04.008>
- Garcia-Segura S, Brillas E (2017) Applied photoelectrocatalysis on the degradation of organic pollutants in wastewaters. *J Photochem Photobiol C* 31:1–35. <https://doi.org/10.1016/j.jphotochemrev.2017.01.005>
- Shinde SS, Bhosale CH, Rajpure KY (2014) Kinetic analysis of heterogeneous photocatalysis: role of hydroxyl radicals. *Catal Rev—Sci Eng* 55:79–133. <https://doi.org/10.1080/01614940.2012.734202>
- Djurišić AB, Leung YH, Ching Ng AM (2014) Strategies for improving the efficiency of semiconductor metal oxide photocatalysis. *Mater Horiz* 1:400–410. <https://doi.org/10.1039/C4MH00031E>
- Peiris S, de Silva HB, Ranasinghe KN, Bandara SV, Perera IR (2021) Recent development and future prospects of TiO₂ photocatalysis. *J Chin Chem Soc* 68:738–769. <https://doi.org/10.1002/jccs.202000465>
- Carvalho IC, Barbosa ML, Costa MJS, Longo E, Cavalcante LS, Viana VGF, Santos, & R.S. (2020) TiO₂-based dye-sensitized solar cells prepared with bixin and norbixin natural dyes: effect of 2,2'-bipyridine additive on the current and voltage. *Optik* 218:165236–165245. <https://doi.org/10.1016/j.ijleo.2020.165236>
- Costa MJS, Costa GS, Lima AEB, da Luz Júnior GE, Longo E, Cavalcante LS, Santos RS (2018) Photocurrent response and progesterone degradation by employing WO₃ films modified with platinum and silver nanoparticles. *ChemPlusChem* 83:1153–1161. <https://doi.org/10.1002/cplu.201800534>
- Costa GS, Costa MJS, Oliveira HG, Lima LCB, Luz GE Jr, Cavalcante LS, Santos RS (2020) Effect of the applied potential condition on the photocatalytic properties of Fe₂O₃/WO₃ heterojunction films. *J Inorg Organomet Polym Mater* 30:2851–2862. <https://doi.org/10.1007/s10904-019-01429-0>
- Qadir AM, Erdogan IY (2019) Structural properties and enhanced photoelectrochemical performance of ZnO films decorated with Cu₂O nanocubes. *Int J Hydrogen Energy* 44:18694–18702. <https://doi.org/10.1016/j.ijhydene.2019.01.101>
- Maruska HP, Ghosh AK (1979) A study of oxide-based heterostructure photoelectrodes. *Solar Energ Mater* 1:411–429. [https://doi.org/10.1016/0165-1633\(79\)90008-X](https://doi.org/10.1016/0165-1633(79)90008-X)
- Su J, Guo L, Bao N, Grimes CA (2011) Nanostructured WO₃/BiVO₄ heterojunction films for efficient photoelectrochemical water splitting. *Nano Lett* 11:1928–1933. <https://doi.org/10.1021/nl2000743>
- Kamat PV (1993) Photochemistry on nonreactive and reactive (semiconductor) surfaces. *Chem Rev* 93:267–300. <https://doi.org/10.1021/cr00017a013>

16. Sivula K, Formal FL, Grätzel M (2009) $\text{WO}_3\text{-Fe}_2\text{O}_3$ photoanodes for water splitting: a host scaffold, guest absorber approach. *Chem Mater* 21:2862–2867. <https://doi.org/10.1021/cm900565a>
17. Minggu LJ, Daud WRW, Kassim MB (2010) An overview of photocells and photoreactors for photoelectrochemical water splitting. *Int J Hydrogen Energy* 35:5233–5244. <https://doi.org/10.1016/j.ijhydene.2010.02.133>
18. Lima AEB, Reis RYN, Ribeiro LS, Ribeiro LK, Assis M, Santos RS, Fernandes CHM, Cavalcante LS, Longo E, Osajima JAO, Luz GE Jr (2021) Microwave-assisted hydrothermal synthesis of CuWO_4 -palygorskite nanocomposite for enhanced visible photocatalytic response. *J Alloy Compd* 863:158731–158742. <https://doi.org/10.1016/j.jallcom.2021.158731>
19. Moura JPC, Reis RYN, Lima AEB, Santos RS, Luz GE Jr (2020) Improved photoelectrocatalytic properties of ZnO/CuWO_4 heterojunction film for RhB degradation. *Journal of Photochemistry and Photobiology A-Chemistry* 401:112778–112783. <https://doi.org/10.1016/j.jphotochem.2020.112778>
20. García-Pérez UM, Martínez-de la Cruz A, Peral J (2012) Transition metal tungstates synthesized by co-precipitation method: Basic photocatalytic properties. *Electrochim Acta* 81:227–232. <https://doi.org/10.1016/j.electacta.2012.07.045>
21. Chen P, He H-Y (2014) H_2 evolution from $\text{H}_2\text{O}/\text{H}_2\text{O}_2/\text{MWO}_4$ ($\text{M} = \text{Fe}^{2+}, \text{Co}^{2+}, \text{Ni}^{2+}$) systems by photocatalytic reaction. *Res Chem Intermed* 40:1947–1956. <https://doi.org/10.1007/s11164-013-1092-5>
22. Zawawi SMM, Yahya R, Hassan A, Mahmud HNME, Daud MN (2013) Structural and optical characterization of metal tungstates (MWO_4 ; $\text{M}=\text{Ni}, \text{Ba}, \text{Bi}$) synthesized by a sucrose-templated method. *Chem Central J* 7:1–10. <https://doi.org/10.1186/1752-153X-7-80>
23. Ruiz-Fuertes J, Friedrich A, Pellicer-Porres J, Errandonea D, Segura A, Morgenroth W, Haussühl E, Tu C-Y, Polian A (2011) Structure solution of the high-pressure phase of CuWO_4 and evolution of the Jahn-Teller distortion. *Chem Mater* 23:4220–4226. <https://doi.org/10.1021/cm201592h>
24. Ke J, Younis MA, Kong Y, Zhou H, Liu J, Lei L, Hou Y (2018) Nanostructured ternary metal tungstate-based photocatalysts for environmental purification and solar water splitting: a review. *Nano-Micro Letters* 10:69. <https://doi.org/10.1007/s40820-018-0222-4>
25. Errandonea D, Ruiz-Fuertes J (2018) A brief review of the effects of pressure on wolframite-type oxides. *Crystals* 8:71. <https://doi.org/10.3390/cryst8020071>
26. Gao J, Gao Y, Sui Z, Dong Z (2018) Hydrothermal synthesis of BiOBr/FeWO_4 composite photocatalysts and their photocatalytic degradation of doxycycline. *J Alloy Compd* 732:43–51. <https://doi.org/10.1016/j.jallcom.2017.10.092>
27. Gao Q, Liu Z (2017) FeWO_4 nanorods with excellent UV–visible light photocatalysis. *Prog Nat Sci: Mater Int* 27:556–560. <https://doi.org/10.1016/j.pnsc.2017.08.016>
28. Mahendran N, Udayakumar S, Praveen K (2019) pH-Controlled photocatalytic abatement of RhB by an $\text{FeWO}_4/\text{BiPO}_4$ p–n heterojunction under visible light irradiation. *New J Chem* 43:17241–17250. <https://doi.org/10.1039/C9NJ04263F>
29. Shanmugapriya S, Surendran S, Nithya VD, Saravanan P, Selvan RK (2016) Temperature dependent electrical and magnetic properties of CoWO_4 nanoparticles synthesized by sonochemical method. *Mater Sci Eng B* 214:57–67. <https://doi.org/10.1016/j.mseb.2016.09.002>
30. Pandey PK, Bhawe NS, Kharat RB (2006) Structural, optical, electrical and photovoltaic electrochemical characterization of spray deposited NiWO_4 thin films. *Electrochim Acta* 51:4659–4664. <https://doi.org/10.1016/j.electacta.2005.12.042>
31. Song Z, Ma J, Sun H, Wang W, Sun Y, Sun L, Liu Z, Gao C (2009) Synthesis of NiWO_4 nano-particles in low-temperature molten salt medium. *Ceram Int* 35:2675–2678. <https://doi.org/10.1016/j.ceramint.2009.03.010>
32. AlShehri SM, Ahmed J, Alzahrani AM, Ahamad T (2017) Synthesis, characterization, and enhanced photocatalytic properties of NiWO_4 nanobricks. *New J Chem* 41:8178–8186. <https://doi.org/10.1039/C7NJ02085F>
33. Karthiga R, Kavitha B, Rajarajan M, Suganthi A (2015) Photocatalytic and antimicrobial activity of NiWO_4 nanoparticles stabilized by the plant extract. *Mater Sci Semicond Process* 40:123–129. <https://doi.org/10.1016/j.mssp.2015.05.037>
34. Srirapu VKV, Kumar PA, Srivastava P, Singh RN, Sinha ASK (2016) Nanosized CoWO_4 and NiWO_4 as efficient oxygen-evolving electrocatalysts. *Electrochimica Acta* 209:75–84. <https://doi.org/10.1016/j.electacta.2016.05.042>
35. Gaillard N, Chang Y, DeAngelis A, Higgins S, Braun A (2013) A nanocomposite photoelectrode made of 2.2 eV band gap copper tungstate (CuWO_4) and multi-wall carbon nanotubes for solar-assisted water splitting. *Int J Hydrog Energy* 38:3166–3176. <https://doi.org/10.1016/j.ijhydene.2012.12.104>
36. Shekofteh-Gohari M, Habibi-Yangjeh A (2016) Fabrication of novel magnetically separable visible-light-driven photocatalysts through photosensitization of $\text{Fe}_3\text{O}_4/\text{ZnO}$ with CuWO_4 . *J Ind Eng Chem* 44:174–184. <https://doi.org/10.1016/j.jiec.2016.08.028>
37. Lima AEB, Costa MJS, Santos RS, Batista NC, Cavalcante LS, Longo E, Luz GE Jr (2017) Facile preparation of CuWO_4 porous films and their photoelectrochemical properties. *Electrochim Acta* 256:139–145. <https://doi.org/10.1016/j.electacta.2017.10.010>
38. Ding W, Wu X, Lu Q (2019) Structure and photocatalytic activity of thin-walled CuWO_4 nanotubes: an experimental and DFT study. *Mater Lett* 253:323–326. <https://doi.org/10.1016/j.matlet.2019.06.109>
39. Mohanty B, Naik KK, Sahoo S, Jena B, Chakraborty B, Rout CS, Jena BK (2018) Efficient photoelectrocatalytic activity of CuWO_4 nanoplates towards the oxidation of NADH driven in visible light. *ChemistrySelect* 3:9008–9012. <https://doi.org/10.1002/slct.201801137>
40. Zhou M, Liu Z, Li X, Liu Z (2018) Promising three-dimensional flowerlike CuWO_4 photoanode modified with CdS and FeOOH for efficient photoelectrochemical water splitting. *Ind Eng Chem Res* 57:6210–6217. <https://doi.org/10.1021/acs.iecr.8b00358>
41. Lalić MV, Popović ZS, Vukajlović FR (2012) Electronic structure and optical properties of CuWO_4 : AN ab initio study. *Comput Mater Sci* 63:163–167. <https://doi.org/10.1016/j.commatsci.2012.05.074>
42. Gonzalez CM, Du X, Dunford JL, Post ML (2012) Copper tungstate thin-films for nitric oxide sensing. *Sens Actuators, B Chem* 173:169–176. <https://doi.org/10.1016/j.snb.2012.06.067>
43. Poovaragan S, Sundaram R, Magdalane CM, Kaviyarasu K, Maaza M (2019) Photocatalytic activity and humidity sensor studies of magnetically reusable $\text{FeWO}_4\text{-WO}_3$ composite nanoparticles. *J Nanosci Nanotechnol* 19:859–866. <https://doi.org/10.1166/jnn.2019.15565>
44. Lannelongue P, Le Vot S, Fontaine O, Brousse T, Favier F (2019) Electrochemical study of asymmetric aqueous supercapacitors based on high density oxides: $\text{C/Ba}_{0.5}\text{Sr}_{0.5}\text{Co}_{0.8}\text{Fe}_{0.2}\text{O}_{3-8}$ and $\text{FeWO}_4/\text{Ba}_{0.5}\text{Sr}_{0.5}\text{Co}_{0.8}\text{Fe}_{0.2}\text{O}_{3-8}$. *Electrochimica Acta*. 326:134886. <https://doi.org/10.1016/j.electacta.2019.134886>
45. Kumar RD, Karuppuchamy S (2014) Microwave-assisted synthesis of copper tungstate nanopowder for supercapacitor applications. *Ceram Int* 40:12397–12402. <https://doi.org/10.1016/j.ceramint.2014.04.090>
46. Kumar RD, Karuppuchamy S (2016) Microwave mediated synthesis of nanostructured Co-WO_3 and CoWO_4 for supercapacitor

- applications. *J Alloy Compd* 674:384–391. <https://doi.org/10.1016/j.jallcom.2016.03.074>
47. Li CL, Fu ZW (2008) Nano-sized copper tungstate thin films as positive electrodes for rechargeable Li batteries. *Electrochim Acta* 53:4293–4301. <https://doi.org/10.1016/j.electacta.2008.01.014>
 48. Liu J, Zhang Z, Wang Z, Tang M, Li J, Yi J, Zuo T, Wu Y, Ma Q (2017) Flower-like $\text{WO}_3/\text{CoWO}_4/\text{Co}$ nanostructures as high performance anode for lithium ion batteries. *J Alloy Compd* 727:107–113. <https://doi.org/10.1016/j.jallcom.2017.08.057>
 49. Peng T, Liu C, Hou X, Zhang Z, Wang C, Yan H, Lu Y, Liu X, Luo Y (2017) Control growth of mesoporous nickel tungstate nanofiber and its application as anode material for lithium-ion batteries. *Electrochim Acta* 224:460–467. <https://doi.org/10.1016/j.electacta.2016.11.154>
 50. Thongpan W, Louloudakis D, Pooseekheaw P, Kumpika T, Kantarak E, Sroila W, Panthawan A, Thongsuwan W, Singjai P (2019) Porous $\text{CuWO}_4/\text{WO}_3$ composite films with improved electrochromic properties prepared by sparking method. *Mater Lett* 257:126747. <https://doi.org/10.1016/j.matlet.2019.126747>
 51. Tang Y, Rong N, Liu F, Chu M, Dong H, Zhang Y, Xiao P (2016) Enhancement of the photoelectrochemical performance of CuWO_4 films for water splitting by hydrogen treatment. *Appl Surf Sci* 361:133–140. <https://doi.org/10.1016/j.apsusc.2015.11.129>
 52. Hu D, Diao P, Xu D, Xia M, Gu Y, Wu Q, Li C, Yang S (2016) Copper(II) tungstate nanoflake array films: sacrificial template synthesis, hydrogen treatment, and their application as photoanodes in solar water splitting. *Nanoscale* 8:5892–5901. <https://doi.org/10.1039/C5NR09210H>
 53. Abdul-hamead AA, Salman ZA, Othman FM (2019) Synthesis and characterization of Iron tungstate oxide films by advanced controlled spray pyrolysis technique. *Iraqi J Phys* 17:29–39. <https://doi.org/10.20723/ijp.17.41.29-39>
 54. Yourey JE, Bartlett BM (2011) Electrochemical deposition and photoelectrochemistry of CuWO_4 , a promising photoanode for wateroxidation. *J Mater Chem* 21:7651–7660. <https://doi.org/10.1039/C1JM11259G>
 55. Gouveia AF, Vieira VEM, Sczancoski JC, Lemos PS, Rout SK, Arul NS, Longo E, Cavalcante LS (2020) Electronic structure, morphological aspects, and photocatalytic discoloration of three organic dyes with MgWO_4 powders synthesized by the complex polymerization method. *J Inorg Organomet Polym Mater* 30(2020):2952–2970. <https://doi.org/10.1007/s10904-019-01435-2>
 56. Benchikhi M, Ouatib RE, Guillemet-Fritsch S, Er-Rakho L, Durand B (2017) Investigation of structural transition in molybdates $\text{CuMo}_{1-x}\text{W}_x\text{O}_4$ prepared by polymeric precursor method. *Processing and Application of Ceramics* 11:21–26. <https://doi.org/10.2298/PAC1701021B>
 57. Dimesso L (2016) Pechini processes: an alternate approach of the sol–gel method, preparation, properties, and applications. In: Klein L, Aparicio M, Jitianu A (eds) *Handbook of sol-gel science and technology*. Springer, Cham. https://doi.org/10.1007/978-3-319-19454-7_123-1
 58. Kakihana M (1996) Invited review “sol-gel” preparation of high temperature superconducting oxides. *J Sol-Gel Sci Technol* 6:7–55. <https://doi.org/10.1007/BF00402588>
 59. Maurera MAMA, Souza AG, Soledade LEB, Pontes FM, Longo E, Leite ER, Varela JA (2004) Microstructural and optical characterization of CaWO_4 and SrWO_4 thin films prepared by a chemical solution method. *Mater Lett* 58:727–732. <https://doi.org/10.1016/j.matlet.2003.07.002>
 60. Cavalcante LS, Sczancoski JC, Albarici VC, Matos JME, Varela JA (2008) Synthesis, characterization, structural refinement and optical absorption behavior of PbWO_4 powders. *Mater Sci Eng B* 150:18–25. <https://doi.org/10.1016/j.mseb.2008.02.003>
 61. Tauc J (1968) Optical properties and electronic structure of amorphous Ge and Si. *Mater Res Bull* 3:37–46. [https://doi.org/10.1016/0025-5408\(68\)90023-8](https://doi.org/10.1016/0025-5408(68)90023-8)
 62. Resende ALS, Costa AGR, Lima AEB, Costa MJS, Longo E, Cavalcante LS, Santos RS (2020) An investigation of photovoltaic devices based on p-type Cu_2O and n-type $\gamma\text{-WO}_3$ junction through an electrolyte solution containing a redox pair. *Int J Energy Res* 45:2797–2809. <https://doi.org/10.1002/er.5974>
 63. Gärtner WW (1959) Depletion-layer photoeffects in semiconductors. *Phys Rev* 116:84–87. <https://doi.org/10.1103/PhysRev.116.84>
 64. Butler MA (1977) Photoelectrolysis and physical properties of the semiconducting electrode WO_2 . *J Appl Phys* 48:1914–1920. <https://doi.org/10.1063/1.323948>
 65. Yang W, Prabhakar RR, Tan J, Tilley SD, Moon J (2019) Strategies for enhancing the photocurrent, photovoltage, and stability of photoelectrodes for photoelectrochemical water splitting. *Chem Soc Rev* 48:4979–5015. <https://doi.org/10.1039/C8CS00997J>
 66. Bard AJ, Faulkner LR (2001) *Electrochemical methods: fundamentals and applications*, 2nd edn. Wiley, New Jersey, p 54
 67. Dholam R, Patel N, Santini A, Miotello A (2010) Efficient indium tin oxide/Cr-doped- TiO_2 multilayer thin films for H_2 production by photocatalytic water-splitting. *Int J Hydrogen Energy* 35:9581–9590. <https://doi.org/10.1016/j.ijhydene.2010.06.097>
 68. Spadavecchia F, Ardizzone S, Cappelletti G, Falciola L, Ceotto M, Lotti D (2013) Investigation and optimization of photocurrent transient measurements on nano- TiO_2 . *J Appl Electrochem* 43:217–225. <https://doi.org/10.1007/s10800-012-0485-2>
 69. Escobar C, Cid-Dresdner H, Kittl P, Duemler I (1971) The Relation between “light wolframite” and common wolframite. *Am Miner* 56:489–498
 70. Weitzel H (1976) Kristallstrukturverfeinerung von Wolframiten und Columbiten. *Z Kristallogr* 144:238–258. <https://doi.org/10.1524/zkri.1976.144.16.238>
 71. Kihlborg L, Gebert E (1970) CuWO_4 , a distorted wolframite-type structure. *Acta Crystallogr Sect B: Struct Crystallogr Cryst Chem* 26:1020–1026. <https://doi.org/10.1107/S0567740870003515>
 72. Yu F, Cao L, Huang J, Wu J (2013) Effects of pH on the microstructures and optical property of FeWO_4 nanocrystallites prepared via hydrothermal method. *Ceram Int* 39:4133–4138. <https://doi.org/10.1016/j.ceramint.2012.10.269>
 73. Innocenzi P, Malfatti L (2013) Mesoporous thin films: properties and applications. *Chem Soc Rev* 42:4198–4216. <https://doi.org/10.1039/C3CS35377J>
 74. Wilber. Image Manipulation Program. *Gimp—GNU* (Version 2.10.30) 21 Dec 2021. <https://www.gimp.org/news/2021/12/21/gimp-2-10-30-released/>
 75. Kwong WL, Savvides N, Sorrell CC (2012) Electrodeposited nanostructured WO_3 thin films for photoelectrochemical applications. *Electrochim Acta* 75:371–380. <https://doi.org/10.1016/j.electacta.2012.05.019>
 76. Zhang J, Wang Y, Li S, Wang X, Huang F, Xie A, Shen Y (2011) Controlled synthesis, growth mechanism and optical properties of FeWO_4 hierarchical microstructures. *Cryst Eng Commun* 13:5744–5750. <https://doi.org/10.1039/C1CE05416C>
 77. Ejima T, Banse T, Takatsuka H, Kondo Y, Ishino M, Kimura N, Watanabe M, Matsubara I (2006) Microscopic optical and photoelectron measurements of MWO_4 (M=Mn, Fe, and Ni). *J Lumines* 119:59–63. <https://doi.org/10.1016/j.jlumin.2005.12.012>

78. Ling C, Zhou LQ, Jia H (2014) First-principles study of crystalline CoWO_4 as oxygen evolution reaction catalyst. *RSC Adv* 4:24692–24697. <https://doi.org/10.1039/C4RA03893B>
79. Bharati R, Singh RA, Wanklyn BM (1981) On electrical transport in CoWO_4 single crystals. *J Mater Sci* 16:775–779. <https://doi.org/10.1007/BF02402795>
80. Tian CM, Jiang M, Tang D, Qiao L, Xiao HY, Oropeza FE, Hofmann JP, Hensen EJM, Tadich A, Li W, Qi DC, Zhang KHL (2019) Elucidating the electronic structure of CuWO_4 thin films for enhanced photoelectrochemical water splitting. *J Mater Chem A* 7:11895–11907. <https://doi.org/10.1039/C8TA12070F>
81. Ojha DP, Karki HP, Song J, Kim HJ (2018) Decoration of $\text{g-C}_3\text{N}_4$ with hydrothermally synthesized FeWO_4 nanorods as the high-performance supercapacitors. *Chem Phys Lett* 712:83–88. <https://doi.org/10.1016/j.cplett.2018.09.070>
82. Rajagopal S, Khyzhun OY, Djaoued Y, Robichaud J, Mangalaraj D (2010) Hydrothermal synthesis and electronic properties of FeWO_4 and CoWO_4 nanostructures. *J Alloy Compd* 493:340–345. <https://doi.org/10.1016/j.jallcom.2009.12.099>
83. Zhu J, Li W, Li J, Li Y, Hu H, Yang Y (2013) Photoelectrochemical activity of $\text{NiWO}_4/\text{WO}_3$ heterojunction photoanode under visible light irradiation. *Electrochim Acta* 112:191–198. <https://doi.org/10.1016/j.electacta.2013.08.146>
84. Wang H, Wang C, Cui X, Qina L, Ding R, Wang L, Liu Z, Zheng Z, Lv B (2018) Design and facile one-step synthesis of $\text{FeWO}_4/\text{Fe}_2\text{O}_3$ di-modified WO_3 with super high photocatalytic activity toward degradation of quasi-phenothiazine dyes. *Appl Catal B* 221:169–178. <https://doi.org/10.1016/j.apcatb.2017.09.011>
85. Dadigala R, Bandi R, Gangapuram BR, Guttena V (2019) Construction of in situ self-assembled $\text{FeWO}_4/\text{g-C}_3\text{N}_4$ nanosheet heterostructured Z-scheme photocatalysts for enhanced photocatalytic degradation of rhodamine B and tetracycline. *Nanoscale Advances* 1:322–333. <https://doi.org/10.1039/C8NA00041G>
86. Sadiq MMJ, Shenoy US, Bhat DK (2017) Enhanced photocatalytic performance of N-doped RGO- $\text{FeWO}_4/\text{Fe}_3\text{O}_4$ ternary nanocomposite in environmental applications. *Mater Today Chem* 4:133–141. <https://doi.org/10.1016/j.mtchem.2017.04.003>
87. Chen S, Yang G, Jia Y, Zheng H (2016) Facile synthesis of CoWO_4 nanosheet arrays grown on nickel foam substrates for asymmetric supercapacitors. *ChemElectroChem* 3:1490–1496. <https://doi.org/10.1002/celec.201600316>
88. Luo F, Xu R, Ma S, Zhang Q, Hu H, Qu K, Xiao S, Yang Z, Cai W (2019) Engineering oxygen vacancies of cobalt tungstate nanoparticles enable efficient water splitting in alkaline medium. *Appl Catal B: Environ* 259:118090. <https://doi.org/10.1016/j.apcatb.2019.118090>
89. Chen S, Yang G, Jia Y, Zheng H (2017) Three-dimensional $\text{NiCo}_2\text{O}_4@/\text{NiWO}_4$ core-shell nanowire arrays for high performance supercapacitors. *J Mater Chem A* 5:1028–1034. <https://doi.org/10.1039/C6TA08578D>
90. Nesbitt HW, Legrand D, Bancroft GM (2000) Interpretation of $\text{Ni}2\text{p}$ XPS spectra of Ni conductors and Ni insulators. *Phys Chem Miner* 27:357–366. <https://doi.org/10.1007/s002690050265>
91. McIntyre S, Cook MG (1975) X-ray photoelectron studies on some oxides and hydroxides of cobalt, nickel, and copper. *Anal Chem* 47:2208–2213. <https://doi.org/10.1021/ac60363a034>
92. Dong H, Li Y, Gao D, Zhou M, Hu X, Peng H, Yang L, He J, Zhang Y, Xiao P (2019) Efficient self-assembly solvothermal synthesis of octahedral CuWO_4 microstructures assisted by ethylene glycol. *J Alloy Compd* 785:660–668. <https://doi.org/10.1016/j.jallcom.2019.01.224>
93. Signorelli AJ, Hayes RG (1973) X-Ray photoelectron spectroscopy of various core levels of lanthanide ions: the roles of monopole excitation and electrostatic coupling. *Phys Rev B* 8:81–86. <https://doi.org/10.1103/PhysRevB.8.81>
94. Cao X, Chen Y, Jiao S, Fang Z, Xu M, Liu X, Li L, Pang G, Feng S (2014) Magnetic photocatalysts with a p–n junction: Fe_3O_4 nanoparticle and FeWO_4 nanowire heterostructures. *Nanoscale* 6:12366–12370. <https://doi.org/10.1039/C4NR03729D>
95. Liu Z, Song Q, Zhou M, Guo Z, Kang J, Yan H (2019) Synergistic enhancement of charge management and surface reaction kinetics by spatially separated cocatalysts and p–n heterojunctions in $\text{Pt}/\text{CuWO}_4/\text{Co}_3\text{O}_4$ photoanode. *Chem Eng J* 374:554–563. <https://doi.org/10.1016/j.cej.2019.05.191>
96. Yang J, Li C, Diao P (2019) Molybdenum doped CuWO_4 nanoflake array films as an efficient photoanode for solar water splitting. *Electrochim Acta* 308:195–205. <https://doi.org/10.1016/j.electacta.2019.04.044>
97. Liu L, Mei Z, Tang A, Azarov A, Kuznetsov A, Xue QK, Du X (2016) Oxygen vacancies: the origin of n-type conductivity in ZnO . *Phys Rev B* 93:235305. <https://doi.org/10.1103/physrevb.93.235305>
98. Oliveira HG, Ferreira LH, Bertazzoli R, Longo C (2015) Remediation of 17- α -ethinylestradiol aqueous solution by photocatalysis and electrochemically-assisted photocatalysis using TiO_2 and TiO_2/WO_3 electrodes irradiated by a solar simulator. *Water Res* 72:305–314. <https://doi.org/10.1016/j.watres.2014.08.042>
99. Lim Y-F, Chua CS, Lee CJJ, Chi D (2014) Sol-gel deposited Cu_2O and CuO thin films for photocatalytic water splitting. *Phys Chem Chem Phys* 16:25928–25934. <https://doi.org/10.1039/C4CP03241A>
100. Xiong X, Fan L, Chen G, Wang Y, Wu C, Chen D, Lin Y, Li T, Fu S, Ren S (2019) Boosting water oxidation performance of CuWO_4 photoanode by surface modification of nickel phosphate. *Electrochim Acta* 328:135125. <https://doi.org/10.1016/j.electacta.2019.135125>
101. Hankin A, Bedoya-Lora FE, Alexander JC, Regoutz A, Kelsall GH (2019) Flat band potential determination: avoiding the pitfalls. *J Mater Chem A* 7:26162–26176. <https://doi.org/10.1039/C9TA09569A>
102. Costa MJS, Costa GS, Lima AEB, Luz GE Jr, Longo E, Cavalcante LS, Santos RS (2018) Investigation of charge recombination lifetime in $\gamma\text{-WO}_3$ films modified with Ag^0 and Pt^0 nanoparticles and its influence on photocurrent density. *Ionic* 24:3291–3297. <https://doi.org/10.1007/s11581-018-2640-1>
103. Radecka M, Rekas M, Trenczek-Zajac A, Zakrzewska K (2008) Importance of the band gap energy and flat band potential for application of modified TiO_2 photoanodes in water photolysis. *J Power Sour* 181:46–55. <https://doi.org/10.1016/j.jpowsour.2007.10.082>
104. Bak T, Nowotny J, Rekas M, Sorrell CC (2002) Photo-electrochemical hydrogen generation from water using solar energy. Materials-related aspects. *Int J Hydrog Energ* 27:991–1021. [https://doi.org/10.1016/S0360-3199\(02\)00022-8](https://doi.org/10.1016/S0360-3199(02)00022-8)
105. Liu Y, Li J, Li W, He H, Yang Y, Li Y, Chen Q (2016) Electrochemical doping induced in situ homo-species for enhanced photoelectrochemical performance on WO_3 nanoparticles film photoelectrodes. *Electrochim Acta* 210:251–260. <https://doi.org/10.1016/j.electacta.2016.05.165>
106. Shrestha NK, Schmuki P (2013) Electrochemistry at TiO_2 nanotubes and other semiconductor nanostructures. *Electrochemistry* 12:87–131. <https://doi.org/10.1039/9781849737333-00087>
107. Alpuche-Aviles MA, Wu Y (2009) Photoelectrochemical study of the band structure of Zn_2SnO_4 prepared by the hydrothermal method. *J Am Chem Soc* 131:3216–3224. <https://doi.org/10.1021/ja806719x>
108. Paulauskas IE, Katz JE, Jellison GE Jr, Lewis NS, Boatner LA, Brown GM (2009) Growth, characterization, and electrochemical properties of doped n-type KTaO_3 photoanodes. *J Electrochem Soc* 156:B580–B587. <https://doi.org/10.1149/1.3089281>

109. Chen H, Leng W, Xu Y (2014) Enhanced visible-light photoactivity of CuWO_4 through a surface-deposited CuO . *J Phys Chem C* 118:9982–9989. <https://doi.org/10.1021/jp502616h>
110. Linsebigler AL, Lu G, Yates JT Jr (1995) Photocatalysis on TiO_2 surfaces: principles, mechanisms, and selected results. *Chem Rev* 95:735–758. <https://doi.org/10.1021/cr00035a013>
111. Hagfeldt A, Graetzel M (1995) Light-induced redox reactions in nanocrystalline systems. *Chem Rev* 95:49–68. <https://doi.org/10.1021/cr00033a003>
112. Polo A, Nomellini C, Grigioni I, Dozzi MV, Selli E (2020) Effective visible light exploitation by copper molybdo-tungstate photoanode. *ACS Appl Energ Mater* 3:6956–6964. <https://doi.org/10.1021/acsaem.0c01021>
113. Duan X, Xu C, El Nahrawy AMJ, Chen Z, Zhu J, Wang Q, Liang F, Cao (2022) Ultrasonic spray pyrolysis-assisted fabrication of ultrathin CuWO_4 films with improved photoelectrochemical performance. *ChemNanoMat* 8:e202100419. <https://doi.org/10.1002/cnma.202100419>
114. Lima AEB, Assis M, Resende ALS, Santos HLS, Mascaro LH, Longo E, Santos RS, Cavalcante LS, Luz GE Jr (2022) $\text{CuWO}_4/\text{MnWO}_4$ heterojunction thin film with improved photoelectrochemical and photocatalytic properties using simulated solar irradiation. *J Solid State Electrochem* 26:997–1011. <https://doi.org/10.1007/s10008-022-05143-9>
115. Chidambaram S, Ramachandran K, Gaidi M, Daoudi K, Natarajamoorthy M (2021) Solution combustion synthesis of iron tungstate nanoparticles for photoelectrochemical water splitting towards oxygen evolution. *J Mater Sci: Mater Electron* 33:9134–9143. <https://doi.org/10.1007/s10854-021-07146-0>
116. Rosa WS, Rabelo LG, Zampaulo LGT, Gonçalves RV (2022) Ternary oxide $\text{CuWO}_4/\text{BiVO}_4/\text{FeCoO}_x$ films for photoelectrochemical water oxidation: insights into the electronic structure and interfacial band alignment. *ACS Appl Mater Interfaces* 14(20):22858–22869. <https://doi.org/10.1021/acsaami.1c21001>
117. Chatterjee P, Chakraborty AK (2022) Enhanced solar water oxidation by $\text{CoWO}_4\text{-WO}_3$ heterojunction photoanode. *Sol Energ* 232:312–319. <https://doi.org/10.1016/j.solener.2021.12.075>
118. Cho HE, Yun G, Arunachalam M, Ahn KS, Kim CS, Lim D-H, Kang SH (2018) Nanolayered CuWO_4 decoration on fluorine-doped SnO_2 inverse opals for solar water oxidation. *J Electrochem Sci Technol* 9:282–291. <https://doi.org/10.5229/JECST.2018.9.4.282>
119. Zhang Y, Wang L, Xu X (2021) A bias-free $\text{CuBi}_2\text{O}_4\text{-CuWO}_4$ tandem cell for solar-driven water splitting. *Inorg Chem Front* 8:3863–3870. <https://doi.org/10.1039/D1Q100088H>
120. Ahmed MI, Adam A, Khan A, Rehman AU, Qamaruddin M, Siddiqui MN, Qamar M (2016) Improved photoelectrochemical water oxidation under visible light with mesoporous CoWO_4 . *Mater Lett* 183:281–284. <https://doi.org/10.1016/j.matlet.2016.07.137>
121. Babu ES, Rani BJ, Ravi G, Yuvakkumar R, Guduru RK, Ganesh V, Kim S (2018) Novel NiWO_4 nanoberries morphology effect on photoelectrochemical properties. *Mater Lett* 220:209–212. <https://doi.org/10.1016/j.matlet.2018.03.018>
122. Ahmed MI, Adam A, Khan A, Siddiqui MN, Yamani Z, Qamar HM (2016) Synthesis of mesoporous NiWO_4 nanocrystals for enhanced photoelectrochemical water oxidation. *Mater Lett* 177:135–138. <https://doi.org/10.1016/j.matlet.2016.04.143>
123. Sun Y, Du F, Xie D, Yang D, Jiao Y, Jia L, Fan H (2020) Improved water oxidation via Fe doping of CuWO_4 photoanodes: influence of the Fe source and concentration. *Chinese Phys B* 29:127801. <https://doi.org/10.1088/1674-1056/aba9cb>
124. Chen Z, Löber M, Rokicińska A, Ma Z, Chen J, Kuśtrowski P, Meyer H-J, Dronskowski R, Slabon A (2020) Increased photocurrent of CuWO_4 photoanodes by modification with the oxide carbodiimide $\text{Sn}_2\text{O}(\text{NCN})$. *Dalton Trans* 49:3450–3456. <https://doi.org/10.1039/C9DT04752B>
125. Balasubramanian V, Kannan S, Thangaraj NS, Sivakumar G, Mohanraj K (2020) Role of W-Rich CuWO_4 and Doped Zn- CuWO_4 ceramics and its improved photoelectrochemical cell performances synthesized by solid state reaction method. *ChemistrySelect* 5:8959–8968. <https://doi.org/10.1002/slct.202000229>

Publisher's Note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

Springer Nature or its licensor (e.g. a society or other partner) holds exclusive rights to this article under a publishing agreement with the author(s) or other rightsholder(s); author self-archiving of the accepted manuscript version of this article is solely governed by the terms of such publishing agreement and applicable law.