ORIGINAL PAPER

Application of silica vanadic acid $[SiO_2-VO(OH)_2]$ as a heterogeneous and recyclable catalyst for oxidative aromatization of Hantzsch 1,4-dihydropyridines at room temperature

Maliheh Safaiee · Mohammad Ali Zolfigol · Mahsa Tavasoli · Mohammad Mokhlesi

Received: 30 August 2013 / Accepted: 7 February 2014 / Published online: 25 February 2014 © Iranian Chemical Society 2014

Abstract A simple method for the oxidative aromatization of Hantzsch 1,4-dihydropyridines to the corresponding pyridines is described using hydrogen peroxide as green oxidant and silica vanadic acid as catalyst in acetonitrile at room temperature. The catalyst can be easily recovered and reused for 15 reaction cycles without considerable loss of activity.

Keywords Hantzsch 1,4-dihydropyridines · Aromatization · Hydrogen peroxide · Silica vanadic acid

Introduction

Development of heterogeneous catalysts for fine chemicals synthesis has become a major area of research. One of the major drawbacks of the homogeneous catalysts is the difficulty in separating the relatively expensive catalysts from the reaction mixture at the end of the process. The possible contamination of catalyst in the product also restricts their use in industry. Efficient anchoring of these catalysts on supports may overcome these drawbacks. Since the catalytic action occurs at specific sites on the solid surface, often called "active sites", the uniform dispersion of metal catalysts is highly desirable for significant improvement of catalytic action. These types of catalysts have used various support materials. One of the

M. Safaiee (⊠)

M. A. Zolfigol · M. Tavasoli · M. Mokhlesi Faculty of Chemistry, Bu-Ali Sina University, P.O. Box 6517838683, Hamedan, Iran useful examples of support materials is silica gel. This inorganic supporter has some advantageous properties such as excellent stability, good accessibility and high surface area; this will be beneficial to the enhancement of loading amount and dispersion of catalytic action [1]. Also, the design of silica-supported transition metal oxides represents a rapidly growing field that has been significantly applied in industry. Among the various transition metals, vanadium, an early member of the 3d transition metal series, exists on the surface of the earth more abundantly and catalytic systems based on the supported vanadium oxide exhibit interesting catalytic properties for the partial oxidation of alkanes, aromatics, alcohols, and alkenes and dehydrogenation of different hydrocarbons [2–4].

Hantzsch 1,4-dihydropyridines are easily prepared from the Hantzsch reaction or its modifications [5-8]. In recent years, it has been found that drugs such as nifedipine and niguldipine undergo redox processes due to the catalysis of cytochrome P-450 in the liver during their metabolism [9]. Therefore, the oxidation of 1,4-dihydropyridines has attracted considerable attention. Several oxidation reagents have been reported for the oxidation of 1,4-dihydropyridines, such as SeO₂ [10], lead(IV) tetraacetate [11], FeCl₃/ KMnO₄ [12], Pd/C [13], nicotinium dichromate [14], silica-gel-supported ferric nitrate (silfen), N₂O₃, MCl_y/ NaNO₂/wet SiO₂ and silica chloride/NaNO₂ wet SiO₂ [15, 16], H₂O₂/Co(OAc)₂ [17], NaHSO₄/Na₂Cr₂O₇/wet SiO₂ [18], peroxydisulfate-cobalt(II) [19], $Zr(NO_3)_4$ [20], Co(II)-catalyzed auto oxidation) [21], $KBrO_3/MCl_n$ [22, 23], $(n-Bu)_4IO_4/[Mn(TPP)Cl]$ [24], Mn(III)-salophen/ NaIO₄ [25], oxone [26], M(NO₃)₂.XH₂O [27], NaClO₂ [28], graphite oxide [29], and Solid acid/NaNO₂ [30]. In this paper, we want to apply silica vanadic acid in the oxidation of dihydropyridines.

Department of Aromatic and Medicinal Plants, Nahavand University, P.O. Box 6591678546, Nahavand, Iran e-mail: azalia_s@yahoo.com; msafaiee@basu.ac.ir

Scheme 1 Synthesis of silica vanadic acid (SVA)



Experimental

Synthesis of silica vanadic acid

In a 100 mL round-bottomed flask, *n*-hexane (25 mL) and silica gel (4.0 g) were stirred for 10 min and then vanadiumoxytrichloride (4.0 g) was dissolved in *n*-hexane (25 mL) and added drop wise to the silica gel suspension (15–20 min). After addition of VOCl₃, the red-brown mixture was stirred for 10 h. Then, solvent was evaporated and the residue (the red-brown powder (**II**) was obtained after the grafting process) was filtered, washed with dry *n*-hexane several times to remove unreacted VOCl₃, dried under vacuum, and stirred in the air for 72 h to promote the hydrolysis of V–O–Cl bonds. At this time the red-brown powder changed to dark green powder (**III**) slowly (Scheme 1) [31, 32]. Typical loading of vanadium was determined using X-ray fluorescence (XRF) and showed a loading 8 ± 0.1 mmol g⁻¹.

General procedure for the oxidation of 1,4dihydropyridines

A suspension of compound 1, silica vanadic acid, and H_2O_2 (5 mmol) in CH₃CN (5 mL) was stirred at room temperature for a specific time (molar ratio of reagents and reactions times are indicated in Table 1). The progress of the reaction was monitored by thin-layer chromatography (TLC). After the spot of starting material 1 on TLC disappeared (Scheme 2), the reaction mixture was filtered off. The solvent was removed, and pure product 2 was obtained.

Results and discussion

In continuation of our studies on the synthesis of new inorganic silica-based resins [33], we found that silica gel reacts with vanadiumoxytrichloride to give silica vanadic acid.

Based on our previous studies on the use of silica vanadic acid as catalyst for carrying out organic reactions [31, 32], and continuing our interest in aromatization of Hantzsch 1,4-dihydropyridines [34], we examined the possibility of using a silica vanadic acid as a oxidation agent in the presence of H_2O_2 on the oxidation aromatization of Hantzsch 1,4-dihydropyridines.

Entry	R ₁	R ₂	Substrate	Product	Time (min)	Yield (%)	
1	COMe	Н	1a	2a	10	97	
2	COMe	Me	1b	2b	18	95	
3	COMe	Ph	1c	2c	60	50	
4	COMe	2-OMe-C ₆ H ₄	1d	2d	26	95	
5	COMe	4-OMe-C ₆ H ₄	1e	2e	25	98	
6	COMe	2,5-(OMe) ₂ - C ₆ H ₃	1f	2f	53	88	
7	COMe	$2-NO_2-C_6H_4$	1 g	2 g	55	65	
8	COMe	$3-NO_2-C_6H_4$	1 h	2 h	35	93	
9	COMe	2-Furyl	1i	2i	26	93	
10	COOEt	Н	1j	2j	10	95	
11	COOEt	Me	1 k	2 k	13	90	
12	COOEt	Et	11	21	45	90	
13	COOEt	2-OMe-C ₆ H ₄	1 m	2 m	16	90	
14	COOEt	$3-NO_2-C_6H_4$	1n	2n	18	92	
15	COOEt	2-Pyridyl	10	20	90	90	
16	COOEt	$3-Br-C_6H_4$	1p	2p	9	94	
17	COOEt	4-Br-C ₆ H ₄	1q	2q	14	93	
18	COOEt	2-Furyl	1r	2r	20	96	

Reaction condition: dihydropyridines (1 mmol), H_2O_2 (30 %) (5 mmol), SVA (0.01 g), CH₃CN (5 mL), room temperature, stir

 Table 2
 Oxidation
 of
 diethyl
 1,4-dihydro-2,6-dimethyl-3,5-pyridinedicarboxylate
 using
 in various
 amount
 of
 catalyst

Entry	Oxidant (mmol)	Catalyst	Time (min)	Yield (%) ^a
1	5	0.01	10	95
2	5	0.05	10	95
3	5	0.1	10	95
4	_	0.05	100	60 ^b
5	5	-	330	95

Reaction condition: 1,4-dihydro pyridine (1 mmol), CH₃CN (5 mL), stir, room temperature

^a Isolated yield

^b Conversion

A good range of dihydropyridines(1) was subjected to the oxidation reaction in the presence of silica vanadic acid and H_2O_2 , in acetonitrile (Scheme 2).

We preferred hydrogen peroxide as oxidant over other available oxidizing agent since it is cheap, operationally safe, environmentally friendly and easy to handle while it **Scheme 2** Oxidation of 1,4-DHP using SVA/H₂O₂ in acetonitrile at room temperature



 $R_1 = CO_2Et$, COMe

 R_2 = Alkyl , Aryl, Phenyl, Heteroaromatic

Table 3 Optimization of solvent for SVA–H₂O₂ mediated oxidative aromatization of 3,5-diacetyl-1,4-dihydro-2,6-dimethylpyridine

Entry	Solvent	Time	Yield ^b
1	CH ₃ CH ₂ OH	70	60
2	CH ₃ OH	55	95
3	CHCl ₃	41	95
4	CH_2Cl_2	35	95
5	CH ₃ COOC ₂ H ₅	53	95
6	H ₂ O	100	40
7	<i>n</i> -Hexane	75	93
8	CH ₃ CN	10	97

Reaction condition: 1,4-dihydropyridine (1 mmol), silica vanadic acid (0.01 g), H_2O_2 (5 mmol), stir, rt

^b Isolated yield

produces only water as a by-product, which reduces purification requirements.

In order to get the best reaction condition, the efficiency of a variety of silica vanadic acid (SVA) in the oxidation of diethyl 1,4-dihydro-2,6-dimethyl-3,5-pyridinedicarboxylate as a model reaction was studied. The best catalytic activity was optimized to be 0.01 g for 1 mmol of starting material in the model reaction and using the catalyst excess (0.05 g) does not show further increase in the conversion and yield of the product. Also, in the absence of catalyst or oxidant, the reaction goes slow or is not complete (Table 2).

Solvent effect on oxidation reaction, in ethanol, methanol, chloroform, ethylacetate, water, *n*-hexane, acetonitrile and dichloromethane was investigated. Although these organic mediums were found unsuitable for this oxidative aromatization, SVA/H_2O_2 system worked quite efficiently in acetonitrile. The results of this study are summarized in Table 3.

A series of 1,4-DHPs were aromatized using the optimized reaction conditions (as shown in Table 1). The reaction proceeded smoothly with various 1,4-DHPs bearing electron rich as well as electron deficient aromatic substituents at C-4. The reaction is quite general and is successfully applied to 1,4-DHPs having aliphatic as well as, substituents at C-4.

The reaction was mild and the workup was straightforward, requiring simple evaporation of the solvent; then, highly pure pyridine derivatives 2 could be obtained if the product is passed through a short pad of silica gel and evaporation of the solvent. The results and reaction conditions are given in Table 1.

In order to recover the catalyst, CH_3CN was evaporated under reduced pressure and removing the product by extracting with ether from the reaction mixture and charging the reaction vessel with fresh substrate and H_2O_2 30 % and then repeating the experiment. The recovered catalyst was reused fifteen times in the oxidation of 3,5diacetyl-1,4-dihydro-2,6-dimethylpyridine (**1a**) with H_2O_2 , and smooth loss of catalytic activity was observed from the 11th time of reuse (Table 4).

To assess the capability and efficiency of our catalyst with respect to the reported catalysts for oxidation of dihydropyridines, the results of the application of these catalysts for the preparation of some pyridines are tabulated in Table 5. The described method has many advantages over other methods, such as, high recycling, short reaction time, high TON and TOF of catalyst.

A plausible mechanism of these oxidizing systems is shown in Scheme 3. The catalytic cycle involves, as fundamental step, the formation in the active site of a peroxovanadium species (III) [31, 32], which is a much stronger oxidant than H_2O_2 . This is followed by proton transfer from SVA to generate peroxidic species (V) [38, 39]. The nitrogen atom of 1,4-DHP attacked peroxidic oxygen(V) to produce hydroxylammonium ion (VI), then proton transfer from nitrogen to hydroxy group gives protonated *N*hydroxyl-1,4-dihydropyridine, and finally dehydration and deprotonation of protonated *N*-hydroxyl-1,4-dihydropyridine afford the pyridine as depicted in scheme 3 [40].

In conclusion, our goal in undertaking this line of work was fourfold: (a) to simplify operation due to the heterogeneous nature of reaction; (b) to develop a high yielding

Run	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15
Yield (%) ^a	97	97	97	97	97	97	97	97	97	97	95	95	95	95	95
Time (min)	10	10	10	10	10	10	10	10	15	15	15	15	15	15	15

 Table 4
 The catalytic activity of SVA in 15 cycles for the oxidation of 3,5-diacetyl-1,4-dihydro-2,6-dimethylpyridine with hydrogen peroxide in acetonitrile

^a Isolated yield

 Table 5 Comparison of the oxidation of diethyl 1,4-dihydro-2,6-dimethylpyridine-3,5-dicarboxylate to diethyl 2,6-dimethylpyridine-3,5-dicarboxylate, the reported catalysts versus silica vanadic acid

Entry	Catalyst	Solvent	Time (min)	Yield (%) ^a	TON ^d	TOF ^e (min ⁻¹)	
1	Silica vanadic acid	CH ₃ CN	10	95 [our work] ^b	180.62	18.062	
2	Mn(pbdo) ₂ Cl ₂ /MCM-41	AcOH	90	97 [35] °	_	_	
3	Mn(salophenl)/TBAO	CH_2Cl_2	30	90 [<mark>36</mark>]	13.43	0.447	
4	Fe(ClO ₄) ₃	AcOH	90	88 [37]	44	0.48	
5	Pd/C	AcOH	210	84 [13]	8.4	0.04	
6	Co(OAc) ₂	CH ₃ OH	15	98 [17]	_	_	

^a No recovery

^b Recovered fifteen times

^c Recovered three times

^d Turnover number

^e Turnover frequency

Scheme 3 The proposed mechanism of aromatization of 1,4-DHPs



conversion of 1,4-dihydropyridines to their corresponding pyridines; (c) to apply the catalytic system with high recycling by using a novel synthetic silica-based oxidant; (d) to apply room temperatures for these conversions.

Acknowledgments Financial support for this work by the Center of Excellence of Development of Chemical Methods (CEDCM) of Bu Ali Sina University, Hamedan, Iran is gratefully acknowledged.

References

- M.R. Maurya, A. Kumar, J.C. Pessoa, Coord. Chem. Rev. 255, 2315 (2011)
- 2. B.M. Weckhuysen, D.E. Keller, Catal. Today 78, 25 (2003)
- 3. R. Neumann, M. Leavin-Elad, Appl. Catal. A 122, 85 (1995)
- A. Bottino, G. Capannelli, A. Comite, S. Storace, R. Di, Felice. Chem. Eng. J. 94, 11 (2003)
- 5. M.A. Zolfigol, M. Safaiee, Synlett 5, 827 (2004)
- 6. M.A. Chari, K. Syamasundar, Catal. Commun. 6, 624 (2005)
- 7. M.A. Zolfigol, P. Salehi, M. Safaiee, Lett. Org. Chem. **3**, 39 (2006)
- G. Sabitha, G.S.K.K. Reddy, C.S. Reddy, J.S. Yadav, Tetrahedron Lett. 44, 4129 (2003)
- A. Ghorbani-Choghamarani, M.A. Zolfigol, M. Hajjami, S. Rastgoo, S. Mallakpour, Lett. Org. Chem. 7, 249 (2010)
- 10. X. Cai, H. Yang, G. Zhang, Can. J. Chem. 83, 273 (2005)
- M. Litvic, I. Cepanec, M. Filipan, K. Kos, A. Bartolincic, V. Druskovic, M.M. Tibi, V. Vinkovic, Heterocycles 65, 23 (2005)
- 12. J.J. Xia, G.W. Wang, Synthesis (14), 2379 (2005)
- N. Nakamichi, Y. Kawashita, M. Hayashi, Org. Lett. 4, 3955 (2002)
- M.M. Sadeghi, I. Mohammadpoor-Baltork, H.R. Memarian, S. Sobhani, Synth. Commun. 30, 1661 (2000). and references cited therein
- M.A. Zolfigol, A. Ghorbani Choghamarani, S. Dialameh, M.M. Sadeghi, I. Mohammadpoor-Baltork, H.R. Memarian, J. Chem. Res-S. (2003) 18, and references cited therein
- M.A. Zolfigol, F. Shirin, A. Ghorbani Choghamarani, I. Mohammadpoor-Baltork, Phosphorus. Sulfur. **178**, 1709 (2003). and references cited therein
- M.M. Hashemi, Y. Ahmadibeni, H. Ghafuri, Monatshefte Fur. Chem. 134, 107 (2003)
- M.A. Zolfigol, M.M. Sadeghi, I. Mohammadpoor-Baltork, A. Ghorbani-Choghamarani, A. Taqian-Nasab, Asian J. Chem. 13, 887 (2001)

- M. Anniyappan, D. Muralidharan, P.T. Perumal, Tetrahedron 58, 5069 (2002)
- G. Sabitha, G.S.K. Kumar Reddy, C.S. Reddy, N. Fatima, J.S. Yadav, Synthesis 8, 1267 (2003)
- S.P. Chavan, R.K. Kharul, U.R. Kalkote, I. Shivakumar, Synth. Commun. 38, 1333 (2003)
- B. Zeynizadeh, K.A. Dilmaghani, A. Roozijoy, J. Chem. Res. (S). (2005) 675
- B. Zeynizadeh, K.A. Dilmaghani, A. Roozijoy, Synth. Commun. 35, 557 (2005)
- M. Nasr-Esfahani, M. Moghadam, S. Tangestaninejad, V. Mirkhani, Bioorg. Med. Chem. Lett. 15, 3276 (2005)
- M. Nasr-Esfahani, M. Moghadam, S. Tangestaninejad, V. Mirkhani, A.R. Momeni, Bioorg. Med. Chem. 14, 2720 (2006)
- Z. Liu, W. Yu, Li Yang, Z.L. Liu, Tetrahedron Lett. 48, 5321 (2007)
- A.C. Shaikh, C. Chinpiao, Bioorg. Med. Chem. Lett. 20, 3664 (2010)
- X. Liao, W. Lin, J. Lu, C. Wanga, Tetrahedron Lett. 51, 3859 (2010)
- 29. M. Mirza-Aghayan, R. Boukherroub, M. Nemati, M. Rahimifard, Tetrahedron Lett. **53**, 2473 (2012)
- M.A. Zolfigol, M. Bagherzadeh, K. Niknam, F. Shirini, I. Mohammadpoor-Baltork, A. Ghorbani, A. Ghorbani Choghamarani, M. Baghbanzadeh, J. Iran. Chem. Soc. 3, 73 (2006)
- M.A. Zolfigol, A. Khazaei, M. Safaiee, M. Mokhlesi, R. Rostamian, M. Bagheri, M. Shiri, H.G. Kruger, J. Mol. Catal. A. Chem. 370, 80 (2013)
- A. Khazaei, M.A. Zolfigol, M. Safaiee, M. Mokhlesi, E. Donyadari, M. Shiri, H.G. Kruger, Catal. Commun. 26, 34 (2012)
- M.A. Zolfigol, P. Salehi, A. Ghorbani Choghamarani, M. Safaiee, M. Shahamirian, Synth. Commun. 37, 1817 (2007)
- M.A. Zolfigol, A. Ghorbani Choghamarani, M. Shahamirian, M. Safaiee, I. Mohammadpoor-Baltork, S. Mallakpour, M. Abdollahi-Alibeik, Tetrahedron Lett. 46, 5581 (2005)
- M.M. Heravi, H.A. Oskooie, R. Malakooti, B. Alimadadi, H. Alinejad, F.K. Behbahani, Catal. Commun. 10, 819 (2009)
- M. Nasr-Esfehani, M. Moghadam, G. Valipour, Synth. Commun. 39, 3867 (2009)
- M.M. Heravi, F.K. Behbahani, H.A. Oskooie, R. Hekmat Shoar, Tetrahedron Lett. 46, 2775 (2005)
- V. Conte, A. Coletti, B. Floris, G. Licini, C. Zonta, Coord. Chem. Rev. 255, 2165 (2011)
- 39. O. Bortolini, V. Conte, J. Inorg. Biochem. 99, 1549 (2005)
- 40. Z.Y. Chen, W. Zhang, Chin. Chem. Lett. 18, 1443 (2007)